



Deactivation in continuous deoxygenation of C18-fatty feedstock over Pd/C

Madsen, Anders Theilgaard; Rozmyslowicz, Bartosz; Mäki-Arvela, Päivi; Eränen, Kari; Murzin, Dmitry Yu.; Fehrmann, Rasmus

Publication date:
2012

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Madsen, A. T., Rozmyslowicz, B., Mäki-Arvela, P., Eränen, K., Murzin, D. Y., & Fehrmann, R. (2012). *Deactivation in continuous deoxygenation of C18-fatty feedstock over Pd/C*. Abstract from 15th Nordic Symposium on Catalysis, Mariehamn, Åland Islands.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Deactivation in continuous deoxygenation of C₁₈-fatty feedstock over Pd/C

Anders Theilgaard Madsen^{1,2*}, Bartosz Rozmysłowicz², Päivi Mäki-Arvela², Kari Eränen, Dmitry Yu. Murzin², Rasmus Fehrmann¹.

1 – DTU Chemistry, Technical University of Denmark, Kemitorvet, 2800 Kgs. Lyngby, Denmark

2 – Process Chemistry Center, Åbo Akademi, Biskopsgatan 8, 20500 Turku/Åbo, Finland

* corresponding atm@kemi.dtu.dk

A promising type of biofuel is the so-called "renewable diesel", i.e. alkanes produced via deoxygenation of fats and oils. The most selective heterogeneous catalysts for decarbonylation and decarboxylation (loss of fatty acid functionality as CO or CO₂) are supported nanoparticles of platinum and palladium.

It is important to understand mechanistic details and deactivation behavior in the deoxygenation reactions to optimize catalyst performance, especially when working with more complex and often troublesome feedstocks like abattoir waste or grease from cooking. To this date only a few profound studies have been published about the deoxygenation of fatty feedstocks, but these have mostly dealt with free fatty acids. Studies until now indicate a somewhat complex reaction network between gas and liquid phases during deoxygenation.

Recently, a remarkable time-dependent shift in the gas production from CO₂ to CO has been observed during deoxygenation by several authors [1,2]. It has also been found that deactivation takes place via occlusion of the pores of the catalyst support [1,3], connected with the presence of unsaturated compounds leading to coking [4].

In this work, continuous deoxygenation has been performed of respectively neat stearic acid, ethyl stearate and tristearin at 300°C in a packed-bed reactor over an egg-shell impregnated catalyst of 2 wt% Pd on Sibunit carbon beads. 5% H₂/Ar at 20 bar was employed as sweeping gas, but after 75 h time-on-stream (stearic acid: 96 h) of uniform operation the gas atmosphere was changed to pure Ar. Both liquid and gas samples were collected for offline GC analysis during each experiment, and CO and CO₂ were measured by online IR.

The alkane production was in the order of reactants: stearic acid > ethyl stearate > tristearin, both initially and after 75 h (see Table 1). However, the switch to pure Ar gas led to swift deactivation, especially for the tristearin. The stearic acid furnished some hydrocarbons after the change to pure Ar sweeping gas, especially unsaturated C₁₇-compounds, while the ester feedstocks did not convert to hydrocarbons without H₂ in the feed.

Table 1: 300°C, 20 bar 5% H₂/Ar gas, 2 wt% Pd/Sibunit

	Deoxygenation to alkanes, yield			Post-reaction catalyst pore vol. (Fresh cat.: 361 m ² /g)
	After 0 h	After 75 h	After 150 h	
	Gas: 5% H ₂ /Ar	Gas: 5% H ₂ /Ar	Gas: Ar	
Stearic acid	>90%	75%	3%	193 m ² /g
Ethyl stearate	>90%	62%	0%	229 m ² /g
Tristearin	85%	28%	0%	200 m ² /g

After each reaction the catalyst beads were sampled in 5 batches and subjected to BET analyzes. No monotonic deactivation profile in axial direction was observed in the reactor although this has previously been observed [1]. The ethyl stearate catalyst appears to be least deactivated with respect to surface area loss (Table 1).

An experiment switching between neat dodecane and stearic acid was conducted over neat Sibunit beads in Ar gas, affording 5% conversion of stearic acid and revealing a startup-time of 3-4 h to reach steady-state. It can thus be concluded that the palladium-containing catalyst was completely deactivated after exposure to stearic acid for the entire 150 h experimentation.

References:

- [1] A.T. Madsen, B. Rozmysłowicz, I.L. Simakova, T. Kilpiö, A.-R. Leino, K. Kordás, P. Mäki-Arvela, K. Eränen, D.Y. Murzin, *Ind. Eng. Chem. Res.* 50 (2011) 11049
- [2] J.G. Immer, H.H. Lamb, *Energy Fuel*, 24 (2010) 5291
- [3] J.G. Immer, M.J. Kelly, H.H. Lamb, *Appl. Catal. A*, 375 (2010) 134
- [4] B. Rozmysłowicz, P. Mäki-Arvela, S. Lestari, O.A. Simakova, K. Eränen, I.L. Simakova, D.Y. Murzin, T.O. Salmi, *Top. Catal.* 53 (2010) 1274