Development of Superconducting Wind Turbine Generators

Jensen, Bogi Bech; Mijatovic, Nenad; Abrahamsen, Asger Bech

Published in:

Scientific Proceedings of EWEA 2012 - European Wind Energy Conference & Exhibition

Publication date:

2012

Document Version

Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):

Jensen, B. B., Mijatovic, N., & Abrahamsen, A. B. (2012). Development of Superconducting Wind Turbine Generators. In *Scientific Proceedings of EWEA 2012 - European Wind Energy Conference & Exhibition* European Wind Energy Association (EWEA).

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Development of Superconducting Wind Turbine Generators

Bogi B. Jensen¹, Nenad Mijatovic¹, Asger B. Abrahamsen²

¹ Department of Electrical Engineering, Technical University of Denmark, Denmark

² Department of Wind Energy, Technical University of Denmark, Denmark

18-04-2012

EWEA 2012 Copenhagen, Denmark

DTU Electrical Engineering
Department of Electrical Engineering

Development of wind turbines

$$\text{CoE} = \frac{\text{Annualised CAPEX and OPEX}}{\text{Annual energy production}}$$

5MW and beyond

Manufacturer	Transmission	Generator
Siemens Wind Power	Direct drive	PMSG 6.0MW
Vestas	Medium speed	PMSG 7.0MW
Enercon	Direct drive	EESG 7.5MW
Alstom	Direct drive	PMSG 6.0MW
REPower	High speed	DFIG 6.2MW
Areva	Low speed	PMSG 5.0MW

10MW and beyond – proposals/investigations

Manufacturer	Transmission	Generator
American Superconductor	Direct drive	HTS 10MW
General Electric	Direct drive	LTS 10-15MW
Advanced Magnet Lab	Direct drive	MgB ₂ 10MW

Schematic of a Superconducting Machine

- The superconductor must be kept at cryogenic temperatures
- The armature winding is usually proposed to be copper at ambient temperature

$$P = \omega \times T$$

$$T \propto A \times B \times V$$

P : power

T : torque

ω : rotational speed

A : electric loading

B : magnetic loading

V : volume

High Temperature Superconductors

- The superconducting state is limited by
 - Critical flux density B_c
 - Critical current density J_c
 - Critical temperature T_c

Overview of superconductors

Type	Price €/m	J_e A/mm ²	Flux density [T]	Temp. [K]
NbTi	0.4	10^3	5	4.2
Nb ₃ Sn	3	$1-4 \times 10^3$	5	4.2
MgB ₂	4	10^2	3	20
Bi-2223	20	390 10	3 $\perp$ tape 3 $\perp$ tape	20 50
YBCO	30	98 (480) 49 (190)	3 $\perp$ tape 3 $\perp$ tape	20 50

Cooling system

- The superconductors need to be cold:
 - <5K for LTS
 - <20K for MgB_2
 - 30-50K for HTS
- Insulation requires large effective airgap
 - Large fault currents and torques
- Torque transfer
- Reliability has yet to be proven and requires years of operating experience
- Production capacity of HTS and MgB_2 are currently not adequate for large-scale commercialisation – this should change if the need is present

Advantages

- Very high torque density

$$P = \omega \times T, \quad T \propto A \times B \times V$$

- Higher efficiency than an equivalent direct drive PM generator

$$P_{Cu} = I_{Cu}^2 R_{Cu} = J_{Cu}^2 A_{Cu}^2 \frac{l_{Cu}}{A_{Cu} \sigma_{Cu}} = \frac{J_{Cu}^2 V_{Cu}}{\sigma_{Cu}}$$

- Very limited dependence on rare earth materials

		PM	HTS
Hybrid		50kgR/MW	20gR/MW
Direct drive		250kgR/MW	100gR/MW

$$m_R = 0.27 m_{R-B-Fe}$$

American Superconductor (AMSC) SeaTitan 10MW

- HTS – Superconducting field winding
- Copper armature winding
- Generator diameter: 4.5–5 meters
- Weight: 150-180 tonnes (55-66Nm/kg)
- Efficiency at rated load: 96%

- Challenge
 - HTS price and availability
- Advantage
 - Relatively simple cooling system with off-the-shelf solutions
 - Cooling power

Highest torque HTS machine intended for ship propulsion:

- 36.5MW @ 120rpm
- 2.9MNm @ 75 tons
- 39Nm/kg

Reproduced with permission from AMSC

General Electric (GE) 10-15MW

- LTS – Superconducting field winding
- Extensive experience from the MRI sector
- Rotating armature
- Challenge
 - Complicated cooling system and higher cooling power
- Advantage
 - Proven technology from MRI
 - Cheaper superconductor

Reproduced with permission from GE

Advanced Magnet Lab (AML) 10MW fully superconducting

- MgB_2 – Fully superconducting generator
- Superconducting field winding
- Superconducting armature winding
- Challenge
 - Complicated cooling system and higher cooling power
 - Improvement in MgB_2 wire is needed
- Advantage
 - Cheap superconductor
 - Fully superconducting
 - More torque dense

Reproduced with permission from AML

$$P = \omega \times T, \quad T \propto A \times B \times V$$

Patent Development

- Web of Knowledge search with keywords: "Supercond*" and "machin*"

Discussion and conclusion

- Superconducting generators might be the answer to large wind turbines
 - Smaller generator
 - Less RE demand by a three orders of magnitude
- A collaborative effort is needed including:
 - Wire manufacturers
 - Wind turbine manufacturers
 - Wind turbine operators
- Large-scale demonstrators are needed
 - To test the performance in a wind turbine
 - To test the reliability
- Thank you