Thermally tunable bandgaps in a hybrid As₂S₃/silica photonic crystal fiber

Markos, Christos; Stefani, Alessio ; Bang, Ole

Published in:
Proceedings of SPIE

Link to article, DOI:
[10.1117/12.2194822](https://doi.org/10.1117/12.2194822)

Publication date:
2015

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Markos, C., Stefani, A., & Bang, O. (2015). Thermally tunable bandgaps in a hybrid As₂S₃/silica photonic crystal fiber. In *Proceedings of SPIE* (Vol. 9634). [96343G] SPIE - International Society for Optical Engineering. Proceedings of SPIE - The International Society for Optical Engineering <https://doi.org/10.1117/12.2194822>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Thermally tunable bandgaps in a hybrid As₂S₃/silica photonic crystal fiber

Christos Markos*, Alessio Stefani and Ole Bang

DTU Fotonik, Department of Photonics Engineering, Technical University of Denmark, DK-2800 Kgs. Lyngby, Denmark

ABSTRACT

We report the fabrication and characterization of a hybrid silica photonic crystal fiber (PCF) with integrated chalcogenide glass layers and we show how the bandgaps of the fiber can be thermally tuned. The formation of the high-index chalcogenide films on the inner surface of the PCF holes revealed resonances as strong as ~35 dB both in the visible and infrared regime. Temperature measurements indicate that the transmission windows can be tuned with a sensitivity as high as ~3.5 nm/°C. The proposed fiber has potential for all-fiber filtering and temperature sensing.

Keywords: Chalcogenide glass, hybrid fiber, nonlinear materials, tunable bandgaps, fiber device

1. INTRODUCTION

One of the main advantage of photonic crystal fibers (PCFs) is the ability to control their guiding properties by modifying the geometric characteristics of the cladding holes, such as hole size, pitch, etc.¹. PCFs are usually made from glass¹ or polymer² or even a combination of other materials³. Silica-based PCFs are mainly used for sensing devices and generation of supercontinuum⁴. On the other hand, polymer planar waveguides or PCFs are used for the development of polymer Bragg grating sensors⁵⁻⁸ or biosensors^{9,10} due to their low Young's modulus and biocompatibility properties, respectively. The ability to infiltrate the cladding holes of the PCF with novel functional nanomaterials created a new class of fibers known as *hybrid PCFs*¹¹. Several research groups around the globe are working towards the development of novel tunable fiber devices by combining different advanced optical materials with PCFs, such as polymeric organosilicon compounds¹²⁻¹⁴, liquid crystals¹⁵, chalcogenide glasses^{16,17}, etc. Recently it has been shown that even soft-glasses can be integrated within polymer PCFs¹⁸. In this paper, we demonstrate the deposition of nanometer-scaled thick As₂S₃ films inside the holes of a silica PCF¹⁶. The high index films introduce an antiresonant guidance mechanism and we present preliminary results on how the high thermo-optic coefficient of chalcogenide glass films compared to the silica host material, provide the ability to tune the bandwidth of the resonant windows. The thermal sensitivity was found to be as high as ~3.5 nm/°C from 22°C up to 70°C.

2. HYBRID AS₂S₃/SILICA PCF CHARACTERIZATION

2.1 Chalcogenide glass solution and fiber preparation

For our experiments we used commercially available bulk chalcogenide glass with the stoichiometric composition of As₂S₃. The bulk glass was then grinded into powder and dissolved in ethylenediamine (EDA) in concentration of ~50mg/ml. In order to expedite the dissolution process of the glass, the nanocolloidal solution was stirred for 2 days at room temperature. The final solution was then infiltrated inside the holes of a silica PCF by means of capillary forces and placed inside the fume hood at room temperature to allow the solvent to be removed smoothly. The fiber was then further annealed at 100°C for 12 hours to achieve the maximum solvent evaporation. The final filled length was ~5 cm. The initial silica PCF used in our experiments was an ESM-12 (by NKT Photonics) with hole diameter $d = 3.5$ μm and pitch (distance between the holes) $\Lambda = 7.7$ μm . The outer diameter of the fiber was 125 μm . Figure 1(a) shows a scanning electron micrograph (SEM) image of the hybrid As₂S₃/silica PCF and Fig. 1(b) shows a section of the cladding holes with formed nanoscaled-thick chalcogenide glass layers. In order to further verify the existence of the As-S glass inside the holes of the fiber we used Energy-dispersive X-ray (EDX) spectroscopy.

*chmar@fotonik.dtu.dk; phone +45 45 25 63 87;

Figure 1 (c) shows the EDX spectrum, which confirms the existence of As and S elements in the coated inner surface of the holes of the PCF. The accurate determination of the thickness of the formed chalcogenide glass films was not possible because the thickness of the layers was a few tens of nanometers. One possible way to determine the exact thickness of the films is to use Atomic Force Microscopy (AFM), which has a resolution down to few nanometers.

Figure 1. (a) SEM image of the hybrid chalcogenide/silica PCF (b) Angled cleaved end-facet of the fiber showing the cladding holes of the fiber having thin chalcogenide films. (c) EDX spectrum clearly indicating the presence of As and S lines.

2.2 Characterization of the hybrid PCF

The characterization of the hybrid PCFs was made using a supercontinuum source (SuperK Versa, NKT Photonics) with a spectrum from 475 – 2000 nm. The light was coupled in the fiber using a 40x microscope objective and the output beam was expanded using a 100x objective. Any undesired cladding light was blocked using an iris while only the light from the core was collected using a 10x objective and a multimode fiber. All measurements were recorded with an Optical Spectrum Analyzer (OSA) with minimum resolution of 0.1 nm. Figure 2 shows the experimental set-up and the near field profile of the fiber recorded with a high resolution CCD camera indicating the presence of the field in the high index inclusions.

Figure 2. Experimental set-up and the near-field profile of the fundamental guided mode showing that a certain fraction of the light is guided in the high index films.

3. RESULTS AND CONCLUSIONS

Chalcogenide glasses possess, apart their extremely high nonlinearity¹⁹, also other important properties, such as a reversible photostructural effects under illumination close to the bandgap of the material, as well as relatively high thermo-optic coefficient^{18,20}. In this work, we investigated the thermo-optic effect of thin chalcogenide glass films formed from an initial nanocolloidal glass solution. The high-index inclusions revealed antiresonant guidance with transmission bands as strong as ~35 dB, as shown in Fig. 3 (a). The position of the resonant windows depends on the refractive index of the high-index films, their thickness and the geometry of the initial PCF. The transmission dips can be predicted using the ARROW model²¹. Figures 3(a) and 3(b) show the transmission spectra of the hybrid fiber for increasing and decreasing the temperature from room up to 70°C, respectively. It is clear that the red-edge of the

transmission windows is blue-shifting when the temperature increases. This is because the refractive index contrast between silica and chalcogenide is decreasing due to the negative thermo-optic coefficient of the high-index chalcogenide films²⁰. Similar behavior has also been reported in a polymer fiber filled with chalcogenide¹⁸ and liquid crystals^{15,22}. Figure 3 (c) shows how the bandgap edge at 1300 nm shifts over a full cycle of temperature variation indicating the thermal tunability of the bandgaps. The temperature sensitivity was found 3.52 nm/°C.

Figure 3. (a) Transmission spectra of the As_2S_3 /silica PCF as the temperature increases from 22°C to 70°C. (b) Transmission spectra of the same fiber sample as the temperature decreases from 70°C to 22°C. (c) Bandgap red-edge shift vs. temperature over a full cycle for the transmission window at 1300 nm.

In conclusion we presented the development of a hybrid As_2S_3 /silica PCFs using a cost-effective approach, which allows the possibility of tuning the resonant transmission windows by changing the temperature. The sensitivity was found to be about 3.5 nm/°C. Liquid crystal filled-PCFs have shown sensitivity up to 6.6 nm/°C²². However it should be emphasized that our proposed technique provides the possibility for further functionalization of the fiber because the air holes are still available to host other materials or analytes. Therefore, the proposed method opens the door to the possibility for the development of all-fiber multi-functional fiber devices for sensing, filtering and nonlinear applications.

4. ACKNOWLEDGMENTS

C.M acknowledges the Carlsberg Foundation for financial support. The authors acknowledge the support from the Danish foundation 'Innovationsfonden' as part of the innovation consortium BIOFORS, contract no. 1382-00058B.

REFERENCES

- [1] Birks, T. A., Knight, J. C. and Russell, P. St.J., "Endlessly single-mode photonic crystal fiber," *Opt. Lett.* 22 (13), 961-963 (1997).
- [2] van Eijkelenborg, M., Large, M., Argyros, A., Zagari, J., Manos, S., Issa, N., Bassett, I., Fleming, S., McPhedran, R., Martijn de Sterke, C. and Nicorovici, N. A., "Microstructured polymer optical fibre," *Opt. Express* 9 (7), 319-327 (2001).

- [3] Abouraddy, A. F., Bayindir, M., Benoit, G., Hart, S. D., Kuriki, K., Orf, N., Shapira, O., Sorin, F., Temelkuran, B. and Fink, Y., "Towards multimaterial multifunctional fibres that see, hear, sense and communicate," *Nat. Mater.* 6 (5), 336–347 (2007).
- [4] Dudley, J. M., Genty, G. and Coen, S., "Supercontinuum generation in photonic crystal fiber," *Rev. Mod. Phys.* 78 (4), 1135–1184 (2006).
- [5] Xiong, Z., Peng, G. D., Wu, B. and Chu, P. L., "Highly tunable Bragg gratings in single-mode polymer optical fibers," *IEEE Photon. Technol. Lett.* 11(3), 352–354 (1999).
- [6] Stefani, A., Yuan, W., Markos, C., and Bang, O., "Narrow bandwidth 850 nm fiber Bragg gratings in few-mode polymer optical fibers," *IEEE Photon. Technol. Lett.* 23(10), 660–662 (2011).
- [7] Markos, C., Stefani, A., Nielsen, K., Rasmussen, H. K., Yuan, W., Bang, O., "High-Tg TOPAS microstructured polymer optical fiber for fiber Bragg grating strain sensing at 110 degrees," *Opt. Express* 21 (4), 4758–4765 (2013).
- [8] Rosenberger, M., Hessler, S., Belle, S., Schmauss B. and Hellmann R., "Fabrication and characterization of planar Bragg gratings in TOPAS polymer substrates," *Sens. Actuators A*, 221 (1), 148–153 (2015).
- [9] Emiliyanov, G., Hoiby, P.E., Pedersen, L.H., Bang, O., "Selective serial multi-antibody biosensing with TOPAS microstructured polymer optical fibers," *Sensors* 13 (3), 3242–3251 (2013).
- [10] Markos, C., Yuan, W., Vlachos, K., Town, G. E. and Bang, O., "Label-free biosensing with high sensitivity in dual-core microstructured polymer optical fibers," *Opt. Express* 19(8), 7790–7798 (2011).
- [11] Cerqueira S. Jr., A., Luan, F., Cordeiro, C. M. B., George, A. K. and Knight, J. C., "Hybrid photonic crystal fiber," *Opt. Express* 14 (2), 926–931 (2006).
- [12] Markos, C., Antonopoulos, G. and Kakarantzas, G., "Broadband guidance in a hollow-core photonic crystal fiber with polymer-filled cladding," *IEEE Photonics Technol. Lett.* 25(20), 2003–2006, (2013).
- [13] Markos, C., Vlachos, K., Kakarantzas, G., "Guiding and birefringent properties of a hybrid PDMS/silica photonic crystal fiber," *Proc. SPIE* 7914, 791427 (2011).
- [14] Markos, C., Vlachos, K. and Kakarantzas, G., "Guiding and thermal properties of a hybrid polymer-infused photonic crystal fiber," *Opt. Mater. Express* 2 (7), 929–941 (2012).
- [15] Yuan, W., Wei, L., Alkeskjold, T. T., Bjarklev, A. and Bang, O., "Thermal tunability of photonic bandgaps in liquid crystal infiltrated microstructured polymer optical fibers," *Opt. Express* 17 (22), 19356–19364 (2009).
- [16] Markos, C., Yannopoulos, S. N. and Vlachos, K., "Chalcogenide glass layers in silica photonic crystal fibers," *Opt. Express* 20 (14), 14814–14824 (2012).
- [17] Granzow, N., Uebel, P., Schmidt, M. A., Tverjanovich, A. S., Wondraczek, L. and Russell, P. St. J., "Bandgap guidance in hybrid chalcogenide–silica photonic crystal fibers," *Opt. Lett.* 36 (13), 2432–2434 (2011).
- [18] Markos, C., Kubat, I. and Bang, O., "Hybrid polymer photonic crystal fiber with integrated chalcogenide glass nanofilms" *Sci. Rep.* 4, 6057, (2014).
- [19] Eggleton, B. J., Luther-Davies, B., Richardson, K., "Chalcogenide photonics," *Nature Photon.* 5, 141–148 (2011).
- [20] Zakery, A. and Elliott, S. R., [Optical Nonlinearities in Chalcogenide Glasses and their Applications] Springer, New York (2007).
- [21] Litchinister, N. M., Abeeluck, A. K., Headley, C. and Eggleton, B. J., "Antiresonant reflecting photonic crystal optical waveguides," *Opt. Lett.* 27, 1592–1594 (2002).
- [22] Wei, L., Eskildsen, L., Weirich, J., Scolari, L., Alkeskjold, T. T. and Bjarklev, A., "Continuously tunable all-in-fiber devices based on thermal and electrical control of negative dielectric anisotropy liquid crystal photonic bandgap fibers," *Appl. Opt.* 48, 497–503 (2009).