Effect of NO₂ and water on the catalytic oxidation of soot

Christensen, Jakob Munkholt; Grunwaldt, Jan-Dierk; Jensen, Anker Degn

Published in:
Applied Catalysis B: Environmental

Link to article, DOI:
[10.1016/j.apcatb.2016.12.024](https://doi.org/10.1016/j.apcatb.2016.12.024)

Publication date:
2017

Document Version
Peer reviewed version

[Link back to DTU Orbit](#)

Citation (APA):
Christensen, J. M., Grunwaldt, J-D., & Jensen, A. D. (2017). Effect of NO₂ and water on the catalytic oxidation of soot. *Applied Catalysis B: Environmental*, 205, 182-188. <https://doi.org/10.1016/j.apcatb.2016.12.024>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Effect of NO₂ and water on the catalytic oxidation of soot

Jakob M. Christensen^{1*}, Jan-Dierk Grunwaldt^{1,2} and Anker D. Jensen¹

¹*Department of Chemical and Biochemical Engineering, Technical University of Denmark, Søtofts*

Plads B229, 2800 Kgs. Lyngby (Denmark)

²*Institute for Chemical Technology and Polymer Chemistry (ITCP), Karlsruhe Institute of*

Technology, Engesserstrasse 20, 76131 Karlsruhe (Germany)

**Corresponding author: jmc@kt.dtu.dk*

Abstract

It has been investigated how the addition of NO₂ to 10 vol% O₂/N₂ influences non-catalytic soot oxidation and soot oxidation in intimate or loose contact with a catalyst. In non-catalytic soot oxidation the oxidation rate is increased significantly at lower temperatures by NO₂. For soot oxidation in tight contact with a Co₃O₄ catalyst a more reactive NO₂-containing atmosphere did not change the oxidation profile significantly during temperature programmed oxidation. This is consistent with the expected Mars van Krevelen mechanism, where the rate limiting step is reaction between carbon and oxide, and where the reaction thus has reached the 0. order regime in the gaseous reactant. In loose contact with a catalyst the presence of NO₂ causes a pronounced enhancement of the oxidation rate. The rate constants for loose contact soot oxidation in the presence of NO₂ exhibited a volcano-curve dependence on the heat of oxygen chemisorption, and among the tested pure metals and oxides Cr₂O₃ was the most active catalyst. Further improvements were achieved with a Fe_aCr_bO_x binary oxide catalyst.

Keywords: Soot oxidation, Nitrogen dioxide, Mars van Krevelen mechanism, Volcano curve, Spillover.

1. Introduction

Soot particles in the exhaust from diesel vehicles adversely affect human health [1-3], and are therefore typically removed from the exhaust gas by filtration through a ceramic filter [4-6]. As the filter becomes blocked by the soot particles, periodic regeneration is necessary. For this purpose the filter temperature is increased, and the soot is oxidized. The growing back pressure due to the soot deposits and the temperature increase required for filter regeneration are associated with increased fuel consumption [7], and it is desirable to develop improved soot oxidation catalysts that can lower the regeneration temperature [4]. Being a gas/solid/solid interaction, where the contact between soot and catalyst is very important, the catalytic effect depends strongly on the intimacy of mixing between soot and catalyst [8, 9]. In laboratory tests, where soot and catalyst are crushed together (so-called tight contact), the oxidation occurs at a significantly lower temperature (typically 100-200 °C), than if soot and catalyst are mixed together gently (so-called loose contact) [8, 9]. In tight contact an extensive interface between the primary particles of soot and catalyst is established, but in loose contact the interface is limited to isolated contact points between larger clusters of the primary particles [10]. A number of filtration experiments have shown indications of reactivity corresponding to both contact types [11-17]. It therefore seems likely that both types of contact would be relevant for real filter applications.

To enable the development of improved soot oxidation catalysts the factors that determine the catalytic activity need to be identified. As expected the surface area of the employed catalyst is important [18, 19], and the strength of the oxygen-catalyst bond, as measured by the heat of oxygen chemisorption, is also very important for the catalytic activity [20]. For both tight and loose contact tests with O₂ as the oxidant the rate constants for various metal or metal oxide catalysts resulted in a

volcano curve if plotted as function of the heat of oxygen chemisorption for the catalytic materials [20]. In tight contact materials such as Co_3O_4 and CeO_2 that bind oxygen more weakly were found to be nearest to the optimal bond strength, while the more strongly binding Cr_2O_3 was nearest to the activity optimum in loose contact [20]. The shift in the optimal material may reflect the existence of multiple reaction pathways that contribute with different relative weight in the two cases. In tight contact tests TEM studies [21, 22], isotopic labeling studies [23-28] and XPS studies [29] have indicated that the oxidation primarily occurs at the soot/catalyst interface by a Mars van Krevelen [30] mechanism, namely an initial oxidation by catalyst lattice oxygen followed by re-oxidation of the catalyst. The rate limiting step is most likely the reaction of lattice oxygen with carbon, since the reaction rate depends on both the oxygen bond strength of the catalyst [20] and the inherent reactivity of the soot [19]. In loose contact tests the activation of oxygen occurs on the oxide [28, 31-34], and most likely the activated oxygen then diffuses to the soot [35-37], and reacts at the most reactive defect sites [38, 39]. A catalytic effect is also present in experiments where soot and catalyst are separated by an inert (and insulating) material that the activated oxygen must pass to reach the soot [32, 36], and it therefore seems likely that the oxygen activation is by dissociative chemisorption into atomic oxygen that would remain reactive [40] also when removed from the catalyst surface.

The absolute rate of soot oxidation will also depend on the gas atmosphere [41-43]. The example of greatest practical importance is that many filter regeneration strategies for diesel vehicles involve acceleration of the soot oxidation by catalytically oxidizing NO in the exhaust gas to NO_2 [44-46], which is a more reactive oxidant than O_2 [46-50]. There are known examples, where the volcano curve for a catalytic reaction, and thus the optimal choice of catalyst, is shifted depending on the gas atmosphere [51, 52]. It is therefore relevant to evaluate, how the components in the gas atmosphere, particularly NO_2 , influence the catalytic reaction and optimal choice of catalyst, also as

a function of the contact between soot and catalyst. This is the topic of the present paper.

Additionally, this work provides global kinetic parameters for the occurring oxidation reactions, which may be of use for CFD-based models of soot combustion dynamics in catalytic diesel particulate filters [53, 54].

2. Experimental

2.1 Catalysts used for screening experiments

The catalysts used in the screening studies were the bulk oxides or metals also used in our previous study, where the identities of the catalysts were confirmed by XRD [20]. In the cases of γ -Fe₂O₃, Pd and Pt commercially acquired samples from Sigma-Aldrich were used. In the cases of CeO₂, Co₃O₄, MnO_x, ZnO and Cr₂O₃ the oxide samples were prepared by flame spray pyrolysis according to the method described elsewhere [19, 20].

2.2 SiO₂ supported FeCr₂O_x binary oxide catalyst

An SiO₂ supported FeCr₂O_x catalysts also employed in our previous study [20] was used. SiO₂ extrudates (Saint-Gobain, 250 m²/g) were impregnated with an aqueous solution of Fe(NO₃)₃·9H₂O and Cr(NO₃)₃·9H₂O (Sigma Aldrich) to produce FeCr₂O_x/SiO₂ with a total metal loading of 14.8 wt%. The impregnated sample was aged for 2 h and then dried at 110 °C overnight. The dried catalyst precursor was then calcined in stagnant air for 2 h at 500 °C (ramp: 20 °C/min). Finally the

calcined catalyst was crushed to $< 300\ \mu\text{m}$ and used in the powdered form. The XRD pattern of the catalyst contains the reflections from $\alpha\text{-Cr}_2\text{O}_3$ shifted slightly downwards towards the reflections from $\alpha\text{-Fe}_2\text{O}_3$ suggesting the formation of a mixed oxide [20].

2.3 Catalytic soot oxidation

The catalytic activity in soot oxidation was measured using a flow reactor setup described elsewhere [20]. For the activity tests soot ($\sim 2\ \text{mg}$, NIST SRM 2975) and catalyst in a ratio of 1:5 (wt:wt) were stirred together with a spatula (loose contact) or crushed together for 6 minutes in an agate mortar (tight contact). The silica supported Fe-Cr binary oxide catalyst was tested at a higher soot:catalyst ratio of 1:10 (wt:wt) due to the lower fraction (15 wt%) of active material in this sample. The soot/catalyst mixture was transferred to a 7 cm long, 1 cm wide alumina sample holder, which was placed in the center of a quartz tube (length: 65 cm, inner diameter: 24 mm) within a horizontal, tubular furnace. The sample was then subjected to a 1 NL/min flow of 10.2 vol% O_2 in N_2 (in some cases the feed also contained 934 ppmv NO_2 or 887 ppmv NO_2 and 5 vol% H_2O). The feed gases (N_2 , O_2 and 1040 ppmv NO_2 in N_2 - all from AGA A/S) were dosed by means of Bronkhorst EL-FLOW mass flow controllers. Distilled water was fed using a Knauer K-120 HPLC pump. When the sample had been installed in the oven, and once any remnants of air had been purged from the reactor (when the CO_2 signal from ambient air had fallen below the detection limit) the reactor was heated at a rate of $11\ ^\circ\text{C}/\text{min}$ to a final temperature of $750\ ^\circ\text{C}$. The temperature was monitored by a type K thermoelement at the external surface of the quartz tube wall. The concentrations of CO and CO_2 in the reactor effluent were monitored continuously using an ABB AO2020 IR gas analyzer calibrated using a certified CO/ CO_2 / N_2 gas mixture from AGA A/S. When water was fed, the reactor effluent was passed through an ice cooled U-tube condenser to avoid that water interfered with the CO/ CO_2 analysis. During the experiments with NO_2 the levels of CO and

CO₂ in the effluent stream were in the 0-200 ppmv range. The conversion of gaseous reactants due to the soot oxidation was thus relatively limited, and the dependence on the oxidant concentration was omitted in the kinetic analyses.

The soot used in the present experiments was a reference material from NIST: “SRM 2975 Diesel Particulate Matter” (from an Industrial Forklift). Various characterizations of this carbonaceous material can be found in the literature [19, 55-57].

2.4 Kinetic analysis

The results have been interpreted in terms of a simple, global kinetic model (assuming differential conditions in the gas phase), where catalytic and non-catalytic oxidation by O₂ and NO₂ are assumed to occur by 4 parallel reactions:

$$\frac{dX}{dt} = k_{NO_2,cat} (1-X)^{2/3} + k_{O_2,cat} (1-X)^{2/3} + k_{NO_2,non-cat.} (1-X)^{2/3} + k_{O_2,non-cat.} (1-X)^{2/3}$$

Here X is the degree of carbon conversion, and k is the rate constant for either catalytic or non-catalytic oxidation by either O₂ or NO₂. The degree of conversion is obtained from numerical integration of the CO and CO₂ signals. The kinetic parameters for soot oxidation by O₂ were taken from our previous study of oxidation in the absence of NO₂ [20]. The kinetic parameters for non-catalytic oxidation by NO₂ were determined in the absence of a catalyst, and the kinetic parameters for catalytic oxidation by NO₂ are then fitted to the results from the present catalytic experiments. The obtained kinetic parameters are listed in table S2 in the supplementary information. The assumption of oxidation by O₂ and NO₂ as parallel reactions is supported by the results of Arthur et al. [49]. Across all the tested samples (both non-catalytic oxidation as well as loose and tight

contact catalytic oxidation) the best fit for the simple kinetic model was achieved with a carbon reaction order of $\frac{2}{3}$. This is consistent with the soot particles behaving as uniformly shrinking spheres [58]. However, as discussed elsewhere [59], other situations may lead to similar reaction orders. An evaluation of the present results in terms of the temperature of maximal oxidation rate (the optimum between the increase in reaction rate with temperature and the decline in reaction rate with increasing reactant consumption), which is another common measure of activity in soot oxidation, generally yields the same conclusions, and such an analysis is provided in the supplementary information (figure S1).

3. Results and Discussion

3.1 Soot oxidation in the presence of NO_2

Figure 1 shows the rate of soot oxidation in a gas atmosphere containing various combinations of O_2 , NO_2 and H_2O with and without the presence of a Cr_2O_3 catalyst ($17 \text{ m}^2/\text{g}$) in loose contact with the soot. In agreement with previous work [46-50] the results show that the presence of NO_2 significantly increases the soot oxidation rate in the 250-550 °C range, although the temperature of the maximal oxidation rate for non-catalytic oxidation does not change significantly in the presence of NO_2 . The beneficial effect of NO_2 could be related to the fact that the strength of the O-NO bond in NO_2 is substantially weaker ($D_{298K}^{\circ} = 305 \frac{\text{kJ}}{\text{mol}}$) than the strength of the O-O bond in O_2 ($D_{298K}^{\circ} = 498.36 \frac{\text{kJ}}{\text{mol}}$) [60]. Furthermore NO_2 is also a radical species that decomposes to NO and O radicals with relative ease, especially in the presence of a catalytic surface [61-63]. It has also previously been proposed that the NO_2 activation is by dissociation to yield atomic oxygen [49], which is known to react with graphite with a high probability [40].

Compared to oxidation with O_2 alone, the presence of NO_2 leads to an increased fraction of the carbon being released as CO_2 , particularly in the 250-550 °C range where oxidation by NO_2 is most important, and this effect is further increased by the presence of water (supplementary information, figures S6-S8).

Figure 1 shows that at lower temperatures the NO_2 assisted rate is further increased by the presence of water. The present observation of a doubling of the non-catalytic, NO_2 assisted reaction rate at 300 °C by the addition of 5 vol% H_2O is in good agreement with other studies using similar concentrations of NO_x and H_2O [46, 64, 65]. The beneficial effect of water requires the presence of NO_x , as the addition of water to the O_2/N_2 feed is without effect on the oxidation rate. It has previously been suggested [41, 65-68] that the effect of water and NO_x is due to the impact of protonated species, particularly HNO_3 and/or OH-species formed by reactions between H_2O and NO_x . Oxidation of carbon surfaces by HNO_3 generates a significant fraction of acidic surface species that upon heating release significant fractions of CO_2 and H_2O at relatively low temperatures [69, 70]. Computational studies [71] have also suggested that HNO_3 may create OH species on the surface of graphite, and the high reactivity of OH radicals in carbon oxidation has previously been established in several studies [72-75]. Attack on aromatic groups in the soot by nitric acid is also a possible mechanism.

The determined activation energies from the results in figure 1 for soot oxidation by NO_2 (40 kJ/mol) and NO_2+H_2O (25 kJ/mol) are considerably lower than for oxidation by O_2 (198.5 kJ/mol). There are presumably several factors that contribute to the lower activation energy in the presence of NO_2 . Firstly, the presence of the more reactive oxidant is expected to raise the oxygen coverage on the surface of the carbonaceous material, and the activation energies for desorption of CO and CO_2 from oxidized species in the surface of graphite are known to decrease with increasing oxygen coverage [76-80]. Secondly, treatment with NO_2 or HNO_3 creates a significant fraction of di-

oxygenated carbon species in the surface of the carbonaceous material [69, 70, 81, 82], and the activation energy for desorption of CO_2 from a di-oxygenated surface species is significantly lower than the activation energy for CO desorption from mono-oxygenated surface species [83, 84]. Thirdly, the decomposition of formed $[\text{CONO}_2]$ surface complexes to CO_2 and NO occurs at relatively low temperatures [82, 85], which is indicative of a low activation energy of desorption.

Figure 1 also shows that the oxidation by both O_2 and O_2+NO_2 benefits from the presence of a catalyst even though the catalyst is only in loose contact (i.e. stirred together) with the soot. The catalytic oxidation is accelerated considerably by NO_2 whereby the oxidation is shifted $\sim 100^\circ\text{C}$ down in temperature, a level of improvement that is quite general for all the studied catalysts (see supplementary information, figure S1). As discussed in the introduction a primary role of the catalyst in loose contact may well be to activate the oxidant, possibly by dissociative adsorption, to create adsorbed atomic oxygen, which can diffuse to reactive sites on the surface of the carbonaceous material and react. Such a mechanism would also be expected to benefit from the presence of the more reactive oxidant with weaker internal bonds, such as NO_2 . Another potentially beneficial role of a catalyst would be to re-oxidize NO, which has donated oxygen to carbon, back into NO_2 , whereby the NO_2 level in the gas is maximized. The influence from catalytic re-oxidation of NO is, however, expected to be a minor effect in the present experiments, where NO_2 is fed in substantial excess compared to the evolved amounts of CO_x .

3.2 Catalytic oxidation in loose contact with a catalyst

Figure 1 shows that loose contact with a catalyst can influence the oxidation significantly and that the catalytic oxidation is shifted to lower temperature by the presence of NO_2 . Figure 2 shows the

rate of soot oxidation as a function of temperature both without a catalyst and in loose contact with CeO_2 , Cr_2O_3 or Pt as catalysts in a feed containing 10.2 vol% O_2 and 934 ppmv NO_2 . Figure 2 shows that the differences between the various catalysts are modest. However, it is clear that the oxidation benefits from the presence of a catalyst and that Cr_2O_3 is the most active of the catalysts evaluated in figure 2 – especially when considering the surface areas of the catalysts.

Assuming that the role of the catalyst is oxidant activation, and assuming that the number of sites contributing to the oxidant activation scales linearly with the total surface area of these bulk catalysts, it would seem reasonable to normalize the catalytic activity by the total surface area. Figure 3 shows, for various catalytic materials, the fitted rate constants at 550 °C for loose contact soot oxidation by $\text{NO}_2 + \text{O}_2$ and O_2 as a functions of their heats of oxygen chemisorption (a full list of kinetic parameters can be found in the supplementary information). Figure 3 indicates that the rate constants with approximation outline a so-called volcano curve with an optimal activity at intermediate bond strength. When comparing the results in figure 3 for oxidation by O_2 and $\text{O}_2 + \text{NO}_2$ it is first of all clear that a marked increase in oxidation rate is seen for all materials in the presence of NO_2 . The best fit might be suggest that the optimal bond strength is shifted slightly upwards (~ 3 kJ/mol) by the presence of NO_2 , but the number of data points does not allow a fully unambiguous conclusion on this point. Among the tested pure oxides Cr_2O_3 is still the most active material with both O_2 and $\text{O}_2 + \text{NO}_2$. In the case of NH_3 synthesis changes in the gas atmosphere has been observed to shift the volcano curve by 10-20 kJ/mol in bond strength [51, 52]. This is the same order of magnitude as the shift hinted by the soot oxidation data.

All catalysts show a markedly increased reaction rate in the presence of NO_2 and in the catalytic soot oxidation the fraction of the carbon released as CO is generally low compared to non-catalytic soot oxidation (supplementary information, figure S9). It is difficult to establish to which extent this occurs because more of the immediate oxidation product is CO_2 or because CO from the soot

oxidation is subsequently oxidized to CO_2 over the catalyst. It is known that oxygen spillover from the catalyst raises the oxygen coverage on the soot [35], and this is likely to create more di-oxygenated species on the carbonaceous surface that could decompose to CO_2 . So it is not unlikely that in the presence of a catalyst there is more CO_2 in the immediate product of the soot oxidation.

With approximation the determined activation energies for loose contact soot oxidation by NO_2 depend linearly on the heat of oxygen chemisorption (supplementary information figure S10) – a so-called Brønsted-Evans-Polanyi relationship [86, 87], but the tendency appears uncertain for materials binding oxygen more strongly than Fe_2O_3 .

As previously mentioned another potential role of the catalyst in connection with the NO_2 -assisted soot oxidation is to reoxidize NO, which has relinquished oxygen to soot, back into NO_2 . The noble metals are known to be very active for the NO oxidation [44-46]. Additionally, the activity for NO oxidation is expected to benefit from a decreasing oxygen bond strength on the catalyst, as for example Co_3O_4 , which binds oxygen relatively weakly [88, 89], exhibits a significant activity in this reaction [90].

3.3 Effect of gas phase components on loose contact oxidation

Both with and without NO_2 in the gas the optimum of the activity volcano appears to be located between the binding energies of Cr_2O_3 and Fe_2O_3 (figure 3). Guided by a classic interpolation principle [91] we have previously [20] tested a range of silica supported $\text{Fe}_a\text{Cr}_b\text{O}_x$ binary oxides and found that activity passed through an optimum for a FeCr_2O_x catalyst. It is also relevant to test how this optimized catalyst depends on the reaction conditions. Figure 4 shows the rate of soot oxidation in loose contact with $\text{FeCr}_2\text{O}_x/\text{SiO}_2$ as a function of temperature in gas atmospheres containing various combinations of O_2 , NO_2 and H_2O .

Figure 4 shows that it is possible to shift the oxidation to a significantly lower temperature by having an NO_2 containing gas atmosphere and using an $\text{FeCr}_2\text{O}_x/\text{SiO}_2$ catalyst even with only loose soot/catalyst contact. The promotional effect of water on the oxidation by NO_2 , which was observed in non-catalytic oxidation (figure 1), is relatively less pronounced in the presence of a catalyst (figure 4) and is mainly visible by the oxidation finishing at a $\sim 50^\circ\text{C}$ lower temperature in the presence of H_2O . Generally the rate of the catalytic oxidation exhibits the same dependence on the atmosphere as the non-catalytic oxidation.

It is worth emphasizing that a more reactive atmosphere and the use of a catalyst, even in loose contact with the soot, can shift the oxidation temperature towards significantly lower temperatures. Figure 4 shows for example how it with $\text{H}_2\text{O}+\text{NO}_2+\text{O}_2$ and the $\text{FeCr}_2\text{O}_x/\text{SiO}_2$ catalyst is possible to reach the same oxidation rate at $275\text{-}300^\circ\text{C}$ that non-catalytic oxidation by only O_2 does not reach until $\sim 550^\circ\text{C}$. This is even under conditions where effects from the heat of reaction is sought to be minimized by small sample amounts and high flows (ΣCO_x always below 372 ppmv). That such a major downshift in oxidation temperature can be achieved under such conditions, also in loose contact, illustrates the potential improvements that may be achieved by a systematic optimization of catalyst and process conditions.

3.4 Catalytic oxidation in tight contact with a catalyst

In tight contact oxidation tests soot and catalyst are crushed together and an extensive interface between soot and catalyst is formed [10]. In tight contact with an active catalyst the rate is already at low temperatures considerably faster than in any of the oxidation tests shown in figure 1 [20]. As

discussed in the introduction the tight contact oxidation most likely occurs via the Mars van Krevelen mechanism, whereby terminal lattice oxygen from the catalyst is transferred to carbon followed by a re-oxidation of the resulting oxygen vacancy in the catalyst surface by an oxidant from the gas phase. The most active catalysts for this contact type are those that bind their surface oxygen weakly – such as Co_3O_4 and CeO_2 [20].

Figure 5 shows that the gas atmosphere only has a very limited impact on the soot oxidation in tight contact with Co_3O_4 . Addition of 887 ppmv NO_2 and 5.0 vol% H_2O to 10 vol% O_2/N_2 only results in a slightly higher activity at the temperature of maximal oxidation rate (this could be related to a contribution from the non-catalytic oxidation by NO_2), but the differences are modest, and the temperature range wherein the oxidation occurs is almost completely identical in the presence or absence of $\text{NO}_2+\text{H}_2\text{O}$. For a Mars van Krevelen mechanism, where reaction between carbon and lattice oxygen rather than catalyst re-oxidation is rate limiting, the presence of a more reactive oxidant in the gas will not necessarily increase the reaction rate, since the re-oxidation of the catalyst is only a minor limitation on the rate. Theoretical studies [92] for $\text{Co}_3\text{O}_4(110)$ indicate that oxygen vacancy re-occupation by O_2 is barrierless, so it seems very likely that the oxide re-oxidation is facile even on weakly binding Co_3O_4 . The limited effect of a more reactive atmosphere observed in the tight contact with Co_3O_4 can thus be rationalized in terms of the expected reaction mechanism. Consequently there is in tight contact oxidation not necessarily a significant gain from the presence of a more reactive gas atmosphere, unless the studied catalyst is significantly limited by the oxygen activation during the re-oxidation of the catalyst. If the conditions become more oxygen deficient the re-oxidation will of course eventually become rate limiting, and a dependence on the oxidant concentration will emerge. There may also be some catalytic materials (particularly weakly-binding surfaces such as gold [20, 63]) that will benefit from a more reactive oxidant raising

the oxygen coverage on the catalyst. However, the highly active Co_3O_4 catalyst investigated here appears to have reached the 0. order regime, where the rate is independent of oxidant concentration.

Conclusion

The rate of non-catalytic soot oxidation in a 10 vol% O_2 in N_2 atmosphere is significantly increased by addition of 934 ppmv NO_2 to the gas. The weaker O-NO bond in NO_2 than the O-O bond in O_2 and the radical nature of NO_2 are possible reasons for the higher reactivity. At lower temperatures the NO_2 -assisted oxidation rate is further increased by the addition of water to the gas, and 5 vol% H_2O causes a doubling of the NO_2 -assisted rate at 300 °C. The beneficial effect of water may be related to the involvement of protonated species such as HNO_3 . HNO_3 generates acidic surface sites on the carbonaceous material that can decompose to CO_2 at relatively low temperatures. The beneficial effect of water requires the presence of NO_2 , as the addition of 5 vol% water to an O_2/N_2 gas mixture does not affect the rate significantly. The oxidation temperature can be lowered further by the use of a catalyst. If the soot is in loose contact with a catalyst (with the materials stirred together) the impact of the gas composition is similar to the non-catalytic case, namely with a significant acceleration of the oxidation rate by NO_2 (oxidation temperature lowered ~100 °C by 934 ppmv NO_2) and possibly a smaller additional enhancement by H_2O . For a number of catalytic materials the rate constants for loose contact soot oxidation by NO_2 outline a volcano curve as a function of their heats of oxygen chemisorption (as a measure of the oxygen bond strength on the catalyst). The location of the optimum of the volcano curve is very close to the position of the optimum for oxidation by O_2 , and among the investigated pure oxides and metals Cr_2O_3 was nearest to the optimal bond strength. If the soot is in tight contact with a catalyst (soot and catalyst crushed together) the catalytic oxidation is considerably faster than the non-catalytic oxidation (with or

without NO₂), and with Co₃O₄, which is a good tight contact catalyst, the reaction rate does not benefit significantly from the addition of NO₂+H₂O to the O₂/N₂ atmosphere. This agrees with the mechanism of tight contact oxidation being of the Mars-van Krevelen type, and where the transfer of lattice oxygen to the soot is rate limiting

Appendix A. Supplementary material

Evaluation of activity in terms of T_{max}-values. Kinetic parameters and examples of fits to data.

Analysis of the effect of NO₂ on the CO/CO₂ distribution in effluent gas. Brønsted-Evans-Polanyi relationship for soot oxidation by NO₂.

Acknowledgements

Financial support from The Danish Council for Strategic Research (Grant No. 2106-08-0039) and from the Innovation Fund Denmark (Grant No. 103-2012-3) is gratefully acknowledged.

References

- [1] C. Ris, *Inhal. Toxicol.* 19 (2007) 229-239.
- [2] B. Frank, M. Schuster, R. Schlögl, D.S. Su, *Angew. Chem. Int. Ed.* 52 (2013) 2673-2677.
- [3] D.B. Kittelson, *J. Aerosol Sci.* 29 (1998) 575-588.
- [4] B.A.A.L. Van Setten, M. Makkee, J.A. Moulijn, *Catal. Rev. Sci. Eng.* 43 (2001) 489-564.
- [5] J. Neeft, M. Makkee, J.A. Moulijn, *Fuel. Process. Technol.* 47 (1996) 1-69.
- [6] J. Adler, *Int. J. Appl. Ceram. Technol.* 2 (2005) 429-439.
- [7] A.M. Stamatelos, *Energy Convs. Mgmt.* 38 (1997) 83-99.
- [8] J. Neeft, M. Makkee, J.A. Moulijn, *Chem. Eng. J.* 64 (1996) 295-302.

- [9] J. Neeft, M. Makkee, J.A. Moulijn, *Appl. Catal. B* 8 (1996) 57-78.
- [10] D. Gardini, J.M. Christensen, C.D. Damsgaard, A.D. Jensen, J.B. Wagner, *Appl. Catal. B* 183 (2016) 28-36.
- [11] A.G. Konstandopoulos, S. Lorentzou, C. Pagkoura, K. Ohno, K. Ogyu, T. Oya, SAE paper 2007-01-1950, 2007.
- [12] A.G. Konstandopoulos, E. Papaioannou, *Kona* 26 (2008) 36-65.
- [13] A. Konstandopolous, E. Papaioannou, D. Zarvalis, S. Skopa, P. Baltzopoulou, E. Kladopoulou, M. Kostoglou, S. Lorentzou, SAE paper 2005-01-0670, 2005.
- [14] P.A. Kumar, M.D. Tanwar, S. Bensaid, N. Russo, D. Fino, *Chem. Eng. J.* 207-208 (2012) 258-266.
- [15] B.W.L. Southward, S. Basso, SAE paper 2008-01-0481, 2008.
- [16] V. Di Sarli, G. Landi, L. Lisi, A. Saliva, A. Di Benedetto, *Appl. Catal. B* 197 (2016) 116-124.
- [17] V.R. Pérez, A. Bueno-López, *Chem. Eng. J.* 279 (2015) 79-85.
- [18] Q. Liang, X. Wu, X. Wu, D. Weng, *Catal. Lett.* 119 (2007) 265-270.
- [19] J.M. Christensen, D. Deiana, J.-D. Grunwaldt, A.D. Jensen, *Catal. Lett* 144 (2014) 1661-1666.
- [20] J.M. Christensen, J.-D. Grunwaldt, A.D. Jensen, *Appl. Catal. B* 188 (2016) 235-244.
- [21] E. Aneggi, N.J. Divins, C. de Leitenburg, J. Llorca, A. Trovarelli, *J. Catal.* 312 (2014) 191-194.
- [22] S. Simonsen, S. Dahl, E. Johnson, S. Helveg, *J. Catal.* 255 (2008) 1-5.
- [23] M. Machida, Y. Murata, K. Kishikawa, D. Zhang, K. Ikeue, *Chem. Mater.* 20 (2008) 4489-4494.
- [24] A. Bueno-Lopez, K. Krishna, M. Makkee, J. Moulijn, *J. Catal.* 230 (2005) 237-248.
- [25] A. Bueno-López, K. Krishna, M. Makkee, J.A. Moulijn, *Catal. Lett.* 99 (2005) 203-205.
- [26] G. Mul, F. Kapteijn, C. Doornkamp, J.A. Moulijn, *J. Catal.* 179 (1998) 258-266.

- [27] K. Harada, T. Oishi, S. Hamamoto, T. Ishihara, J. Phys. Chem. C 118 (2013) 559-568.
- [28] S. Wagloehner, J.N. Baer, S. Kureti, Appl. Catal. B 147 (2014) 1000-1008.
- [29] L. Soler, A. Casanovas, C. Escudero, V. Pérez-Dieste, E. Aneggi, A. Trovarelli, J. Llorca, ChemCatChem 8 (2016) 2748-2751.
- [30] P. Mars, D.W. Van Krevelen, Chem. Eng. Sci. Special Suppl. 3 (1954) 41-59.
- [31] K. Suzuki, K. Harada, H. Yamada, K. Okamoto, A. Takami, SAE paper 2007-01-1919, 2007.
- [32] K. Yamazaki, Y. Sakakibara, F. Dong, H. Shinjoh, Appl. Catal. A 476 (2014) 113-120.
- [33] D. Reichert, H. Bockhorn, S. Kureti, Appl. Catal. B 80 (2008) 248-259.
- [34] S. Wagloehner, M. Nitzer-Noski, S. Kureti, Chem. Eng. J. 259 (2015) 492-504.
- [35] G. Mul, J.P.A. Neeft, F. Kapteijn, J.A. Moulijn, Carbon 36 (1998) 1269-1276.
- [36] L. Zeng, T. Turek, A.P. Weber, Chem. Ing. Tech. 83 (2011) 1276-1281.
- [37] L. Zeng, A.P. Weber, Chem. Ing. Tech. 84 (2012) 295-300.
- [38] R.T.K. Baker, J.J. Chludzinski, Carbon 19 (1981) 75-82.
- [39] D.W. McKee, Carbon 8 (1970) 623-635.
- [40] H.D. Allendorf, D.E. Rosner, AIAA J. 6 (1968) 650-654.
- [41] J. Oi Uchisawa, A. Obuchi, Z. Zhao, S. Kushiyama, Appl. Catal. B 18 (1998) L183-L187.
- [42] J. Oi-Uchisawa, A. Obuchi, A. Ogata, R. Enomoto, S. Kushiyama, Appl. Catal. B 21 (1999) 9-17.
- [43] S. Liu, A. Obuchi, J. Uchisawa, T. Nanba, S. Kushiyama, Appl. Catal. B 37 (2002) 309-319.
- [44] B.J. Cooper, H.J. Jung and J.E. Thoss, Eur. Patent 0 341 832 (1996), to Johnson Matthey Inc.
- [45] W. Wang, G. McCool, N. Kapur, G. Yuan, B. Shan, M. Nguyen, U.M. Graham, B.H. Davis, G. Jacobs, K. Cho, X. Hao, Science 337 (2012) 832-835.
- [46] B.J. Cooper, J.E. Thoss, SAE Paper 890404, 1989.
- [47] J.-O. Müller, B. Frank, R.E. Jentoft, R. Schlögl, D.S. Su, Catal. Today 191 (2012) 106-111.

- [48] K.-Y. Choi, N.W. Cant, D.L. Trimm, *J. Chem. Technol. Biotechnol.* 71 (1998) 57-60.
- [49] J.R. Arthur, H.F. Ferguson, K. Lauber, *Nature* 178 (1956) 206-207.
- [50] X. Chu, L.D. Schmidt, *Ind Eng Chem Res* 32 (1993) 1359-1366.
- [51] J.K. Nørskov, T. Bligaard, J. Rossmeisl, C.H. Christensen, *Nature Chem.* 1 (2009) 37-46.
- [52] C.J.H. Jacobsen, S. Dahl, A. Boisen, B.S. Clausen, H. Topsøe, A. Logadottir, J.K. Nørskov, *J. Catal.* 205 (2002) 382-387.
- [53] V. Di Sarli, A. Di Benedetto, *Chem. Eng. Sci.* 137 (2015) 69-78.
- [54] V. Di Sarli, A. Di Benedetto, *Ind. Eng. Chem. Res.* 55 (2016) 11052–11061.
- [55] J. Im, C.M. Lee, J.T. Coates, *Chemosphere* 71 (2008) 621-628.
- [56] A. Braun, B.S. Mun, F.E. Huggins, G.P. Huffman, *Environ. Sci. Technol.* 41 (2007) 173-178.
- [57] Ö. Gustafsson, T.D. Bucheli, Z. Kukulska, M. Andersson, C. Largeau, J.-N. Rouzaud, C.M. Reddy, T.I. Eglinton, *Global Biogeochem. Cycles* 15 (2001) 881-890.
- [58] O. Levenspiel, *The chemical reactor omnibook*, OSU Book Stores, Corvallis, Oregon, 1996.
- [59] C.J. Tighe, M.V. Twigg, A.N. Hayhurst, J.S. Dennis, *Combust. Flame* 159 (2012) 77-90.
- [60] D.R. Lide (Ed.), *Handbook of Chemistry and Physics*, 78th ed., CRC Press, USA, 1997.
- [61] C. Decarne, E. Abi-Aad, A. Aboukaïs, *Catal. Lett.* 62 (1999) 45-48.
- [62] D. Dahlgren, J.C. Hemminger, *Surf. Sci. Lett.* 123 (1982) L739-L742.
- [63] X. Deng, B.K. Min, A. Guloy, C.M. Friend, *J. Am. Chem. Soc.* 127 (2005) 9267-9270.
- [64] F. Jacquot, V. Logie, J.F. Brilhac, P. Gilot, *Carbon* 40 (2002) 335-343.
- [65] M. Jeguirim, V. Tschamber, J.F. Brilhac, P. Ehrburger, *Fuel* 84 (2005) 1949-1956.
- [66] K. Tikhomirov, O. Kröcher, M. Elsener, A. Wokaun, *Appl. Catal. B* 64 (2006) 72-78.
- [67] D.H. Cotton, N.J. Friswell, D.R. Jenkins, *Combust. Flame* 17 (1971) 87-98.
- [68] P. Glarborg, *Proc. Comb. Inst.* 31 (2007) 77-98.
- [69] S.R. Kelemen, H. Freund, *Energy Fuels* 2 (1988) 111-118.

- [70] Y. Otake, R.G. Jenkins, Carbon 31 (1993) 109-121.
- [71] A. Rodríguez-Forteza, M. Iannuzzi, M. Parrinello, J. Phys. Chem. B 110 (2006) 3477-3484.
- [72] C.P. Fenimore, G.W. Jones, J. Phys. Chem. 71 (1967) 593-597.
- [73] R.C. Millikan, J. Phys. Chem. 66 (1962) 794-799.
- [74] B.S. Haynes, H.G. Wagner, Prog. Energy Combust. Sci. 7 (1981) 229-273.
- [75] M.F.R. Mulcahy, B.C. Young, Carbon 13 (1975) 115-124.
- [76] S.S. Barton, B.H. Harrison, J. Dollimore, J. Chem. Soc. , Faraday Trans. 1 69 (1973) 1039-1048.
- [77] S.S. Barton, B.H. Harrison, J. Dollimore, J. Phys. Chem. 82 (1978) 290-294.
- [78] S.R. Kelemen, H. Freund, Carbon 23 (1985) 619-625.
- [79] Z.H. Zhu, J. Finnerty, G.Q. Lu, R.T. Yang, Energy Fuels 16 (2002) 1359-1368.
- [80] P.L. Walker, R.L. Taylor, J.M. Ranish, Carbon 29 (1991) 411-421.
- [81] A. Setiabudi, M. Makkee, J.A. Moulijn, Appl. Catal. B 50 (2004) 185-194.
- [82] B. Azambre, S. Collura, J.M. Trichard, J.V. Weber, Appl. Surf. Sci. 253 (2006) 2296-2303.
- [83] B. Marchon, J. Carrazza, H. Heinemann, G.A. Somorjai, Carbon 26 (1988) 507-514.
- [84] B. Marchon, W.T. Tysoe, J. Carrazza, H. Heinemann, G.A. Somorjai, J. Phys. Chem. 92 (1988) 5744-5749.
- [85] H. Muckenhuber, H. Grothe, Carbon 44 (2006) 546-559.
- [86] M.G. Evans, M. Polanyi, Trans. Faraday Soc. 34 (1938) 11-24.
- [87] J.N. Brønsted, K. Pedersen, Z. Phys. Chem. 108 (1924) 185-235.
- [88] G.K. Boreskov, V.V. Popovsky, V.A. Sazonov, Fourth Int. Cong. Catal. - Reprints of Papers 2 (1968) 580-603.

- [89] V.A. Razdobarov, V.A. Sadykov, S.A. Veniaminov, N.N. Bulgakov, O.N. Kovalenko, Y.D. Pankratiev, V.V. Popovskii, G.N. Kryukova, S.F. Tikhov, *React. Kinet. Catal. Lett.* 37 (1988) 109-114.
- [90] B.M. Weiss, N. Artioli, E. Iglesia, *ChemCatChem* 4 (2012) 1397-1404.
- [91] A.A. Balandin, *Adv. Catal.* 19 (1969) 1-210.
- [92] D. Jiang, S. Dai, *Phys. Chem. Chem. Phys* 13 (2011) 978-984.

Figure 1 The rate of soot oxidation (normalized by the total, initial amount of carbon) as a function of the temperature in various gas atmospheres and with and without the presence of a Cr_2O_3 catalyst (in loose contact). Experimental conditions: Soot:Catalyst = 1:5 wt:wt, ramp = 11 °C/min, 1 NL/min. Feed compositions: 10.2 vol% O_2 in N_2 ; 9.7 vol% O_2 and 5.0 vol% H_2O in N_2 ; 10.2 vol% O_2 and 934 ppmv NO_2 in N_2 ; 9.7 vol% O_2 , 887 ppmv NO_2 and 5.0 vol% H_2O in N_2 .

Figure 2 The rate of soot oxidation (normalized by the total, initial mass of carbon) as a function of temperature in loose contact with Pt (32 m^2/g), CeO_2 (182 m^2/g) or Cr_2O_3 (17 m^2/g). Experimental conditions: Soot:Catalyst = 1:5 wt:wt, ramp = 11 °C/min, 1 NL/min, 934 ppmv NO_2 and 10.2 vol% O_2 in N_2 .

Figure 3 The rate constant at 550 °C for soot oxidation in loose contact with a catalyst in an O_2+NO_2 ($k_{\text{O}_2}+k_{\text{NO}_2}$, filled points) or O_2 (k_{O_2} , open points) atmosphere as function of the heat of oxygen chemisorption for various catalytic materials. The rate constant is normalized by the surface area of the catalyst. Dashed lines given as a guide to the eye. The experimental conditions are given in connection with figure 2. The heats of oxygen chemisorption are taken from ref. [20].

Figure 4 The rate of soot oxidation (normalized by the total, initial amount of carbon) in loose contact with a $\text{FeCr}_2\text{O}_x/\text{SiO}_2$ catalyst a function of the temperature in various gas atmospheres. Experimental conditions: Soot:Catalyst = 1:10 wt:wt, ramp = 11 °C/min, 1 NL/min. Feed compositions: 10.2 vol% O_2 in N_2 ; 9.7 vol% O_2 and 5.0 vol% H_2O in N_2 ; 10.2 vol% O_2 and 934 ppmv NO_2 in N_2 ; 9.7 vol% O_2 , 887 ppmv NO_2 and 5.0 vol% H_2O in N_2 .

Figure 5 The rate of soot oxidation (normalized by the total, initial mass of carbon) as a function of temperature in tight contact with the Co_3O_4 catalyst ($131 \text{ m}^2/\text{g}$) in either 10.2 vol% O_2 in N_2 or 9.7 vol% O_2 , 887 ppmv NO_2 and 5.0 vol% H_2O in N_2 . Experimental conditions: Soot:Catalyst = 1:5 wt:wt, ramp = $11 \text{ }^\circ\text{C}/\text{min}$, $1 \text{ NL}/\text{min}$.

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5

Loose soot/catalyst contact: Strong effect of more reactive gas atmosphere

Main rate limitation: Oxidant activation $\Rightarrow$ strong benefit from NO_2

Tight soot/catalyst contact: limited effect of more reactive gas atmosphere

Main rate limitation: Reaction of C with lattice oxygen $\Rightarrow$ little benefit from NO_2

Highlights

- Oxidation of soot in loose contact with a catalyst is significantly enhanced by NO_2
- Loose contact oxidation by NO_2 has a volcano-type dependence on bond strength of oxygen on the surface
- Addition of NO_2 and loose contact with FeCr_2O_x shifts oxidation down by $\geq 200^\circ\text{C}$
- For soot in tight contact with a Co_3O_4 catalyst hardly any effect of NO_2
- Limited effect on oxidation in tight contact consistent with Mars van Krevelen mechanism