



## Comparison of Pulsed Electron Deposition and Pulsed Laser Deposition of selected materials

Ettlinger, Rebecca Bolt; Pattini, Francesco; Rampino, Stefano; Cazzaniga, Andrea Carlo; Crovetto, Andrea; Bosco, Edoardo; Gilioli, Edmondo ; Hansen, Ole; Schou, Jørgen

*Publication date:*  
2016

*Document Version*  
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

*Citation (APA):*  
Ettlinger, R. B., Pattini, F., Rampino, S., Cazzaniga, A. C., Crovetto, A., Bosco, E., Gilioli, E., Hansen, O., & Schou, J. (2016). *Comparison of Pulsed Electron Deposition and Pulsed Laser Deposition of selected materials*. Abstract from EMRS Spring Meeting 2016, Lille, France.

---

### General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

## **Comparison of Pulsed Electron Deposition and Pulsed Laser Deposition of selected materials**

Rebecca B. Ettliger<sup>(1)</sup>, Francesco Pattini<sup>(2)</sup>, Stefano Rampino<sup>(2)</sup>, Andrea Cazzaniga<sup>(1)</sup>, Andrea Crovetto<sup>(3)</sup>, Edoardo Bosco<sup>(3)</sup>, Edmondo Gilioli<sup>(2)</sup>, Ole Hansen<sup>(3)</sup> and Jørgen Schou<sup>(1)</sup>

<sup>(1)</sup> DTU Fotonik, Technical University of Denmark, Roskilde, Denmark

<sup>(2)</sup> IMEM-CNR, Parma, Italy

<sup>(3)</sup> DTU Nanotech, Technical University of Denmark, Kgs. Lyngby, Denmark

Pulsed Electron Deposition (PED) is a method of creating thin films through ablation at low pressure that has many similarities to Pulsed Laser Deposition (PLD). Key advantages of PED include lower equipment cost and higher energy efficiency. We have investigated the use of PED as an alternative to PLD for production of the new solar cell material copper zinc tin sulfide (CZTS). Measurements of the electron energy distribution of the PED pulses at different discharge voltages are compared to the composition of the resulting films and to the influence of laser fluence on film composition with PLD. There is a similar deviation from the target stoichiometry depending on fluence/electron energy with the two techniques. Additionally, droplets occur with both techniques with a strong reduction in droplet density at low energy/low fluence. Finally the desired lattice structure of crystalline CZTS is obtained at a relatively low temperature around 300 °C with both techniques and the deposition rate for PED is at least as fast as PLD with a 248 nm excimer laser or a 355 nm Nd:YAG laser. The beam-target interaction of PED versus PLD is discussed and our results for CZTS are compared with PED and PLD production of ZnS and CIGS. Overall, we find that PED is able to produce films in a similar manner to PLD with both techniques requiring some fine tuning of the deposition parameters for good-quality films.