High Q gallium nitride microring resonators

Stassen, Erik; Pu, Minhao; Semenova, Elizaveta; Zavarin, E.; Lundin, W.; Yvind, Kresten

Published in:

2017 Conference on Lasers and Electro-Optics Europe & European Quantum Electronics Conference (CLEO/Europe-EQEC)

Link to article, DOI:

[10.1109/CLEOE-EQEC.2017.8086619](https://doi.org/10.1109/CLEOE-EQEC.2017.8086619)

Publication date:

2017

Document Version

Peer reviewed version

[Link back to DTU Orbit](#)

Citation (APA):

Stassen, E., Pu, M., Semenova, E., Zavarin, E., Lundin, W., & Yvind, K. (2017). High Q gallium nitride microring resonators. In *2017 Conference on Lasers and Electro-Optics Europe & European Quantum Electronics Conference (CLEO/Europe-EQEC)* IEEE. <https://doi.org/10.1109/CLEOE-EQEC.2017.8086619>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

High Q Gallium Nitride Microring Resonators

E. Stassen¹, M. Pu¹, E. Semenova¹, E. Zavarin², W. Lundin², and K. Yvind¹

1. DTU Fotonik, Technical University of Denmark, Ørstedes Plads 345A, 2800 Kgs. Lyngby, Denmark

2. Ioffe Institute, Politekhnicheskaya str. 26, 194021 St. Petersburg, Russia;

Gallium nitride (GaN) is a promising material for nonlinear microresonators. It has large intrinsic $\chi^{(2)}$ and $\chi^{(3)}$, excellent thermal properties and a relatively large bandgap [1] and can be used for example for parametric conversion and frequency doubling [2]. Furthermore it is quite resilient and can withstand high temperatures and power. In this paper, we demonstrate GaN microring resonators with a quality factor (Q) larger than 10^5 , which, to the best of our knowledge, is the highest demonstrated Q for microring resonators in a pure GaN platform [3].

GaN was grown on sapphire in Dragon-125 MOVPE system using low-temperature GaN nucleation layer annealed under H_2 -free ambient for promoting planar growth of thin layer. A PECVD SiO_2 layer was then deposited on top of the wafer for protection before cleaving it into small pieces with a laser micromachining tool. E-beam lithography in HSQ resist and Cl_2 ICP RIE was used to create the device. A SEM image of the coupling region (before cladding) between bus waveguide and resonator is shown in Fig. 1(a). Finally the devices were cladded with PECVD SiO_2 and cleaved with a laser micromachining tool in a region where the waveguides are tapered out to match the mode profile of a lensed optical fiber used for characterization. A resonator with an FSR of 1 THz having a radius of $19.33 \mu m$ and a racetrack resonator with an FSR of 100 GHz with a bending radius of $19.33 \mu m$ and a circumference of $1239 \mu m$ were fabricated and characterized. The waveguide for resonators has a width of $1.25 \mu m$ and a height of 700 nm. The resonators were characterized in the 1550 nm band by measuring the transmission of the bus waveguide. All resonators were under-coupled, and the intrinsic Q was calculated from the loaded Q as $Q_{int}=2Q_{load}/(1+\sqrt{T_0})$ [4] with T_0 being the relative transmission at the resonance. The 1 THz resonator exhibited a maximum intrinsic Q of 119,000 and the 100 GHz an intrinsic Q of 137,000 (an example of a Lorentzian fit for a 1 THz resonator shown in Fig. 1(b)).

Fig. 1(a) SEM picture of the coupling region of a GaN microring resonator after etching process. The E-beam resist HSQ is kept on the device. Inset: zoom in on particle near sidewall. (b) Lorentzian fit to a resonance of a 1 THz resonator.

The characterization was carried out using a scanning laser system with a resolution of 3 pm. The performance of the resonators may be affected by randomly distributed particles (probably originating from incomplete removal of the SiO_2 protection layer) which are highlighted in the inset of Fig. 1(a). In conclusion, we demonstrate the highest Q for microring resonators fabricated in a pure GaN platform, which is promising in nonlinear applications.

Acknowledgements

The authors acknowledge financial support from the Danish Research Council via the SPOC (DNRF123) center of excellence.

References

- [1] S. Pezzagna, J. Brault, M. de Micheli, P. Vennéguès, A.D. Wieck, J. Massies "GaN, a new material for integrated nonlinear optics," Proc. of ECIO 2007, **25**(2007).
- [2] C. Xiong, W. Pernice, K. Ryu, C. Schuck, K. Fong, T. Palacios and H. Tang, "Integrated GaN photonic circuits on silicon (100) for second harmonic generation" Optics Express.**19**, 10462 (2011).
- [3] A. Bruch, C. Xiong, B. Leung, M. Poot, J. Han and H. Tang, "Broadband nanophotonic waveguides and resonators based on epitaxial GaN thin films" Appl. Phys. Lett..**107**, 141113 (2015).
- [4] L. Ottaviano, M. Pu, E. Semenova and K. Yvind, "Low-loss high-confinement waveguides and microring resonators in AlGaAs-on-insulator" Optics Letters.**41**, 3996 (2016).