



Foam based on fish skin collagen by-product: a colloidal approach

Casanova, Federico; Mohammadifar, Mohammad Amin; Kobbelgaard, Sara; Jakobsen, Greta; Jessen, Flemming

Publication date:
2019

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Casanova, F., Mohammadifar, M. A., Kobbelgaard, S., Jakobsen, G., & Jessen, F. (2019). *Foam based on fish skin collagen by-product: a colloidal approach*. Poster session presented at Seminar on ingredients from new biomasses, Kgs. Lyngby, Denmark.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.


Foam based on fish skin collagen by-product: a colloidal approach

Federico Casanova ^{a*}, Mohammad Amin Mohammadifar ^a, Sara Kobbelgaard ^b, Greta Jakobsen ^c and Flemming Jessen ^{a*}

^a Food Production Engineering, DTU Food, Technical University of Denmark, Søtofts Plads 227, Dk-2800 Lyngby, Denmark.

^b Technological Institute, Kongsvang Alle 29, DK-8000 Aarhus C.

^c Danish Fish Protein, Adelvej 11, Hoejmark, DK-6940 Lem St.




Level 1 – foam scale: liquid fraction, stability, rheology, viscoelastic behavior, yielding behavior, steady-flow behavior
 Level 2 – bubble scale: mean bubble size, distribution of bubbles sizes, bubble rearrangement dynamics ⁽¹⁾
 Level 3 – lamella scale: thickness, uniformity, permeability, stability ⁽²⁾
 Level 4 – interfacial scale: dynamic and equilibrium conditions of protein absorption, interfacial tension reduction, rheological properties ⁽³⁾

Recent changing in consumption trends, due to ecological problems, animal welfare, allergies, sanitary and religious restrictions, have led to making a concerted effort to find alternative protein sources that can provide similar functionalities in food systems. The large quantities of by-products generated by the fish-processing industry are a potential source for the production of gelatin.

Research question : Can gelatin by-products be employed as alternative sources of protein ?

We compared the *Foamability* (F), the *Foam capacity* (F_c) and the *Foam stability* (F_s) of 2 commercial fish collagen samples (A and B) and 3 fish skin by-products collagen (C, D and E).



V_0 is the volume of the foam after formation, V_l is the volume of the liquid and V_{time} is the volume of the foam as a function of the time.

Partial conclusions: No significant difference was observed in terms of F between the samples. Better F_c (+ 25 %) was observed for the sample E. Fish skin by-products collagen present greater F_s compared to commercial sample: sample C, D and E present 48 ± 2 % of F_s after 30 min whereas A and B present only 4.4 % and 0 %.

Future directions: In order to deeper investigate and better understand these differences, other analytical approaches are planned: dynamic interfacial tension, ellipsometry, film pressure balance as well as small angle X-ray scattering (SAXS).

⁽¹⁾ Wiebke Drenckhan, Stefan Hutzler (2015). Structure and energy of liquid foams, Advances in Colloid and Interface Science, 224 (2015) 1–16.
⁽²⁾ Brakke K. (1992). The Surface Evolver Exp Math 1(2):141–65.
⁽³⁾ Fameau, A. L., Salonen A. (2014). Effect of particles and aggregated structures on the foam stability and aging. Comptes Rendus Physique, 15, 748-760.