Hydration States and Blood Compatibility of Hydrogen-Bonded Supramolecular Poly(2-methoxyethyl acrylate)

Jankova, Katja; Javakhishvili, Irakli; Kobayashi, Shingo; Koguchi, Ryohei; Murakami, Daiki; Sonoda, Toshiki; Tanaka, Masaru

Published in:
ACS Applied Bio Materials

Link to article, DOI:
[10.1021/acsabm.9b00363](https://doi.org/10.1021/acsabm.9b00363)

Publication date:
2019

Document Version
Peer reviewed version

[Link back to DTU Orbit](#)

Citation (APA):

Jankova, K., Javakhishvili, I., Kobayashi, S., Koguchi, R., Murakami, D., Sonoda, T., & Tanaka, M. (2019). Hydration States and Blood Compatibility of Hydrogen-Bonded Supramolecular Poly(2-methoxyethyl acrylate). *ACS Applied Bio Materials*, 2(10), 4154-4161. <https://doi.org/10.1021/acsabm.9b00363>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

1
2
3
4
5
6
7 Hydration states and blood compatibility of
8
9
10
11 Hydrogen-bonded supramolecular poly(2-
12
13
14
15 methoxyethyl acrylate)
16
17
18
19

20 *Katja Jankova,^{1,2} Irakli Javakhishvili,³ Shingo Kobayashi,¹ Ryohei Koguchi,^{1,4} Daiki*
21
22
23
24 *Murakami,¹ Toshiki Sonoda,¹ and Masaru Tanaka^{1*}*
25
26
27

28
29 ¹ Soft Materials Chemistry, Institute for Materials Chemistry and Engineering, Kyushu
30
31
32 University, Build. CE41, 744 Motooka Nishi-ku, Fukuoka, 819-0395, Japan
33
34
35

36
37 ² Department of Energy Conversion and Storage, Technical University of Denmark,
38
39
40 Elektrovej, Build. 375, 2800 Kongens Lyngby, Denmark
41
42
43

44
45 ³ Danish Polymer Centre, Department of Chemical and Biochemical Engineering,
46
47
48 Technical University of Denmark, Build. 229, 2800 Kongens Lyngby, Denmark
49
50
51

⁴ AGC Inc. New Product R&D Center, 1150 Hazawa-cho, Kanagawa-ku, Yokohama,
Kanagawa 221-8755, Japan

KEYWORDS: blood compatible polymer, hydrogen bonding, poly(2-methoxyethyl
acrylate), free-standing film, intermediate water, 2-{3-(6-methyl-4-oxo-1,4-
dihydropyrimidin-2-yl)ureido}ethyl methacrylate.

ABSTRACT: The practical use of the viscous liquid polymer, poly(2-methoxyethyl
acrylate) (PMEA) was expanded from thin films with excellent blood compatibility to
thick coatings and free-standing films without essentially sacrificing its blood
compatibility. This was undertaken by creating multiple hydrogen-bonding polymer
networks by introducing a functional methacrylic monomer bearing a 6-methyl-2-ureido-
4[1H]-pyrimidone group in the PMEA backbone via free radical copolymerization. The
hydrogen-bonded PMEA (H-PMEA) contained about 6 mol% of the functional monomer
in the copolymer. These functional monomers as physical cross-links are distributed in
the PMEA matrix with a T_g of $-35\text{ }^{\circ}\text{C}$, making H-PMEA solid rubber-like material with

recoverable tensile strain. Additionally, mechanical tests revealed its tensile strength, and thermogravimetric analyses confirmed its higher thermostability. The dry and hydration states of H-PMEA were assessed by differential scanning calorimetry, contact angle, and atomic force microscopy measurements. Comparison with viscous PMEA was made. For the first time, we included PVC alongside with PET, the surface we usually use as a negative control, in the platelet adhesion test with human blood, and found out that 1.5 times more platelets adhered onto the PVC surface than onto the PET surface, while H-PMEA proved to have a clear edge. Thus, H-PMEA may serve as a suitable replacement of polymers in products contacting blood as it shows potential for making free-standing films, thick coatings, implants and articles with various geometries for the medicinal industry.

Introduction

Compatibility with human blood is an important characteristic of materials used in medical devices. Poly(2-methoxyethyl acrylate) (PMEA) is an acrylic homopolymer having an ethylene oxide unit in the side chain. It has low toxicity and is FDA approved for medical use. This polymer boasts the largest share on coating market, is easy to synthesize and inexpensive, possesses excellent blood compatibility, low protein adsorption and denaturation.¹⁻³ Intermediately hydrophilic, with the water contact angle of approximately 40 degrees, it is not soluble in water above the molecular weight (MW) of 4-5 kDa, but it is soluble in methanol as well as many other organic solvents. Being a viscous liquid has not obstructed PMEAs extensive use, especially in the Japanese industry, to coat various organic and inorganic surfaces to which the polymer adheres well. These properties made it very useful to coat with a thin film of liquid PMEA various stents, an artificial oxygenator,⁴ a bioartificial liver, heart,⁵ cell enrichment filter, etc., and thus to protect blood from contacting the substrate material. However, only thin films were possible to be produced from PMEA so far. When the thickness of the film is below 50 microns the films are not sticky. Usually, for coating purposes, PMEA with the number average MW of around 23,000 Da (18-25 kDa) has been used.¹⁻³ The effect of

the MW of PMEA on the interfacial structure and the blood compatibility was investigated very recently.⁶ PMEAs with higher MWs were found to have a very little (30 and 44 kDa) or even more (183 kDa) reduced blood compatibility as compared to PMEA with 19 kDa. These PMEAs with higher MW were also viscous and sticky. Recently, charged PMEA microspheres were synthesized⁷ by aqueous precipitation polymerization with potassium peroxydisulfate, and were also turned into small free-standing films with thicknesses up to 1.2 mm.

Liquid polymers can be transformed into higher viscosity products by using either chemical or physical cross-linking. The chemical crosslinks are introduced by curing where covalent bonds are formed. However, besides using an additional step of curing, the material cannot be processed afterwards. Non-covalent interactions are often the means of property improvement in polymer science. By introducing hydrogen bonding, metal complexation, ionic or hydrophobic interactions, etc. the supramolecular polymer, which can be recycled, is obtained.⁸⁻⁹ Hydrogen bonding is not the strongest among the non-covalent interactions, but has been employed to confer many new functionalities like stimuli-responsiveness¹⁰ and self-healing properties to polymeric materials.¹¹⁻¹⁴

1
2
3
4 Acid-base interactions are often utilized in polymer electrolyte membranes for fuel cells
5
6
7 to increase the strength and conductivity of the ionic polymers.¹⁵⁻¹⁷ We have previously
8
9
10 exploited a strategy involving hydrophobic interactions both in aq. solutions¹⁸⁻¹⁹ and in
11
12
13 bulk.²⁰ Triblock copolymers with small amounts of outer blocks were designed, which
14
15
16 could associate in bulk to build a morphology very similar to that of the thermoplastic
17
18
19 elastomers, where hard segments act as physical cross-links distributed in a matrix of a
20
21
22 low T_g polyether polymer – this way Li ion conducting solid polymer electrolytes
23
24
25 comprising PEG or PEG/PEGPG soft segments together with polyethylene or
26
27
28 polypentafluorostyrene hard segments could be produced.²⁰⁻²¹
29
30
31

32
33
34
35 Introducing additional chemical or physical interactions in MEA would allow
36
37
38 preparation of a solid PMEA, which in turn would make it possible to manufacture thick
39
40
41 coatings and materials with various shapes without negatively affecting its blood
42
43
44 compatibility. Since the mid-20th century, plasticized PVC has been utilized to collect
45
46
47 and store whole blood, and various blood bags, tubes, catheters, etc. have been
48
49
50 produced. Usually, the sodium salt of citric acid is added to the blood²² acting as an
51
52
53 anticoagulant, and increasing the stability of blood with time. As the most harmful in
54
55
56
57
58
59
60

PVC are plasticizers, new plasticizers other than phthalates (including citrates) are being employed.²²⁻²⁶ Polymers other than PVC are being developed as well.²³⁻²⁴ However, both new plasticizers and polymers are expensive. Additionally, some of the new plasticizers for PVC have a foul odour, cause allergic reactions and are leachable.²⁵ Due to these drawbacks, alternative materials are constantly sought. RENOLIT *Medical* supplies polyolefins,²³ while MELITEK provides *XE film grades* of PP with high purity and without plasticizers for medical and pharmaceutical applications.²⁴ It is claimed that these non-PVC containing alternatives fulfil all the demands posed on blood compatible materials. However, these alternative solutions are not economical.

The goal of this work is to combine benefits of PVC and PMEA into a single platform in an attempt to mitigate the problem associated with the scarcity of materials suitable for blood-contacting applications. Thus, a strategy to convert the low viscosity and highly blood compatible PMEA into a solid polymer without substantially decreasing its blood compatibility by employing copolymerization of MEA with a strong hydrogen-bonding monomer in a simple and facile manner is proposed.

Experimental

Materials

The MEA monomer (Sigma-Aldrich) was passed through a pre-packed disposable column to remove an inhibitor. α,α' -Azobis(isobutyronitrile) (AIBN) was recrystallized from methanol. All other solvents or chemicals were employed as received unless specified otherwise. PVC was kindly supplied from Sekisui co., Japan. AIBN and phosphate-buffered saline (PBS) were obtained from FUJIFILM Wako Pure Chemical Corporation, Japan. Bovine serum albumin (BSA) and human fibrinogen from Sigma-Aldrich, USA, and human whole blood for the platelet adhesion test from Tennessee blood services, USA were employed. The micro-BCA protein assay kit from Thermo Fisher Scientific, USA was used to evaluate the amount of adsorbed protein.

Synthesis and molecular characteristics of polymers

PMEA was prepared by free radical polymerization. The polymerization was conducted in 1,4-dioxane at 75 °C for 6 hours making use of AIBN as the initiator.²⁷⁻²⁸ The polymer was precipitated from THF/hexane mixture, and dried *in vacuo* at 60 °C for several days. The functional 2-{3-(6-methyl-4-oxo-1,4-dihydropyrimidin-2-yl)ureido}ethyl methacrylate and its H-bonding copolymer with MEA (H-PMEA) were synthesized and analyzed as reported in the literature.²⁹ H-PMEA copolymer prepared in this work contains 6 mol% of the functional monomer according to ¹H NMR spectroscopy (Figure S1). The molecular weight characteristics of both polymers are presented in Table 1.

Table 1. Glass transition temperatures, static water contact angles and the molecular weight characteristics of the synthesized PMEA, H-PMEA, and the used PET substrate

Polymer	$T_{g \text{ dry,}}$ °C	$T_{g \text{ hydrated,}}$ °C	M_n^b Da	M_w/M_n	Sessile drop 30 s	Captive bubble 30 s
PMEA	−35.0	−50.1	22,000	2.81	42 ± 2	133 ± 2
H-PMEA	−33.3	−41.5	25,800	2.13	65 ± 2	142 ± 1
PET	76	-	-	-	80 ± 1	115 ± 3

^a Measurements (degree, mean ± SD, n=5) of the polymer films (annealed overnight at 60 °C)

^b Determined by SEC with a PS calibration curve

Analyses

Analytical techniques

¹H NMR spectra were acquired on JEOL 500 MHz JNM-ECX and Bruker Avance 300 MHz spectrometers in DMSO-*d*₆ or CDCl₃ at room temperature.

Molecular weights and polydispersity indices were estimated by Size-Exclusion Chromatography (SEC) equipped with a triple detector array (refractive index, right

angle laser light scattering, and viscometer) SEC system of Malvern Viscotek TDAmix and Tosoh TSKgel columns connected in a series of guard column H_{HR}-H, GMH_{HR}-H × 2, and G2000H_{HR}. Measurements were carried out in THF at 40 °C with a flow rate of 1.0 mL/min. The system was calibrated using narrow molecular weight distribution PS standards in the range of $5 \times 10^2 - 3.64 \times 10^5$ g/mol.

Differential scanning calorimetry (DSC) measurement was conducted in the temperature range of -100-50 °C and at the rate of 5.0 °C/min on a Seiko Instruments Inc. X-DSC7000 purged with N₂. T_g was determined from the second heating curve automatically, and is reported as the onset of the thermal transition. A TGA Q500 apparatus from TA Instruments was utilized to conduct thermogravimetric analyses (TGA). Samples were heated from 20 to 550 °C with a heating rate of 5 °C/min under either air or nitrogen flow.

Mechanical tests

Films of H-PMEA and PVC with a thickness of 0.1 - 0.2 mm were hot pressed from each of the polymers between 2 PTFE plates first at 60 °C for 15 min under a pressure of 5 MPa, and at 150 °C for 15 min at 10 MPa, respectively, and then 5 more minutes at room temperature.

Polymer films were drawn uniaxially at a rate of 10 mm/min with a universal tensile testing machine (Tensilon RTC-1210A, A&D Co., Ltd.) at room temperature. Dogbone specimens 64 mm long and 10 mm broad were used, and the measuring part was 10 mm long.

Quantification of water-polymer interactions

In hydrated macromolecules, 3 kinds of water are determined:^{27,28,30} non-freezing water (*NFW*), intermediate water (*IW*), and free water (*FW*), and their content is given as NFWC, IWC, and FWC, respectively. DSC is employed to estimate the equilibrium water content (EWC) of a polymer as the water content at which a peak at about 0 °C corresponding to the melting of ice and a small shoulder or peak below this temperature originating from melting of *IW* appear, and is given in equation (1):

$$\text{EWC (wt\%)} = ((W_1 - W_0) / W_1) \times 100 \quad (1)$$

where W_0 and W_1 are the weight of the dry and hydrated sample, respectively.

In hydrated polymers, EWC encompasses different types of water as expressed by equation (2):

$$\text{EWC (wt\%)} = \text{NFW (wt\%)} + \text{IW (wt\%)} + \text{FW (wt\%)} \quad (2)$$

$$\text{IW (wt\%)} = \Delta H_{cc} / 334(\text{Jg}^{-1}) \quad (3)$$

$$\text{FW (wt\%)} = (\Delta H_m / 334(\text{Jg}^{-1})) - \text{IW} \quad (4)$$

ΔH_{cc} represents enthalpy change during cold crystallization whereas ΔH_m is enthalpy change during the melting of ice. 3-7 mg of samples was taken. Before measurements, the samples were immersed in ultrapure water for 7 days to attain full hydration.

Preparation and characterization of the polymer surfaces

Film samples were produced and utilized for contact angle (CAs) and atomic force microscopy (AFM) measurements as well as for the human blood platelet adhesion test. For this reason, the polymer samples H-PMEA and PMEA were dissolved in toluene (60 °C for 3 days) or methanol, respectively, to give 0.2 wt/vol% solutions. Round-shaped PET surfaces with the diameter of 14 mm were washed with methanol, and the filtered polymer solutions were spin-coated onto them. A Mikasa spin coater MS-A100 was used to coat the substrates in the following manner: Any particular polymer solution was coated twice onto a substrate at rates of 500 rpm for 5 s, 2000 rpm for 10 s, slope for 5 s, 4000 rpm for 5 s, and slope for 4 s. Afterwards, the substrates were dried at room temperature.

Water CAs on the airside of the polymer films were measured by the sessile drop method with an accuracy of $\pm 2^\circ$ at 25 °C. An air bubble of 2 μL was injected to the hydrated surface immersed in water in the captive bubble method, which is a means of measuring the contact angle between a liquid and a solid by the drop shape analysis.^{31,32} The averages of three measurements carried out at different positions of a film are reported for both measurements.

AFM observations were carried out with a Bioscope Resolve (Bruker) Instrument with a cantilever SNL-10 (spring constant $k = 0.35 \text{ N/m}$, resonance frequency $f = 65 \text{ kHz}$ in air, tip radius $< 12 \text{ nm}$; Bruker). AFM topographies were imaged in PBS in a Peak Force

Tapping mode after the samples had been immersed in PBS for 60 min or longer. The arithmetical mean height is determined before and after immersion in PBS for 60 minutes.

Determination of the Amount of Adsorbed Protein by μ BCA and ELISA^{1-3,27,28,30,31}

Amounts of the platelet poor plasma (PPP) adsorbed on the polymer surfaces were quantified by the μ BCA. In addition, the ELISA was executed to relatively evaluate the conformational alteration of the adsorbed fibrinogen from PPP.

The polymer surfaces for the μ BCA and the ELISA were prepared as follows: a 96-well polypropylene plate was coated with the polymers by applying 15 μ L of the polymer solution (0.2 wt/vol%) of PMEA in methanol or of H-PMEA in toluene, and slowly air-drying the surface at room temperature for 3 days.

For both methods, 100 μ L of PBS was introduced in each well followed by incubating the plate for 1 hour at 37 °C. The PBS was removed, 50 μ L of PPP was put on in each well, and the plate was incubated again for another hour at the same temperature. PPP was removed from each well, and the wells were rinsed with 200 μ L PBS for at least five times. In case of the μ BCA, a 30 μ L solution of 5% sodium dodecyl sulfate and 0.1 N NaOH was used to extract the adsorbed proteins by incubation for 2 hours at 37 °C. The proteins were then evaluated by the μ BCA assay

1
2
3 following the manufacturer's instructions. The protein amount was determined by making use of
4
5 the albumin standard curve that had been prepared for each experiment.
6
7

8 When the ELISA was applied the procedure, in the beginning was the same as above
9
10
11 using PPP. The samples were then incubated with Blocking-One (Nacalai Tesque) for
12
13
14 30 min at the same temperature preventing non-specific reactions. Washing five times
15
16
17 with 200 μ L PBS as before followed. Further incubation with 50 μ L of Anti-Fibrinogen γ '
18
19
20 antibody (Ab) (Millipore) for 1 hour at 37 °C, and then (after washing) with peroxidase-
21
22
23 conjugated anti-mouse Immunoglobulin G (IgG) Ab for 2 hours at 37 °C followed. Lastly,
24
25
26 the samples were incubated with 2,2'-azinobis(3-ethylbenzothiazoline-6-sulfonic
27
28
29 acid)ammonium salt in a buffer (Roche Diagnostics). A plate reader (BIO-RAD) was
30
31
32 used to measure absorbance at a wavelength of 405 nm. The averages of 5
33
34
35
36
37
38
39
40 measurements are reported.
41
42
43
44
45
46

47 *Human Platelet Adhesion Test*^{1-3,27,28,30,31}

48
49

50 The polymer substrates for the platelet adhesion test with human blood were
51
52
53 fabricated in the following manner: 8 × 8 mm squares were cut out of the polymer
54
55
56
57
58
59
60

coated substrates, and were mounted on an SEM specimen stage with a double-sided tape. Platelet-rich plasma (PRP) and PPP were separated from human blood by centrifuging in two stages: the first stage involved centrifuging at 1500 rpm for 5 min to get PRP while the second stage involved centrifuging the same blood at 4000 rpm for 10 min to get PPP. The cells in PRP and PPP were counted on a hemocytometer, and a plasma solution comprising 4×10^7 cells cm^{-2} of platelets was obtained by mixing the PRP and PPP solutions in a predetermined ratio. 200 μL of the final solution was applied onto the polymer-coated substrates, which afterwards were washed with PBS twice. Immersion in 1% glutaraldehyde in PBS for 120 min at 37 °C ensured fixation of the adhered platelets. As the final step, the substrates were washed in this order: once with PBS, once with PBS-water 1:1 mixture, and twice with pure water. The substrates were examined with SEM to determine the number of adhered platelets. Human blood obtained from 3 different donors was used, and the platelet adhesion test was carried out 3 times for statistical purpose. The averages of 5 points measured on 3 different films are reported.

Results and discussion

A copolymer of MEA with the functional methacrylic monomer 2-{3-(6-methyl-4-oxo-1,4-dihydropyrimidin-2-yl)ureido}ethyl methacrylate^{8,9,33} was synthesized as reported by Shabir et al.²⁹ The copolymer contained about 6 mol% of the functional monomer as judged by ¹H NMR (Figure S1). The structure of the copolymer is depicted also in Scheme 1a. Because of the multiple hydrogen bonding, the copolymer was designated as hydrogen-bonding PMEAs (H-PMEAs). This kind of bonding between the copolymer chains is realized through strongly associating stickers (Scheme 1c and 1d). Introducing such stickers turns liquid PMEAs into solid, rubber-like, and not sticky H-PMEAs, which can be processed into a transparent self-supporting film shown in Scheme 1b. Films of various thicknesses can be produced by pressing the material at 60 °C and 5 MPa, or by solvent casting.

Scheme 1. Chemical structure of poly[2-methoxyethyl acrylate-co-2-{3-(6-methyl-4-oxo-1,4-dihydropyrimidin-2-yl)ureido}ethyl methacrylate] (H-PMEA) (a), appearance of the

polymer as a transparent self-supporting film (b), morphology with stickers (c), and multiple hydrogen bonding at the side chains (d).

Thermal and mechanical properties

Besides being solid, H-PMEA features thermal stability. The overlay of the TGA curves of PMEA and H-PMEA in air and nitrogen is shown in Figure S1. The initial degradation of H-PMEA starts at around 30 °C later than that of PMEA, and it occurs in 2 steps. Having in mind the high amount of water that is associated with the MEA polymers even in dry conditions it is assumed that the process of dehydration for both polymers finishes at 300 °C. The second step is related to the main degradation, where H-PMEA decomposes at a higher temperature than PMEA. Thus, H-PMEA is more thermally stable than PMEA, a property gained by forming physical cross-links.

For comparison, PVC degrades in 3 steps and at 300 °C already 45% to 50% of the polymer is thermally decomposed.

The rheological properties of the copolymers of MEA and the functional methacrylic monomer bearing a 6-methyl-2-ureido-4[1H]-pyrimidone group (3 or 8 mol% of the functional monomer) have already been evaluated.²⁹ We investigate the basic mechanical properties of the H-PMEA (with 6 mol% of the functional monomer) synthesized for this work and PVC. Tensile stress measurements and DMA were

performed at room temperature. The film thickness was 0.1 and 0.2 mm for H-PMEA and PVC, respectively. Big differences in the elastic modulus (0.3 and 220 PPa), tensile stress (1.1 and 57.2 MPa), and elongation (814 and 8%) of H-PMEA and PVC films were observed. The elastic modulus and the T_g of H-PMEA, determined by DMA are close to those from the tensile stress and DSC measurements (Table 1). These results show that although being of lower strength, H-PMEA is a rubber-like polymer, which can be employed to form thick coatings. Furthermore, the acquired mechanical data confirm, that this polymer is able to withstand the necessary loads for forming free-standing films and articles, possibly with various forms and dimensions. The MW and the number of hydrogen-bonding stickers in the H-PMEA can be adjusted further to obtain particular target properties of the material.

Hydration structure of PMEA and H-PMEA

The hydration structure of H-PMEA is evaluated by DSC, AFM, and contact angle (CA) measurements, and compared to PMEA with a similar MW (Table 1). The T_g of both polymers in a dry state are quite close, however, they differ a lot in the hydrated

1
2
3 state. That PMEAs exhibit 15 °C lower T_g in its hydrated state is already known. It is
4
5
6
7 related to the polymer-water interactions that will be elaborated later in this paragraph.
8
9
10 T_g of H-PMEA in a hydrated state has decreased by only 8 °C – the hydrogen bonding
11
12
13 and thereby lower mobility restrict the diffusion of water, and therefore its interaction
14
15
16
17 with the high viscosity polymer is weakened. However, the T_g of the copolymer is still
18
19
20 below room temperature, –33.5 °C.
21
22
23

24 The CA measurements show that the intermediately hydrophilic PMEAs are transformed
25
26
27 into an intermediately hydrophobic H-PMEA polymer (Table 1). While the water CA (by
28
29
30 sessile drop method) is stable in case of PMEAs (42°), it continues changing with time
31
32
33 and from 65° at 30 min reaches 58° at 60 min for H-PMEA. The air CA (by captive
34
35
36 bubble method) is stable for both polymers and decreases from 142 to only 140° for H-
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
PMEAs during the 60 min scan – this polymer needs longer time to form its interfacial
structure with water. However, after immersing 24 hours in water there is no more
change in the air CA of H-PMEA. All these show that the copolymerization and the
physical cross-links have turned PMEAs into more hydrophobic H-PMEAs with lower
mobility – a feature responsible for the platelet adhesion onto a polymer.

Based on its interactions with a polymer, 3 kinds of water in macromolecules are classified: non-freezing water (*NFW*), intermediate water (*IW*), and free water (*FW*). In this order the polymer-water interactions decrease, and therefore also the freezing bound water is referred to as *IW* as it has an intermediate association with the polymer matrix. It is believed, that polymer's blood compatibility is related to the amount of *IW*. The water content of both polymers is therefore investigated by DSC, and the results are summarized in Table 2. Additionally, the DSC curves are shown in Figure S2. In the cooling scan, only the T_g of H-PMEA could be detected. In contrast, PMEA shows *IW* already in the cooling scan, whereas in case of H-PMEA it is observed in the heating scan and with much lower content. This behaviour is characteristic of polymers with lower mobility. Moreover, EWC of H-PMEA is quite different from that of PMEA; in the former, this amount is more than twice decreased as the physical cross-links lead to a reduction in free volume and a reduction in the polymer chain mobility. This prevents water from easily entering into the free volume of the polymer. More data presented in Table 2 show that this has happened by decreasing primarily *FW* (by 90%) and *IW* (by 40%) in H-PMEA. The H-bonding present in the polymer matrix increases the

interactions between macromolecules and decreases those between water and the polymer chains: *IW* and *NFW* predominate in PMEA as compared to H-PMEA. This influences *FW* as well, which is being 10 times less in H-PMEA than in PMEA. The IWC is also lower in H-PMEA as compared to the NFWC, possibly due to the added interactions of its cross-links with water resulting in more *NFW*. These results are expected to influence the platelet adhesion on the surface of H-PMEA too.

Table 2. Water content of the polymers

Polymer	EWC wt%	NFWC wt%	IWC wt%	FWC wt%	IWC/NFWC
PMEA	9.6	1.8	3.8	4.0	2.1
H-PMEA	4.3	1.6	2.3	0.4	1.4

AFM of the hydrated polymers

The interface morphology of the samples in dry and hydrated states was evaluated by AFM. The AFM images of the dry polymers (not shown here), PMEA³⁴⁻³⁶ and H-PMEA,

present flat structures with an arithmetical mean height around 5 nm. By immersing the substrate with the polymers in PBS, continuous hydration of the surface induces phase separation forming a nanoscale structure. Therefore, in the AFM images of the hydrated polymers protrusions appear due to the micro-phase separation into polymer-rich and water-rich domains.³⁴⁻³⁶ Such structures of polymer and water at the interfacial region are characteristic for biopolymers containing a large amount of *W*. These interfacial nanometer-scale structures in case of both investigated polymers have similar shapes and are with similar domain sizes (Figure 1). The height of the protrusions for H-PMEA has the same range as previously found for PMEA: 50 - 80 microns.^{1-3,6,34-36} However, the numbers of the soft protrusions/hills seem to be more and at the same time the areas of the valleys are smaller in H-PMEA as compared to PMEA, probably because of these two being hydrophobic and hydrophilic, respectively. These facts resulted in the less pronounced phase separation of H-PMEA clearly visible in its 2D and 3 D images. The H-bonding obstructs segregation of the MEA polymer at the polymer-PBS interface, which results in the possibility for the blood cells to settle down probably on the hills.³⁴⁻³⁶

Figure 1. Two- (left) and three-dimensional (right) images of the polymer/PBS interfaces of H-PMEA (a) and PMEAE (b)

Protein adsorption and denaturation behavior on MEA polymers and negative control substrates

Plasma proteins including fibrinogen and albumin adsorb easily to the material surface through nonspecific interactions, and the cell adhesion behavior depends strongly on the amount, the composition, and the structure of adsorbed proteins. Thus, its surface adsorption amount was analyzed by a micro BCA using PPP. The result is shown in

Figure 2. A significant change was observed for the adsorbed proteins from PPP onto PMEA and H-PMEA, probably due to the effect of physical crosslinking that restrict the mobility of polymer chains and reduces the amount of IWC. Even though H-PMEA adsorbs more proteins than PMEA, their amount is much less than the ones adsorbed onto PP and especially PVC.

Figure 2. Amount of adsorbed proteins determined by the micro BCA method with PPP.

The data represent the mean $\pm$ SD ($n = 5$). **: $P < 0.01$ vs. PMEA, and *: $P < 0.05$ vs. PMEA. PP and PVC are used as controls.

Subsequently, the conformational alteration of adsorbed fibrinogen was quantified by an ELISA. The plasma proteins change in conformation due to the contact with the

foreign body surface. The conformational alteration exposes the platelet adhesion site in fibrinogen, and the exposure degree of this site on the material surface has a direct impact on the non-thrombogenic property of materials. Thus, the ELISA with the antibody that can identify c-terminus in the fibrinogen γ' chains – the platelet adhesion site – was employed to evaluate the degree of the site exposure using PPP. The results are presented in Figure 3. There was no significant difference between PMEA and H-PMEA, and the conformation of adsorbed fibrinogen remained unchanged against the adsorption onto both MEA polymer surfaces. In contrary, this is not the case for the negative controls, PP and PVC, where even for PVC the conformational alteration of fibrinogen is almost doubled as compared to PP (Figure 4).

Figure 3. Conformationally altered fibrinogen in the adsorbed proteins evaluated by the ELISA method with PPP detected with an anti-fibrinogen γ' chain antibody after 1 h. The data represent the mean $\pm$ SD ($n = 5$). **: $P < 0.01$ vs. PMEA. PP and PVC are used as controls.

Analyses with human blood

Platelet adhesion test with human blood is the best direct method to reveal the blood compatibility of polymers. As depicted in Figure 4, the blood compatibility of H-PMEA is slightly decreased as compared to that of PMEA, probably due to its higher hydrophobicity, lower water and IW content, and chain mobility. Also, the free volume of the polymers is expected to play a role, as the H-bonding should reduce the distances between 2 sliding macromolecules. However, the decrease of the platelet adhesion on both MEA polymers as compared to PET and PVC is enormous. These results further substantiate the anticipated big advantage of the examined H-PMEA over the other hydrophobic polymers used as negative control (Figure 2-4).

Figure 4. Platelet adhesion test with human blood onto PMEA and H-PMEA as compared to PET and PVC. Blood of three donors was tested in triplicates, and five fields were analyzed per substrate. The data represent the mean $\pm$ SD. **: $P < 0.01$ vs. PMEA. PP and PVC were used as controls. The number of adhered platelets was classified into three types according to the degree of activation as shown in the figure: (I) native (spherical shape), (II) partially activated (hemispherical shape with several pseudopods), and (III) activated (spread shape with numerous pseudopods or flat discoid).

The morphology of the platelets (Figure 4) was observed by SEM (Figure 5). The platelet adhesion was suppressed by both PMEA and H-PMEA films onto PET,

1
2
3 compared with that of untreated PET and PVC. The adhered platelets on all surfaces
4
5
6
7 except PME A formed many pseudopods and spread, which means that even though
8
9
10 there was a low number onto H-PME A film, more than half of the platelets were highly
11
12
13
14 activated. PET and PVC have much higher numbers of adhered platelets, 33 and 48 %
15
16
17 of which show the highest activation degree III.
18
19
20
21
22
23

Figure 5. Scanning electron micrographs of platelets adhered onto the surface of PET, PMEA, H-PMEA, and PVC. The scale bare corresponds to 50 μm in all micrographs.

The trend for the platelet compatibility of the MEA polymers evaluated in this work is the same in all methods employed: ELISA, micro BCA, and human blood test. Normalized values of the protein adsorption of the MEA polymers to that of PVC, presented in Figure 6, suggest that the most blood compatible is PMEA, followed by H-PMEA. In this order, the water content of the polymers and their IWC, as well as the mobility and the hydrophilicity decreases, which explains the slightly decreased blood compatibility of H-PMEA. This observation is in accord with the morphology/topography of hydrated PMEA and H-PMEA obtained by AFM. Presence of more polymer-rich protrusions and less water-rich valleys in hydrated H-PMEA results in H-PMEA being slightly less blood compatible than PMEA as the protrusions are believed to serve as scaffolds for fibrinogen (a protein playing an important role in thrombus formation) adsorption and the valleys are expected to comprise much of W .³⁴⁻³⁶ Therefore, these

parameters can be used as a quantitative guidepost for the blood compatibility of various materials.

Figure 6. Normalized values of the conformational alteration of adsorbed fibrinogen evaluated by ELISA (white), the amount of adsorbed protein from PPP evaluated by μ -BCA (black), and the number of adhered platelets by human platelet adhesion test (red) to those of PVC.

Despite slight decrease in blood compatibility, the gain from turning the viscous PMEA to solid H-PMEA is enormous: preparation of free-standing films, thick coatings, possibly articles with various shapes and geometries for the medicinal and anti-fouling industry with still significantly higher compatibility with human blood as compared to PVC.

1
2
3
4 **Conclusion**
5
6

7 In conclusion, introducing strongly-associating hydrogen-bonding stickers in PMEA
8
9
10 resulted in transforming this low viscosity polymer featuring excellent blood compatibility
11
12
13
14 into a solid, rubber-like, and thermally stable supramolecular copolymer H-PMEA. Blood
15
16
17 compatibility is assessed by 3 methods showing either no or slightly increased
18
19
20
21 adsorption of platelets onto the rubbery H-PMEA when comparing it with the low
22
23
24 viscosity PMEA. These changes in case of H-PMEA may be attributed to its higher
25
26
27
28 hydrophobicity, lower chain mobility in hydrated condition, lower water, *FW*, and *IW*
29
30
31 content as compared to the MEA homopolymer. Analysis of the free volume of both
32
33
34
35 MEA polymers, which should also influence the water-polymer interactions at the
36
37
38 interface, is being carried out. While sacrificing a bit the blood/platelet compatibility of
39
40
41
42 PMEA, H-PMEA allows for the preparation of free-standing films and thick coatings as
43
44
45 well as potentially tubes and articles with various shapes and geometries for the
46
47
48
49 medicinal and anti-fouling industry with still significantly higher compatibility with human
50
51
52 blood as compared to PVC. Thus, H-PMEA displays promising properties as the
53
54
55
56 material that may replace polymers in products used in contact with blood or storage of
57
58
59
60

1
2
3 blood, which either are expensive or are known to comprise harmful for our health
4
5
6
7 compounds. The period of implementation during storage and processing can be at the
8
9
10 same time extended, the platelet adhesion dramatically suppressed, and the material
11
12
13 recycled. This strategy will be implemented in our laboratories to turn other viscous
14
15
16
17 blood compatible polymers into solid materials as well.
18
19
20
21
22
23

24 ASSOCIATED CONTENT

25 26 27 28 Supporting Information

29
30
31
32
33 Supporting Information. ^1H NMR spectroscopy, TGA, and DSC results for the
34
35
36 discussed polymers.
37
38
39

40
41 The Supporting Information is available free of charge on the ACS Publication
42
43
44 website at DOI: ***.
45
46
47

48 AUTHOR INFORMATION

49 50 51 52 Corresponding Author

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

*E-mail: masaru_tanaka@ms.ifoc.kyushu-u.ac.jp

ORCID

Katja Jankova: 0000-0002-4218-064X

Irakli Javakhishvili: 0000-0003-3681-3161

Shingo Kobayashi: 0000-0002-8357-8654

Ryohei Koguchi: 0000-0003-0017-4783

Daiki Murakami: 0000-0002-5552-4384

Toshiki Sonoda: 0000-0002-0504-7559

Masaru Tanaka: 0000-0002-1115-2080

Notes

The authors declare no competing financial interest.

ACKNOWLEDGEMENTS

Project PROGRESS 100 from Kyushu University is acknowledged for financial support. This work was partially supported by Dynamic Alliance for Open Innovation Bridging Human, Environment and Materials.

REFERENCES

- (1) Tanaka, M.; Motomura, T.; Kawada, M.; Anzai, T.; Kasori, Y.; Shiroya, T.; Shimura, K.; Onishi, M.; Mochizuki, A. Blood compatible aspects of poly(2-methoxyethylacrylate) (PMEA) – relationship between protein adsorption and platelet adhesion on PMEA surface. *Biomaterials* **2000**, *21* (14), 1471–1481.
- (2) Tanaka, M.; Motomura, T.; Kawada, M.; Anzai, T.; Kasori, Y.; Shimura, K.; Onishi, M.; Mochizuki, A.; Okahaya, Y. A new blood-compatible surface prepared by poly(2-methoxyethylacrylate)(PMEA) coating-protein adsorption on PMEA surface. *Jpn. J. Artif. Organs* **2000**, *29*, 209-216.
- (3) Tanaka, M.; Mochizuki, A.; Ishii, N.; Motomura, T.; Hatakeyama, T. Study of Blood Compatibility with Poly(2methoxyethyl acrylate). Relationship between Water Structure and Platelet Compatibility in Poly(2-methoxyethyl acrylate-co-2-hydroxyethyl methacrylate). *Biomacromolecules* **2002**, *3* (1), 36–41.

- (4) Anzai, T.; Okumura, A.; Kawaura, M.; Yokoyama, K.; Oshiyama, H.; Kido, T.; Nojiri, C. Evaluation of the Biocompatibility of an In Vitro Test Using a Poly(2-methoxyethylacrylate) Coated Oxygenator. *Jpn. J. Artif. Organs* **2000**, *9*, 73-77.
- (5) Lee, W.; Kobayashi, S.; Nagase, M.; Jimbo, Y.; Saito, I.; Inoe, Y.; Yambe, T.; Sekino, M.; Malliaras, G.G.; Yokota, T.; Tanaka, M.; Someya, T. Nontrombogenic, stretchable, active multielectrode array for electroanatomical mapping. *Science Advances* **2018**, *4*:eaau2426.
- (6) Murakami, D.; Mawatari, N.; Sonoda, T.; Kawazaki, A.; Tanaka, M. Effect of the molecular weight of Poly(2-methoxyethyl acrylate) on Interfacial Structure and Blood Compatibility. *Langmuir* **2019**, *35*, 2808-2813.
- (7) Kureha, T.; Hiroshige, S.; Matsui, S.; Suzuki, D. Water-immiscible bioinert coatings and film formation aqueous dispersions of poly(2-methoxyethyl acrylate) microspheres. *Colloids Surf. B* **2017**, *155*, 166-172.
- (8) Bottehuis, N.E.; van Beek, D.J.M.; van Gemert, G.M.L.; Bosman, A.W.; Sijbesma, R.P. Self-assembly and morphology of polydimethylsiloxane supramolecular thermoplastic elastomers, *J. Polym. Sci., Part A: Polym. Chem.* **2008**, *46* (12), 3877-3885.
- (9) Yamauchi, K.; Lizotte, J.R.; Long, T.E. Thermoreversible poly(alkyl acrylates) consisting of self-complementary multiple hydrogen bonding. *Macromolecules* **2003**, *36* (4), 1083-1088.
- (10) Ogliani, E.; Yu, L.; Javakhishvili, I.; Skov, A.L. A thermo-reversible silicone elastomer with remotely controlled self-healing. *RSC Adv.* **2018**, *8*, 8285-8291.
- (11) Chen, S.; Mahmood, N.; Beiner, M.; Binder, W.H. Self-Healing Materials from V- and H-Shaped Supramolecular Architectures. *Angew. Chem. Int. Ed.* **2015**, *54*, 10188-10192

- (12) Kajita, T.; Noro, A.; Mtsushita, Y. Design and properties of supramolecular elastomers. *Polymer* **2017**, *128*, 297-310.
- (13) Weber, M.J.; Dankers, Y.W. Supramolecular hydrogels for biomedical applications. *Macromol. Biosci.* **2019**, *19*, 1800452.
- (14) Pan, Y.; Hu, J.; Yang, Z.; Tan, L. From Fragile Plastic to Room-Temperature Self-Healing Elastomer: Tuning Quadruple Hydrogen Bonding Interaction through One-Pot Synthesis. *ACS Appl. Polym. Mater.* **2019**, DOI:10.1021/acsapm.8b00153
- (15) Dimitrov, I.; Jankova, K.; Hvilsted, S. Synthesis of Polystyrene-Based Random Copolymers with Balanced Number of Basic or Acidic Functional Groups. *J. Polym. Sci., Part A: Polym. Chem.* **2010**, *48*, 2044–2052.
- (16) Kerres, J.; Ullrich, A.; Haring, T.; Baldauf, M.; Gebhardt, U.; Preidel, W. Preparation, characterization and fuel cell application of new acid-base blend membranes. *J. New Mater. Electrochem. Syst.* **2000**, *3* (3), 2000, 229-239.
- (17) Li, W.; Manthiram, A.; Guiver, M.D. Acid-base blend membranes consisting of sulfonated poly(ether ether ketone) and 5-amino-benzotriazole tethered polysulfone for DMFC. *J. Membrane Sci.* **2010**, *362*, 289-297.
- (18) Hietala, S.; Mononen, P.; Strandman, S.; Järvi, P.; Torkkeli, M.; Jankova, K.; Hvilsted, S.; Tenhu, H. Synthesis and rheological properties of an associative star polymer in aqueous solutions. *Polymer* **2007**, *48*, 4087–4096.
- (19) Hietala, S.; Strandman, S.; Järvi, P.; Torkkeli, M.; Jankova, K.; Hvilsted, S.; Tenhu, H. Rheological Properties of Associative Star Polymers in Aqueous Solutions: Effect of Hydrophobe Length and Polymer Topology. *Macromolecules* **2009**, *42* (5), 1726–1732.

- (20) Jankova, K.; Jannasch, P.; Hvilsted, S. Ion conducting solid polymer electrolytes based on polypentafluorostyrene-*b*-polyether-*b*-polypentafluorostyrene prepared by atom transfer radical polymerization *J. Mater. Chem.* **2004**, *14*, 2902-2908.
- (21) Jannasch, P. Ionic conductivity in physical networks of polyethylene-polyether-polyethylene triblock copolymers *Chem. Mater.* **2002**, *14*, 2718–2724.
- (22) Haishima, Y.; Kawakami, T.; Fukui, C.; Tanoue, A. Characterization of alternative plasticizers in poly(vinyl chloride) sheets for blood containers. *J. Vinyl Addit. Techn.* **2015**, *22* (4), 520-528.
- (23) www.renolit.com: Blood and blood component applications.
- (24) www.melitek.com; www.pvcfreebloodbag.eu: New PVC-free blood bags have reached a major milestone, **2015**.
- (25) Bhaskaran Nair, C.S.; Vidya, R.; Ashalatha, P.M. Hexamoll DINCH plasticised PVC containers for the storage of platelets. *Asian J. Transfus. Sci.* **2011**, *5*, 18-22.
- (26) Dumont, L.J.; VandenBroeke, T. Seven-day storage of apheresis platelets: report on an in vitro study. *Transfusion* **2003**, *43*, 143-150.
- (27) Tanaka, M.; Mochizuki, A. Effect of water structure on blood compatibility - thermal analysis of water in poly(meth)acrylate. *J. Biomed. Mater. Res.* **2004**, *68A* (4), 684–695.
- (28) Sato, K.; Kobayashi, S.; Sekishita, A.; Wakui, M.; Tanaka, M. *Biomacromolecules* **2017**, *18*, 1609-1616.
- (29) Shabbir, A.; Javakhishvili, I.; Cervený, S.; Hvilsted, S.; Skov, A.L.; Hassager, O.; Alvarez, N. Linear Viscoelastic and Dielectric Relaxation Response of Unentangled UPy-Based Supramolecular Networks. *Macromolecules* **2016**, *49*, 3899-3910.

- (30) Koguchi, R.; Jankova, K.; Tanabe, N.; Amino, Y.; Hayasaka, Y.; Kobayashi, D.; Miyajima, T.; Yamamoto, K.; Tanaka, M. Controlling the hydration structure with small amount of fluorine to produce blood compatible fluorinated poly(2-methoxyethyl acrylate). *Biomacromolecules*, **2019**, *20*, 2265-2275.
- (31) Kobayashi, S.; Wakui, M.; Iwata, Y.; Tanaka, M. Poly(ω -methoxyalkyl acrylate)s: Nonthrombogenic Polymer Family with Tunable Protein Adsorption. *Biomacromolecules* **2017**, *18* (12), 4214-4223.
- (32) Sato, K.; Kobayashi, S.; Sekishita, A.; Wakui, M.; Tanaka, M. Synthesis and Thrombogenicity Evaluation of Poly(3-methoxypropionic acid vinyl ester): A Candidate for Blood-Compatible Polymers. *Biomacromolecules* **2017**, *18* (5), 1609–1616.
- (33) Kajita, T.; Noro, A.; Matsushita, Y. Design and properties of supramolecular elastomers. *Polymer* **2017**, *128*, 297-310.
- (34) Murakami, D.; Kobayashi, S.; Tanaka, M. Interfacial Structures and Fibrinogen Adsorption at Blood- Compatible Polymer/Water Interfaces. *ACS Biomater. Sci. Eng.* **2016**, *2* (12), 2122–2126.
- (35) Murakami, D.; Kitahara, Y.; Kobayashi, S.; Tanaka, M. Thermosensitive Polymer Biocompatibility based on Interfacial Structure at Biointerface, *ACS Biomater. Sci. Eng.* **2018**, *4*, 1591-1597.
- (36) Ueda, T.; Murakami, D.; Tanaka, M. Analysis of interaction between interfacial structure and fibrinogen at blood-compatible polymer/water interface. *Front. Chem.* **2018**, *6*, 542: doi: 10.3389/fchem.2018.00542.

Table of content graphics