Deactivation of a CoMo catalyst during catalytic hydrolysis of biomass. Part I: Product distribution and composition

Stummann, Magnus Zingler; Høj, Martin; Hansen, Asger Baltzer; Beato, Pablo; Wiwel, Peter; Gabrielsen, Jostein; Jensen, Peter Arendt; Jensen, Anker Degn

Published in:
Energy and Fuels

Link to article, DOI:
[10.1021/acs.energyfuels.9b02523](https://doi.org/10.1021/acs.energyfuels.9b02523)

Publication date:
2019

Document Version
Peer reviewed version

[Link back to DTU Orbit](#)

Citation (APA):
Stummann, M. Z., Høj, M., Hansen, A. B., Beato, P., Wiwel, P., Gabrielsen, J., Jensen, P. A., & Jensen, A. D. (2019). Deactivation of a CoMo catalyst during catalytic hydrolysis of biomass. Part I: Product distribution and composition. *Energy and Fuels*, 33(12), 12374-12386. <https://doi.org/10.1021/acs.energyfuels.9b02523>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Biofuels and Biomass

Deactivation of a CoMo catalyst during catalytic hydropyrolysis of biomass. Part I: Product distribution and composition

Magnus Zingler Stummann, Martin Høj, Asger Baltzer Hansen, Pablo Beato, Peter Wiwel, Jostein Gabrielsen, Peter Arendt Jensen, and Anker Degn Jensen

Energy Fuels, **Just Accepted Manuscript** • DOI: 10.1021/acs.energyfuels.9b02523 • Publication Date (Web): 14 Nov 2019

Downloaded from pubs.acs.org on November 18, 2019

Just Accepted

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.

Deactivation of a CoMo catalyst during catalytic hydropyrolysis of biomass. Part I: Product distribution and composition

---

M.Z. Stummann^a, M. Høj^a, A. B. Hansen^b, P. Beato^b, P. Wiwel^b, J. Gabrielsen^b, P. A. Jensen^a, A. D. Jensen^{a*}

^a*Department of Chemical and Biochemical Engineering, Technical University of Denmark (DTU), 2800 Kgs. Lyngby (Denmark)*

^b*Haldor Topsøe A/S, 2800 Kgs. Lyngby (Denmark)*

^{*}*aj@kt.dtu.dk*

Abstract

Deactivation of a sulfided CoMo/MgAl₂O₄ catalyst during fluid bed catalytic hydropyrolysis of biomass (beech wood) was studied. The stability of the catalyst was investigated by converting approximately 4.4 kg of biomass and collecting the liquid and solid products for every 1 kg fed, using the same catalyst load. The total time on stream was 16.2 h. A secondary hydrotreating reactor with a sulfided NiMo/Al₂O₃ catalyst was used after the fluid bed to further deoxygenate the vapors. The condensed organics and C₄₊ gasses yield for each 1 kg fed was 22.2 ± 1 wt.%, which was variations within the experimental uncertainty. The CO and CO₂ yield during the experiment increased from 14.9 to 18.2 wt.% daf, while the aqueous phase yield decreased from 38.0 to 35.1 wt.% daf from the first to the fifth kilogram fed. The change in CO, CO₂, and aqueous phase yields was ascribed to a decrease in hydrodeoxygenation activity of the used catalysts. The concentration of oxygen in the condensed organic phase increased from 40 to 2832 ppm, indicating that deactivation of the catalyst in both the fluid bed and the HDO reactor occurred. Our previous study¹ has shown that potassium, a known catalyst poison, is transferred from the beech wood to the catalyst, and the effect of doping the catalyst with 1.9 wt.% potassium was therefore also investigated. The results were compared to a similar experiment with a fresh catalyst. Both experiments were performed without the

1
2
3
4 24 downstream hydrotreating reactor to show the effect on the chemistry in the fluid bed reactor only. This
5
6 25 showed that potassium decreased the catalyst's cracking, hydrogenation, and hydrodeoxygenation activity.
7
8
9 26 Doping the catalyst with potassium also increased the char and coke yield from 13.3 to 14.6 wt.% daf,
10
11 27 indicating that potassium can act as a catalyst for polymerization of the pyrolysis vapors. Overall, the
12
13 28 results show promise for using CoMo based catalysts for catalytic hydrolysis, but also indicates that
14
15 29 attention should be paid to catalyst deactivation.
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

30   **Abbreviations**

AED	Atomic emission detector
BET	Brunauer–Emmett–Teller
daf	Dry, ash free basis
db	Dry basis
diAro	Diaromatics
FB	Fluid bed
FID	Flame ionization detector
GC	Gas chromatograph
HDO	Hydrodeoxygenation
ICP-OES	Inductive coupled plasma optical emission spectroscopy
mAro	Monoaromatics
MS	Mass spectrometry
Naph	Naphthenes
O-Ali	Oxygenated aliphatics
O-Aro	Larger oxygenated aromatics
Par	Paraffins
PhOH	Phenolics
Ph(OH) ₂	dihydroxybenzene
SSA	Specific surface area
SIMDIS	Simulated distillation by GC
STEM	Scanning transmission electron microscopy
TAN	Total acid number
Temp.	Temperature

tetAro+	Tetra- and higher aromatics
triAro	Triaromatics
TOS	Time on stream
TPD	Temperature programmed desorption

31

32

1 Introduction

The world's energy consumption continues to increase², while the need for decreasing the greenhouse gas (GHG) emission becomes more urgent³, making it necessary to replace fossil fuels with renewable fuels in the near future. During the last decades many researchers have investigated fast pyrolysis as a means of producing carbon based liquid fuels from biomass^{4,5}. However, the produced bio-oil has a high acidity and low heating value due to its high oxygen content⁶. In order to use it in the transportation sector it must be upgraded by hydrotreating. This is a catalyzed reaction at high temperatures (350-400°C) and pressures (80-300 bar), where catalyst deactivation and reactor plugging are common problems due to coking^{7,8}.

Catalytic hydropyrolysis of biomass has gained interest since the Gas Technology Institute (GTI)^{9,10} showed that it is possible to get high yields, between 21 to 46 wt.% dry ash free (daf), of oxygen free oil (<1 wt.%) with their IH²® process. In this process, biomass is fed into a pressurized reactor loaded with a hydrotreating catalyst fluidized by hydrogen. Here, the biomass undergoes fast pyrolysis leading to the formation of char, light gasses, water and oil vapors with a low oxygen content. The char is removed immediately after the fluid bed and the gas and uncondensed oil are transferred to a hydrotreating reactor where deep hydrodeoxygenation (HDO) takes place^{9,10}. The IH²® process was operated continuously for 750 hours with a biomass feeding rate of 50 kg/h without any observed deactivation. However, due to catalyst entrainment fresh catalyst was continuously added to the fluid bed reactor during the experiment¹⁰. Life cycle assessments of this process have indicated that gasoline and diesel produced by the IH²® process have 30-96 % lower greenhouse gas (GHG) emissions compared to gasoline and diesel produced from fossil fuels. The difference in the GHG emissions mainly depends on the type of biomass used, with bagasse giving the largest reduction^{11,12}.

Dayton et al.¹³⁻¹⁵ also used a fluid bed reactor to study catalytic hydropyrolysis of woody biomass and tested several pre-reduced catalysts, including a commercial NiMo hydrotreating catalyst and a molybdenum oxide based catalyst. Their experiments were conducted at 375 to 500 °C and at total

pressure between 1 and 31 bar. Operating at atmospheric pressure they were able to obtain a condensable organic carbon yield(C_{4+}) of 43 %, with an oxygen concentration of 6.2 wt.% dry basis (db) in the condensed organic phase¹⁵. However, the fresh catalysts were only to a limited extent characterized and the spent catalysts were not characterized. Furthermore they conducted a 10 days stability test where they used a reduced NiMo catalyst operating at 450 °C 20.7 bar pressure, 40 vol.% H_2 and each day used approximately 1 kg of biomass. During this experiment the organic yield, oxygen content and CO_2/CO ratio were fairly stable, indicating a high catalyst stability¹⁴. However, this was partly because they regenerated the catalyst each day by oxidation followed by reduction. This stability experiment therefore only shows that the process is stable when the catalyst is continuously regenerated. Likewise, using a pyroprobe analyzer Gamliel et al.^{16–18} investigated the effect of using reduced metal catalysts and focused on Ni on a zeolite (H-ZSM-5) support. The fresh catalysts were characterized, but the spent catalysts were not. Chandler and Resende¹⁹ studied the differences of catalytic pyrolysis and catalytic hydropyrolysis in a fluid bed reactor using H-ZSM-5 and observed that conducting the pyrolysis in hydrogen lead to a lower loss of catalyst surface area and lower coke yield.

Sulfided Co or Ni promoted Mo catalysts are widely used in oil refineries for hydrotreating of the crude oil and several studies have shown that they also are active for HDO of bio-oil and model components^{20–29}. Because most types of biomass contain sulfur⁶, one of the advantages of these sulfided Mo promoted catalysts is that they are sulfur tolerant, while it is well-known that most reduced metal catalysts are not. Our group have therefore mainly used these Mo promoted catalysts for catalytic hydropyrolysis in our previous work, where we have studied the effect of temperature and pressure^{30,31}, the effect of using catalytically inactive materials (pure catalyst carrier material), different commercial hydrotreating catalysts, and the natural mineral bog iron as catalyst³². Additionally we investigated the difference between Co and Ni promoted Mo, and unpromoted Mo as catalysts in the fluid bed¹. Our work showed that the Co promoted Mo catalyst was most favorable to use in the catalytic hydropyrolysis reactor compared to the Ni promoted Mo and unpromoted Mo catalyst¹. Furthermore, we observed that alkali metals, particularly

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

potassium and calcium, are transferred from the beech wood to the catalyst, and since potassium is a known poison for hydrodeoxygenation catalysts^{33,34}, this could lead to catalyst deactivation.

In the present work, the deactivation of a CoMoS/MgAl₂O₄ catalyst was investigated in a series of hydropyrolysis experiments using a fluid bed reactor. Firstly, the stability of the catalyst was investigated by a 16.2 h semi-continuous experiment conducted over five days using the same catalyst load, where the product distribution and composition were followed by collecting products each day. Secondly, the effect of poisoning the catalyst by doping it with potassium, in the form of K₂CO₃, was studied. In this work (part I) we report detailed product characterization including the composition of the condensed liquids, while in part II³⁵ we characterize the spent catalysts and the produced char in detail. This is to our knowledge the first study in the open literature where the effect of the time on stream on catalytic hydropyrolysis with a well-defined catalyst is tested and the effect of potassium on the catalytic activity in catalytic hydropyrolysis of biomass is investigated.

2 Material and methods

2.1 Biomass feedstock

Beech wood (bark free) was used as feedstock. The beech wood has previously been used in catalytic hydropyrolysis experiments³⁰. The moisture and ash content in the beech wood was 6.72 wt.% and 0.59 wt.% on dry basis (db), respectively, and the potassium content was 0.12 wt.% db³⁰.

2.2 Catalyst preparation and characterization

The catalysts used in the catalytic hydropyrolysis reactor were prepared by sequential incipient wetness impregnation of the MgAl₂O₄ spinel support. The support material was supplied by Haldor Topsøe A/S and a detailed description of the methodology can be found elsewhere¹. After impregnation the samples were calcined at 500°C in air. For the CoMo catalyst doped with potassium, an additional impregnation was performed with K₂CO₃ (Sigma-Aldrich ≥99.0%) and the catalyst was re-calcined at 500°C and sieved. The

composition of the catalysts is shown in Table 1. The catalysts were sulfided in-situ in the setup as described elsewhere¹. In order to ensure that the catalyst remained sulfided during the experiments, H₂S was co-fed to the setup during all catalytic hydropyrolysis experiments.

Table 1 Overview of the tested catalysts

Catalyst	Mo (wt.%)	Co (wt.%)	K (wt.%)	Co/Mo (molar)	K/Mo (molar)	Mo load (Atoms/nm ²)	BET SSA (m ² /g)
CoMo#1	3.41	0.637	-	0.30	-	3.6	60
CoMo#2	3.29	0.615	-	0.30	-	3.8	58
CoMoK#1	3.43	0.603	1.935	0.29	2.67	3.9	55

The HDO reactor was loaded with 173 g NiMo/Al₂O₃ catalyst (shaped as extrudates), supplied by Haldor Topsøe A/S. In the experiment where the HDO reactor was used, the catalysts in the catalytic hydropyrolysis and HDO reactor were sulfided simultaneously, using the same procedure as for the experiments with only the catalytic hydropyrolysis reactor. However, the holding time was increased to 3 hours to ensure that the catalysts in both reactors were in the sulfided phase. After the sulfidation of the NiMo/Al₂O₃ catalyst in the HDO reactor, it was by accident exposed to an air flow for ~5 seconds and the temperature in the bottom of the reactor increased to ~600 °C, indicating oxidation of the catalyst. Therefore the HDO reactor was resulfided for 1 hour at 350 °C. Dabros²⁹ investigated the reactivation of a coked sulfided NiMo catalyst by oxidation and subsequent resulfidation and found that it led to a decrease in the cracking and HDO activity. The change was ascribed to a change in the catalyst morphology and composition; it was observed that the Mo content had decreased. Furthermore, sintering had occurred, which had led to an increased degree of stacking, causing a loss in the number of brim sites²⁹. The catalyst in the HDO reactor had therefore most likely lost some of its activity, prior to the experiment.

The composition, surface area of the calcined oxide catalyst precursors were measured and temperature programmed ammonia desorption (NH₃-TPD) and Raman spectroscopy were also performed. The catalyst characterization methods have previously been described in detail¹.

2.3 Experimental setup and procedure

The Experiments were conducted in a pilot plant shown in Figure 1 which is described in detail elsewhere^{1,30,32}. The fluid bed hydrolysis reactor was operated at 450 °C and 26 bar and the fixed bed HDO reactor was operated at ~370°C, when used.

Figure 1. Simplified overview of the used setup

For the 16.2 h experiment conducted over five days, the setup was depressurized, flushed with N₂ and the remaining biomass (beech wood) in the screw feeder was weighed and replaced with a new batch each day. The filter and tracing was cooled to room temperature, while the reactor temperatures were decreased to 150 °C. The solids in the filter was removed and considered as the solid yield and the condensed liquids were collected. The setup was leak tested and the reaction conditions listed in Table 2 were established. When the temperature in the reactor reached steady state the experiment was started by turning on the screw feeder. The catalyst carryover was estimated by combusting a sample of the solids from the filter at 600 °C and assuming that all ash from the biomass is captured in the filter.

After each complete experiment the catalyst and the remaining char was removed from the fluid bed, and replaced with the fresh catalyst for the subsequent experiment. The total solid yield for experiment 1 (obtained on day 5), experiment 2 and 3 was calculated by subtracting the mass of loaded catalyst from the total mass of solids collected from the filter and fluid bed.

2.4 Liquid phase analysis methods

2.4.1 Organic phase

The condensed organic phase was analyzed with several different methods and a more detailed description can be found elsewhere^{1,30,32}. The following properties of the organic phases were measured: hydrogen content, sulfur content, oxygen content, simulated distillation (SIMDIS), density at 40 °C, viscosity at 40 °C and water content. Furthermore, the organic phases were analyzed by gas chromatography (GC) using an atomic emission detector (AED) in both sulfur and oxygen detection mode, and the organic phases were also analyzed with GC×GC-ToF/MS. The GC×GC-ToF/MS analysis was used to classify the oil phase compounds into the following groups: phenols, dihydroxybenzene, larger oxygenated aromatics, oxygenated aliphatics, sterols, paraffins, naphthenes, mono-, di-, and tri- and higher aromatics.

2.4.2 Aqueous phase

The aqueous phases were analyzed with GC-AED in carbon selective mode and this was used to determine the total carbon content in the aqueous phases. The aqueous phases were also analyzed with GC-MS/FID to determine specific compounds in this phase.. A detailed description of the used equipment and methods can be found elsewhere^{1,32}.

2.5 Char analysis

The elemental composition (CHNSO) of the produced char was analyzed at DB Lab A/S by use of a Flash 2000 elemental analyzer from Thermo Fisher. The total ash and catalyst content in the produced char were measured by combusting the char at 600°C in air. A detailed description of the analysis can be found elsewhere³⁰.

1

2

3

4

5

6

7

8

9

10

11

12

13

14

15

16

17

18

19

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57

58

59

60

164

165

166

167

168

169

170

171

172

173

3

Results and Discussion

165

3.1.1 Characterization of the oxide catalyst precursors

166

3.1.1.1 NH_3 -TPD

The acidity of the fresh oxide precursors was investigated with NH_3 -TPD, see Figure 2. This showed that the number of acidic sites and their acid strength on the fresh CoMo#1 and CoMo#2 were comparable, 0.124-0.149 mmol/g, while the number of acidic sites on the fresh CoMoK#1 catalyst, 0.039-0.043 mmol/g, was significantly lower than for the fresh CoMo#1 and CoMo#2 catalyst, as expected. It is well-known that the Brønsted acidity facilitates the transport of the potassium onto the catalyst and that potassium decreases the number of acidic sites^{36–43}. The observed changes after the addition of K_2CO_3 is therefore in agreement with the literature and potassium is most likely located at the acidic sites.

Figure 2 NH_3 -TPD profiles for the fresh oxide precursors and the K-doped catalyst.

176

3.1.1.2 Raman spectroscopy

To gain insight into the phases of the oxide catalyst precursors, they were analyzed by Raman spectroscopy applying the fluidized bed set-up as described by Beato et al.⁴⁴ (Figure 3). The samples were also analyzed by Raman microscopy at different spatial spots (see supporting information Figure S.1), which evidenced some degree of phase heterogeneity for the individual samples. The bands observed at 407, 678, and 771 cm^{-1} are ascribed to the MgAl_2O_4 spinel carrier⁴⁵. Since a monolayer of Mo on Al_2O_3 would correspond to 4.5 Mo/ nm^2 ⁴⁶, the catalysts have between 80 and 87 % monolayer coverage, which should result in well

dispersed $\text{Co}_x\text{Mo}_y\text{O}_z$ phases. The spectra for CoMo#1 and CoMo#2 are fairly similar, indicating that these two catalysts contain largely the same phases. The main difference between CoMo#1 and CoMo#2 is the presence of a sharp doublet between 940-950 cm^{-1} for CoMo#1, which is characteristic for $\beta\text{-CoMoO}_4$ ⁴⁷. However, both samples show a small band at $\sim 879\text{ cm}^{-1}$ which together with the broad band at $\sim 930\text{ cm}^{-1}$ is typical for the hydrated $\text{CoMoO}_4 \cdot x\text{H}_2\text{O}$ phase⁴⁷. The metal coordination in $\beta\text{-CoMoO}_4$ and $\text{CoMoO}_4 \cdot x\text{H}_2\text{O}$ is very similar, both containing CoO_6 octahedra and MoO_4 tetrahedra⁴⁸. The slight differences in the Raman spectra are therefore most probably related to a different degree of hydration which leads to a slight change in the relative rearrangement of the metal polyhedra⁴⁸. Furthermore, no Co_3O_4 is observed, since the corresponding main Raman band at 692 cm^{-1} is not observed. Also the presence of crystalline $\alpha\text{-MoO}_3$ can be excluded, since the characteristic sharp band at 992 cm^{-1} due to terminal $\text{Mo}=\text{O}$ stretching mode⁴⁶ was not observed. For the CoMoK#1 sample no distinct bands between 200-230 cm^{-1} and 920-960 cm^{-1} are observed. Instead, two sharp bands at 887 and 914 cm^{-1} emerge, which are characteristic for isolated tetrahedral monomolybdate units²⁵. This therefore indicates that doping the catalyst with potassium leads to the formation of more isolated MoO_x species. On the other hand, the additional bands at 821 and 851 cm^{-1} are typical for longer $\text{Mo}-\text{O}$ bonds, which indicates the presence of some connectivity between the polyhedra. It is worth noting that for the CoMoK#1 sample a broad Raman band at around 593 cm^{-1} can be recognized, which has been assigned to supported CoO_x species⁴⁹.

Figure 3 Baseline corrected Raman spectra of CoMo#1, CoMo#2, and CoMoK#1 in the oxide phase (calcined, not dehydrated). The Raman bands were assigned to hydrated MoO_x (gray), hydrated CoMoO₄ (blue), CoO_x (green), and MgAl₂O₄ (yellow).

3.2 Catalyst stability

The process and catalyst stability were evaluated by conducting a 16.2 h experiment over five days with CoMo#2 in the fluid bed reactor and a commercial NiMo/Al₂O₃ catalyst in the HDO reactor. The run time was approximately 3.5 h per day, except for day 3, where the experiment was stopped after 2.2 h due problems with the biomass feeding system. An overview of the test conditions and mass balances is shown in Table 2. The mass balance closed between 100.3 and 103.1 wt.% daf based on the amount of biomass fed. The reason for the mass balance being above 100 % is hydrogen incorporation in the products. It was not possible to determine the char and coke yield each day, because that would require that the fluid bed reactor was unloaded. Instead the filter was unloaded each day and the solid yield in the filter was determined. The catalyst carryover from the fluid bed to the filter was estimated to between 1 and 9 g per day, with a total carryover of 20 g after five days, corresponding to 41 wt.% of the total amount of catalyst loaded in the fluid bed. Experiment 2, shown in Table 2, has previously been published¹ and is reported here as a reference.

Table 2 Test conditions and yields for each day of the 16.2 h experiment (1), a reference experiment (2) and the experiment with the potassium impregnated catalyst (3).

Experiment	1 (day 1)	1 (day 2)	1 (day 3)	1 (day 4)	1 (day 5)	1 (average)	2	3
Conditions								
FB temperature (°C)	453	452	454	455	453	453	451	454
FB catalyst	CoMo#2	CoMo#2	CoMo#2	CoMo#2	CoMo#2	CoMo#2	CoMo#1	CoMoK#1
FB catalyst amount (g)	49.99	-	-	-	-	49.99	50.03	49.98
FB catalyst lost (g)	5	9	3	2	1	4	ND	ND
HDO temperature (°C)	370	370	366	372	373	370	-	-
HDO catalyst	NiMo/Al ₂ O ₃	NiMo/Al ₂ O ₃	NiMo/Al ₂ O ₃	NiMo/Al ₂ O ₃	NiMo/Al ₂ O ₃	NiMo/Al ₂ O ₃	-	-
HDO catalyst amount (g)	173	173	173	173	173	173	-	-
Pressure (bar)	26	26	26	26	26	26	26	26
Feed time (h)	3.5	3.5	2.2	3.5	3.5	3.2	3.5	3.5
Feeding rate (g/h)	274	276	240	274	273	267	275	268
H ₂ S conc.(ppm)	460	460	460	460	460	460	460	460
H ₂ flow (NL/min)	82	82	82	82	82	82	82	82
N ₂ flow (NL/min)	5	5	5	5	5	5	5	5
Yields (wt. daf %)								
Gas	29.4	30.0	29.6	30.7	31.2	30.2	26.1	24.9
Solid	10.9 ^a	13.8 ^a	14.6 ^a	13.2 ^a	13.6 ^b	13.2	13.3 ^b	14.6 ^b
Aqueous phase	38.0	37.1	36.4	34.5	35.1	36.2	33.3	28.9
Organic phase	12.2	13.7	12.5	14.6	14.1	13.4	17.7	19.9
C ₄₊ in the gas	9.9	9.2	8.7	8.3	9.1	9.0	7.5	4.1
Organics + C ₄₊	22.1	22.9	21.2	22.9	23.2	22.5	25.2	24.1
Mass balance	100.3	103.7	101.8	101.2	103.1	102.0	97.8	92.5
Carbon recovery (%)								
C ₁ -C ₃	23	21	21	21	21	21	19	12
C ₄₊	17	15	15	14	15	15	13	7.1
CO+CO ₂	11	12	12	13	13	12	11	13
Solid	15	18	20	19	19	18	ND	ND
Organic phase	20	22	23	24	23	22	26	28
Aqueous phase	0.039	0.052	0.044	0.085	0.17	0.078	3.2	3.2
Organic phase + C ₄₊	36	37	37	39	38	37.4	39	35
Organic phase composition								
Water (wt.%) ^c	ND	ND	ND	ND	ND	ND	3.3	6.3
C ^d (wt.% db)	87.8	87.8	ND	87.9	88.1	87.9	81	77
H (wt.% db)	12.15	12.16	ND	12.06	11.85	12.1	9.39	9.12
O (wt ppm db)	40	162	228	988	2832	850	9.0×10 ⁴	13.8×10 ⁴
S (wt.% db)	0.055	0.015	0.018	0.0083	0.011	0.021	0.22	0.18
Organic phase physical properties								
Density at 40°C (g/ml)	0.827	0.831	0.832	0.835	0.844	0.8338	0.944	0.968
Dynamic viscosity at 40°C (Pa s)	0.894 × 10 ⁻³	ND	ND	ND	1.06 × 10 ⁻³	0.977 × 10 ⁻⁴	ND	ND
TAN (mg _{KOH} /g)	<0.05	<0.05	ND	<0.05	<0.05	<0.05	4.00	14.7
Aqueous phase composition (wt.%)								
C	0.047	0.064	0.055	0.11	0.22	0.099	4.3	4.8
Gas composition (wt.% daf)								
CO	7.6	8.3	8.4	9.1	9.3	8.5	3.5	9.6
CO ₂	8.2	8.1	8.4	8.7	9.2	8.5	9.2	8.6
C ₁ -C ₃	14.4	13.6	13.1	13.3	13.2	13.5	10.3	6.3
C ₄₊	9.9	9.2	8.7	8.4	9.2	9.1	7.5	4.1
Solids in filter composition (wt.%)								
C	72.1	69.2	72.2	73.2	72.9	71.9	ND	ND
H	3.45	3.00	3.22	3.27	3.22	3.23	ND	ND
S	2.20	2.18	2.35	2.33	2.25	2.26	ND	ND
N	0.28	0.26	0.31	0.28	0.26	0.28	ND	ND
O	16.2	15.7	15.0	15.3	15.5	15.5	ND	ND
Ash	10.2	10.8	8.2	6.1	5.3	8.1	ND	ND

^a Solid = Solid in filter

^b Solid = Solid in filter + solid in fluid bed – catalyst loaded

^c assumed below detection limit for all experiments with HDO reactor

^d By difference

3.2.1 Product distribution

The condensable organic yield varied between 21.2 and 23.2 wt.% daf, see Figure 4(A). The lowest yield was obtained after 9.2 hours (3rd day), but this was most likely due to the operational problems described previously. Furthermore, the condensable organics yield (22.1 wt.% daf), especially the condensed organics yield (12.2 wt.% daf), was low after the first day (TOS 3.5 h), however, this was probably due to an initial

wetting of the setup. The total gas yield was fairly constant, see Figure 4(B), but the CO and CO₂ yield increased from 14.9 to 18.2 wt.% daf, while the C₁-C₃ yield decreased from 14.4 to 13.0 wt.% daf. The C₁-C₃ yield was significantly higher when the HDO reactor was used (experiment 1, C₁-C₃ yield: 14.4-13.1 wt.% daf) compared to the experiment without the HDO reactor (experiment 2, C₁-C₃ yield: 10.3 wt.% daf). The reason for the higher C₁-C₃ yield when the HDO reactor was used is probably a combination of cracking of larger molecules and HDO of the C₁-C₃ oxygenates detected in the aqueous phase when the HDO reactor was bypassed, see supporting information Tables S.1-3. In the experiment without the HDO reactor the concentration of olefins in the gas (C₂-C₅) was 6.5 wt.% daf, while using the HDO reactor led to an initial total saturation of the C₂-C₅ hydrocarbons in the gas. However, the concentration of C₂-C₅ olefins increased to 0.06 wt.% daf after 9.1 hours and to 0.3 wt.% daf after 16.2 hours, indicating deactivation of the NiMo/Al₂O₃ catalyst in the HDO reactor. The total CO₂ and CO yield was initially the same with the HDO reactor as in the experiment without the HDO reactor. However, the CO to CO₂ molar ratio increased from 1.1 without the HDO reactor to 1.6 with the HDO reactor, indicating that reverse water gas shift takes place in the HDO reactor. This is opposite to what we previously observed with a commercial CoMo/MgAl₂O₄ catalyst in the fluid bed, where forward water gas shift was observed in the HDO reactor³⁰. The reason for the difference was that the CO/CO₂ ratio was 3.1 when using the commercial CoMo/MgAl₂O₄ catalyst in fluid bed without the HDO reactor³⁰, compared to 1.1 in this study. At equilibrium the CO/CO₂ ratio is 1.6 mol/mol at 370 °C and 3.6 at mol/mol at 450 °C¹, thus the CO/CO₂ ratio approaches equilibrium from either side in the HDO reactor depending on the catalyst in the fluid bed.

The solid yield was between 10.9 and 14.6 wt.% daf, see Figure 4(C). The low solid yield after 3.5 h TOS (day 1) was due to an initial char accumulation in the fluid bed, which therefore decreased the yield of collected solids in the filter. During the rest of the experiment the solid yield was fairly constant and varied from 13.1 to 14.6 wt.% daf, thus the variation in the solid yield was within the experimental error and comparable to the char and coke yield obtained without the HDO reactor, as expected.

As shown in Figure 4(D), the aqueous phase yield decreased from 38.0 to 35.1 wt.% daf during the 5 day experiment. The decrease in the aqueous phase yield is almost equivalent to the increase in the yield of CO and CO₂, hence the decrease in the aqueous phase yield could be due to an increased decarbonylation and/or decarboxylation activity. However it could also be due to decreased hydrodeoxygenation activity in the fluid bed reactor, which increased the life time of the very reactive oxygenates, which led to a higher degree of decarbonylation and/or decarboxylation. The aqueous phase yield without the HDO reactor was only 33.3 wt.% daf, but this difference is because hydrodeoxygenation takes place in the HDO reactor, increasing the amount of water formed.

Figure 4 Effect of time on stream on the condensable organic yield (A), gas yield (B), solid yield (C), and aqueous phase yield (D). Conditions: Catalytic hydrolysis reactor temp.: 452-455 °C, hydrotreating reactor temp.: 366-373 °C, total pressure: 26 bar, beech wood feeding rate: 240-276 g/h, total beech wood used: 4358 g, hydrogen flow: 82 NL/min, nitrogen flow: 5 NL/min, and hydrogen disulfide conc.: 460 ppm.

3.2.2 Chemical composition of the condensed liquids

The oxygen and hydrogen concentrations in the organic phase are shown in Figure 5(A). The oxygen concentration increased during the first 9.1 hours from 40 ppm to 228 ppm, after which the slope increased and the oxygen content in the organic phase increased to 2832 ppm, showing a decrease in the deoxygenation activity in either the fluid bed, HDO or both reactors. The hydrogen concentration also decreased from 12.15 to 11.85 wt.% during the experiment, indicating that the concentration of olefins and/or aromatics in the organic phase increased, corresponding to a decrease in the hydrogenation activity. This correlates with the observed decrease in the hydrogenation from the gas analysis.

Figure 5 Effect of TOS on the oxygen and hydrogen concentration (A) and the density and viscosity (B) of the organic phase. Conditions: Catalytic hydrothermal reactor temp.: 452-455°C, hydrotreating reactor temp.: 366-373 °C, total pressure: 26 bar, beech wood feeding rate: 240-276 g/h, total beech wood used: 4358 g, hydrogen flow: 82 NL/min, nitrogen flow: 5 NL/min, and hydrogen disulfide conc.: 460 ppm.

The density of all the condensed organics was measured, while the viscosity was only measured on the condensed organics from the first and last day, see Figure 5(B). The density at 40°C increased during the experiment from 0.827 to 0.844 g/ml, which is due to the increased oxygen content and decreased hydrogen content in the organic phase. Furthermore, the boiling point of the organic phase also increased, see simulated distillation curves in the supporting information Figure S.2, and the diesel fraction increased from 70 to 80 vol. %, which is probably also part of the reason for the increased density. The increase in the boiling point is most likely due to a decrease in the cracking activity and deoxygenation activity, which agrees with the decrease in the C₁-C₃ yield in the gas. The deactivation also affected the viscosity, which

increased from 0.894×10^{-3} to 1.06×10^{-3} Pa·s. It should be noted that the density of the produced organic phase was within the typical range of density for diesel, which is 0.82-0.85 g/ml, while the viscosity was below the viscosity of diesel, which is between 1.56×10^{-3} to 3.83×10^{-3} Pa·s⁸. The hydrogen content in diesel is typically 13 wt.%⁸, thus further hydrogenation of the produced organics is needed before it can be used as such.

The sulfur content in the condensed oil in the reference experiment (number 2) without the HDO reactor was 0.22 wt.% and using the HDO reactor decreased it to between 0.008 and 0.055 wt.%. Sulfur specific GC-AED showed that the sulfur in the organic phase from the experiment without the HDO reactor consisted of H₂S (382 ppm S), methylethylsulfide (150 ppm S), thiols (55 ppm S), thiophenes (80 ppm S) and benzothiophenes (29 ppm S). Furthermore, the condensed organics from 3.5 h TOS and 16.2 h TOS from the experiment with the HDO reactor were analyzed with GC-AED (see supporting information Table S.4). This indicated that most of the sulfur in the organic phase was H₂S and only 21 ppm and 20 ppm S was ascribed to sulfur containing hydrocarbons after 3.5 and 16.2 h TOS, respectively. All the thiols were removed and the thiophene concentration was 2 ppm S at 3.5 h TOS and was not detected at 16.2 h TOS, and the concentration of dibenzothiophenes was 4 ppm S at 3.5 h TOS, and was not detected at 16.2 h TOS. However, some larger unknown sulfur containing organics (13 ppm S) were detected in the condensed organics from 16.2 h TOS. The reason for the total removal of thiols is probably the low concentration of olefins, which can react with H₂S and form thiols³⁴. The low level of organic sulfur in the organic phase is due the high hydrodesulfurization (HDS) activity of CoMoS and NiMoS catalysts, which are commonly used in modern refineries for HDS^{50,51}. Based on the results from the sulfur specific GC-AED it can be assumed that catalytic hydropyrolysis using sulfided CoMo catalysts followed by HDO can produce liquid fuels with a low S concentration and therefore requires none or little additional hydrotreating in order to obtain an acceptable level of sulfur.

1
2
3
4 303 In order to obtain a deeper understanding of the composition of the condensed organic phase they were
5
6 304 analyzed with GC×GC-ToF/MS or –FID. The concentration of paraffins varied between 2.6 and 3.1 % area-
7
8
9 305 FID and there was no apparent correlation between the TOS and the paraffin concentration. The
10
11 306 concentration of naphthenes (Naph) was between 49.3 and 50.3 % area-FID during the first 12.6 hours,
12
13 307 after which it decreased to 47.3 %, see Figure 6(A). The concentration of monoaromatics (mAro) decreased
14
15 308 from 36.3 to 33.8 %-area FID during the first 7.0 hours, but was constant at 33.8-34.3 % during the rest of
16
17
18 309 the experiment. The decrease in monoaromatics was probably related to the increase from 10.6 to 12.1 %
19
20 310 area-FID in the di-and larger aromatics (diAro+). The oxygenated aliphatics (O-ali) increased during the
21
22 311 experiment from 0.01 to 0.2 % area-FID, shown in Figure 6(B). A small increase from 0.006 to 0.01 % area-
23
24 312 FID in the oxygenated di-and larger aromatics (O-Aro) was also observed, but this is within the uncertainty
25
26
27 313 of the measurement. The concentration of phenols (PhOH) was between 0.9 and 1.1 % area-FID during the
28
29 314 first 9.1 hours, but then increased to 3.0 % after 16.2 hours. The increase in the concentration of phenols
30
31 315 corresponds to the decrease in the naphthenes, which is most likely because the NiMo/Al₂O₃ catalyst in the
32
33 316 fixed bed reactor mainly remove the phenols through the HYD pathway ⁵², hence a deactivation of this
34
35
36 317 catalyst would lead to a decreased concentration of naphthenes. Since a hot gas filter is located between
37
38 318 the fluid bed reactor and fixed bed reactor the deactivation of the NiMo/Al₂O₃ catalyst is most likely due to
39
40 319 coking, which is common in hydrotreating⁸. Furthermore, only traces of oxygenated aliphatics were
41
42 320 detected in the condensed organic phase.
43
44

45 321 The observed increase of the oxygen content in the condensed organic phase was because approximately
46
47 322 40 wt.% of the catalyst in fluid bed was transferred to the filter during the experiment and the catalyst
48
49
50 323 deactivated. We have previously shown that it is possible to obtain an organic phase with less than 0.0018
51
52 324 wt.% db oxygen in the condensed organic phase when using olivine sand, which has no catalytic activity, as
53
54 325 bed material in the fluid bed and a NiMoS catalyst in the HDO reactor³². Therefore it is certain that some
55
56 326 deactivation of the catalyst in the HDO reactor has taken place. The catalyst in the fluid bed reactor
57
58
59 327 operates under more harsh conditions and has also been partly deactivated due to carbon deposition and
60

uptake of potassium as will be discussed in detail in part II of this work. It is possible to regenerate some of the catalyst activity lost due to coking²⁹, while catalyst deactivation due to metals deposited on the catalyst are less reversible⁵³, and thus of greater concern. Furthermore it should be noted that coking mainly takes place in the beginning of the experiment and levels off, while transfer of metals occurs at a more constant rate⁵⁴.

333

Figure 6 Effect of TOS on the organic phase composition. Conditions: Catalytic hydropyrolysis reactor temp.: 452-455°C, hydrotreating reactor temp.: 366-373 °C, total pressure: 26 bar, beech wood feeding rate: 240-276 g/h, total beech wood used: 4358 g, hydrogen flow: 82 NL/min, nitrogen flow: 5 NL/min, and hydrogen disulfide conc.: 460 ppm.

The carbon recovery in the aqueous phase was between 0.039 and 0.17 % and was constant during the first 9.6 hours after which it increased, as shown in Figure 7. However, the carbon recovery in the aqueous phase was still significantly lower than in the experiment without the HDO reactor (3.2 %). GC-MS/FID on the aqueous phase after 16.2 hours, showed that it contained phenol (45 % area-FID), m-cresol (30 % area-FID), o-cresol (5.6 % area-FID), 2-ethyl-phenol (4.6 % area-FID), and 2,5 dimethyl phenol (5.3 % area-FID). Since neither furans, acids, or ketones were detected in the aqueous phase and only a very low concentration of oxygenated aliphatics (≤ 0.2 % area-FID) was detected in the organic phase, the observed catalyst deactivation resulted in mainly phenols not being deoxygenated.

Figure 7 Carbon yield in the aqueous phase as a function of TOS. Conditions: Catalytic hydropyrolysis reactor temp.: 452-455°C, hydrotreating reactor temp.: 366-373 °C, total pressure: 26 bar, beech wood feeding rate: 240-276 g/h, total beech wood used: 4358 g, hydrogen flow: 82 NL/min, nitrogen flow: 5 NL/min, and hydrogen disulfide conc.: 460 ppm.

3.3 Effect of catalyst pre-deactivation with potassium

3.3.1 Product distribution

In our previous work¹ we analyzed several spent catalysts from the fluid bed reactor with SEM-EDS and observed that the potassium content on the spent catalysts was between 0.3 and 2.4 wt.%. Therefore, in order to investigate the effect of the transfer of potassium from the biomass to the catalyst, a CoMo/MgAl₂O₄ catalyst was impregnated with K₂CO₃ corresponding to a potassium content of 1.94 wt.%, which corresponds to the amount of potassium in approximately 1 kg of dry beech wood, 0.99 g potassium, to 50 g of catalyst in the fluid bed. The catalyst was tested without the HDO reactor and the mass balance closed at 92.5 wt.% daf, as shown in Table 2, which is lower than normally achieved. The produced organic phase was sticky and the reason for the low mass balance is probably that part of the organic phase was accumulated in the setup.

The product distribution for the experiment with CoMoK#1 is compared to the reference experiment with CoMo#1 in Figure 8. The char and coke yield increased from 13.4 to 14.6 wt.% daf, when the CoMoK#1 was used, which indicates that potassium can act as a catalyst for polymerization reactions. The reason for this phenomenon is further investigated in part II³⁵. The C₁-C₃ yield decreased from 10.3 to 6.3 wt.% daf, which was mainly due to a decrease in the C₂-C₃ hydrocarbons from 6.8 to 3.1 wt.% daf. This shows that the cracking activity of the catalyst decreased after impregnation with K₂CO₃, which also decreased its acidity (see Figure 2). The C₂-C₃ paraffin to olefin ratio also decreased from 0.90 to 0.50 mol/mol, indicating a lower hydrogenation activity for CoMoK#1. The CO and CO₂ yield increased from 15.8 to 18.6 wt.% when replacing CoMo#1 with CoMoK#1, but the increase was due to an increase in the CO yield, while the CO₂ yield decreased from 9.2 to 8.6 wt.% daf, indicating a higher decarbonylation activity. However, the CO₂ concentration in the gas, which is normally constant, decreased during the experiment with CoMoK#1 from 0.6 to 0.3 mol % (see supplementary information Figure S.3), indicating that deactivation of the catalyst occurred during the experiment. Similarly Pan et al.⁵⁵ observed an increased CO and CO₂ yield when they conducted pyrolysis of potassium impregnated wood. In this work, doping the catalyst with potassium also

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59

led to a significant decrease in the aqueous phase yield, from 33.3 to 28.9 wt.%, which was due to a decreased hydrodeoxygenation activity, which probably led to an increased decarbonylation/decarboxylation activity. The total condensable organic yield was also lower with the CoMoK#1 than CoMo#1, but the reason is most likely that part of the organic phase had accumulated in the setup. The C₄₊ yield was also lower for the CoMoK#1, which was due to the decreased cracking activity.

Figure 8 Product distribution for catalytic hydropyrolysis of beech wood with CoMoK#1 and CoMo#1. Conditions: Catalytic hydropyrolysis reactor temp.: 452-454°C, total pressure: 26 bar, beech wood feeding rate: 261-268 g/h, beech wood used: 941-963 g, hydrogen flow: 82 NL/min, nitrogen flow: 5 NL/min, and hydrogen disulfide conc.: 460 ppm.

3.3.2 Chemical composition of the condensed liquids

The oxygen content in the condensed organic phase from the experiment with CoMoK#1 was 13.8 wt.% db while it was 9.0 wt.% db with CoMo#1, showing that the deoxygenation activity for CoMoK#1 is significantly lower than the deoxygenation activity of CoMo#1. Similarly, the TAN was 4.0 mg_{KOH}/g for CoMo#1, but 14.7 for CoMoK#1 mg_{KOH}/g, indicating that the potassium decreases the catalysts ability to remove carboxylic acids, which are well-known coke precursors²⁹. The hydrogen content decreased from 9.39 to 9.11 wt.% db when CoMoK#1 was used instead of CoMo#1, which indicates a decrease in the hydrogenation activity. This therefore shows that potassium decreases the catalyst deoxygenation and hydrogenation activity. Furthermore, the sulfur concentration in the condensed organic phase was 0.22 wt.% db when CoMo#1 was used and 0.18 wt.% db when CoMoK#1 was used. The condensed organic phase was also analyzed with sulfur specific GC-AED and the concentration of the different sulfur containing compounds are shown in

Figure 9 and a detailed list of the detected molecules can be found in supplementary information Tables S.5 and S.6. This showed that the thiol concentration was 41 ppm S, the thiophene concentration was 54 ppm S, and the benzothiophene concentration was 16 ppm when CoMoK#1 was used. The concentration of thiols was 55 ppm S, thiophenes 80 ppm S, and benzothiophenes 29 ppm S when CoMo#1 was used. The concentration of other types of sulfur containing molecules, such as methyl ethyl sulfide, and unidentified sulfur containing molecules was significantly higher for CoMo#1 (659 wt-ppm S) than CoMoK#1 (267 wt-ppm S). This indicates that using CoMoK#1 instead of CoMo#1 in the fluid bed decreased the sulfur content in the organic phase. This is most likely not due to a higher hydrodesulfurization (HDS) activity for CoMoK#1 compared to CoMo#1, but rather lower sulfur incorporation into the organics. Sulfur incorporation reactions are typically acid catalyzed⁵⁶ and since the addition of potassium decreased the number of acidic sites on the catalyst, it is very likely that the lower sulfur content in organic phase from the experiment with CoMoK#1 compared to CoMo#1 is due to lower sulfur incorporation.

Figure 9 Concentration of sulfur species in the condensed organic phase from the experiment with CoMo#1 and CoMoK#1 determined with S specific GC-AED. Conditions: Catalytic hydrothermal reactor temp.: 452-454°C, total pressure: 26 bar, beech wood feeding rate: 261-268 g/h, beech wood used: 941-963 g, hydrogen flow: 82 NL/min, nitrogen flow: 5 NL/min, and hydrogen disulfide conc.: 460 ppm.

Mortensen et al.³⁴ investigated the effect of potassium on a sulfided NiMo HDO catalyst by pre-impregnating it with KNO₃ and using phenol as a model compound. They found that potassium decreased the catalyst's deoxygenation activity with 80 %, hence they observed a larger effect of potassium in their

study compared to this. The larger decrease in the deoxygenation activity that Mortensen et al.³⁴ observed could be because NiMoS removes the oxygen by first saturating the aromatic ring and then removes the oxygen (the hydrogenation pathway)^{52,57}, while CoMoS removes the oxygen without saturating the aromatic ring (direct deoxygenation pathway)^{26,52,58,59}. Potassium should therefore have a larger impact on the deoxygenation activity for NiMoS than CoMoS. Another important difference is that Mortensen et al.³⁴ conducted their experiment at 280 °C, thus the temperature was 170 °C lower compared to this study. The results therefore also indicate that the effect of potassium decreases with increasing temperature.

GC×GC-FID/MS chromatograms of the condensed organics from the experiment with CoMo#1 and CoMoK#1 are shown in Figure 10. As indicated by the chromatograms, the organic phase from these two experiments were quite different and the chromatogram for CoMoK#1 contained more peaks than that for CoMo#1. An overlap between the aromatics and oxygenates in the chromatogram for CoMoK#1 was observed, making it difficult to analyze and compare with the chromatogram for CoMo#1. The condensed organic phase from both experiments consisted of paraffins, naphthenes, mono-, di-, tri-, and larger aromatics, oxygenated aliphatics, phenols, dihydroxybenzenes, and sterols (only traces). However, a significantly higher concentration of oxygenated aliphatics (including carboxylic acids) was observed for CoMoK#1 (Figure 10(C)) compared to CoMo#1 (Figure 10(A)), which is in accordance with the higher TAN number for CoMoK#1 compared to CoMo#1. It should also be noted that more furans are observed in Figure 10(C) compared to Figure 10(A), indicating that the CoMoK#1 is less active towards these otherwise reactive oxygenates. The concentration of phenols and dihydroxybenzenes were also significantly higher when CoMoK#1 was used compared to CoMo#1. The concentration of phenols was 44 % area-FID and the concentration of dihydroxybenzenes was 12 % area-FID for CoMoK#1, while the concentration of phenols was 40 % area-FID and the concentration of dihydroxybenzenes was 2.4 % area-FID for CoMo#1. This therefore shows that potassium decreases the catalyst's ability to deoxygenate the rather stable phenols. The increased concentration of dihydroxybenzenes, furans, and acids could make the condensed organic phase more reactive.

Interestingly, dimethyl dihydroxybenzene was the main dihydroxybenzene when CoMo#1 was used, while methyl dihydroxybenzene was the main dihydroxybenzene when CoMoK#1 was used. Likewise, methylpyrene was observed with CoMo#1 while pyrene was observed with CoMoK#1. Therefore, the difference in peak intensity could indicate that doping the catalyst with potassium decreases the alkylation activity, which is most likely due to the decreased acidity.

Figure 10 Composition (A) and chromatogram (B) of the condensed organic phase from the experiment with CoMo#1 (experiment 2), and composition (C) and chromatogram (D) of the condensed organic phase from the experiment with CoMoK#1 (experiment 3). The components in the condensed organics is divided into paraffins (Par), naphthenes (Naph), monoaromatics (mAro), diaromatics (diAro), triaromatics (triAro), tetraaromatics and larger aromatics (tetAro+), oxygenated aliphatics (O-ali), phenols (PhOH), dihydroxybenzenes (Ph(OH)₂), and larger oxygenated aromatics (O-aro). Conditions: Catalytic hydrolysis temp.: 452-454°C, total pressure: 26 bar, beech wood feeding rate: 261-268 g/h, beech wood used: 941-963 g, hydrogen flow: 82 NL/min, nitrogen flow: 5 NL/min, and hydrogen disulfide conc.: 460 ppm.

The compositions of the aqueous phases are shown in Figure 11. The carbon concentration in the aqueous phase was 4.3 and 4.8 wt.% when CoMo#1 and CoMoK#1 were used, respectively, however the carbon recovery was 2.6 % in the aqueous phase for both catalysts. This was due to the lower aqueous phase yield,

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

but higher carbon concentration in the aqueous phase when the CoMoK#1 was used. A significant increase in the concentration of furans and ketones were observed, while the concentration of alcohols and phenols decreased when the catalyst was impregnated with K_2CO_3 . Sugars were also observed in the aqueous phase when the CoMoK#1 was used, which is another indication of the lower degree of hydrogenation of the pyrolysis vapors.

Figure 11 Composition of the aqueous phase when the CoMo#1 and CoMoK#1 is used in the fluid bed reactor. Conditions: Catalytic hydrolysis reactor temp.: 452-454°C, total pressure: 26 bar, beech wood feeding rate: 261-268 g/h, beech wood used: 941-963 g, hydrogen flow: 82 NL/min, nitrogen flow: 5 NL/min, and hydrogen disulfide conc.: 460 ppm.

4 Conclusion

The catalyst stability in catalytic hydrolysis of wood was investigated by running a fluid bed hydrolysis setup for 16.2 hours over a period of 5 days (2.2-3.5 hours each day) with a sulfided CoMo catalyst followed by a deep HDO reactor with a sulfided NiMo catalyst. The condensed organics and C_{4+} yield was 22.2 ± 1 wt.% daf, the aqueous phase yield decreased during the experiment from 38.0 to 35.1 wt.% daf, while the CO and CO_2 yield increased from 14.9 to 18.2 wt.%. The decrease in aqueous phase yield was ascribed to a decreasing hydrodeoxygenation activity, which led to an increasing degree of decarbonylation/decarboxylation. The oxygen content in the produced organic phase increased during the experiment from 40 to 2832 wt. ppm, indicating that deactivation of the catalysts had occurred.

Adding 1.9 wt.% potassium in the form of K_2CO_3 to the catalyst prior to sulfidation significantly decreased the catalyst's acidity, which decreased its cracking activity because potassium binds to the acid sites. A significant decrease in the deoxygenation activity was also observed, as the oxygen content in the organic phase increased from 9.0 to 13.8 wt.% db. However, adding potassium increased the $CO+CO_2$ yield from 15.8 wt.% daf for a potassium free catalyst to 18.6 wt.% daf after potassium addition. This was most likely due to a decrease in the catalysts hydrodeoxygenation activity, which increased the life time of very reactive oxygenates that led to a higher degree of decarbonylation/decarboxylation. The results indicate that the increased CO and CO_2 yield observed during the 5 day test of the catalyst stability could be due to transfer of potassium from the biomass to the catalyst. Furthermore, the hydrogen content in condensed organic phase decreased from 9.39 to 9.12 wt.% and the C_2 - C_3 paraffin to olefin ratio decreased from 0.90 to 0.50 mol/mol, indicating a decrease in the hydrogenation activity. The solid yield (coke+char) also increased when the potassium doped catalyst was used, indicating that the potassium catalyzes polymerization reactions. This phenomenon is further investigated in part II³⁵.

Overall, this work shows that catalytic hydrothermal pyrolysis is a promising process but more research into the deactivation of the catalysts is needed. In this work the deactivation was followed over 16 hours, but significantly longer experiments are needed to unravel the effect of deactivation on the process. Furthermore the effect of other alkaline metals such calcium needs to be studied.

5 Acknowledgments

This work is part of the H2CAP project (Hydrogen assisted catalytic pyrolysis for green fuels) conducted at The Department of Chemical and Biochemical Engineering at DTU, Denmark. The work was supported by The Danish Council for Strategic Research (now Innovation Fund Denmark, project 1377-00025A), The Programme Commission on Sustainable Energy and Environment. Funding from DTU is also gratefully acknowledged. The authors also acknowledge Aino Nielsen (Haldor Topsøe A/S) for technical assistance with the Raman spectroscopy, Søren Birk Rasmussen for assistance with NH_3 -TPD, the Inorganic Analysis

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Department at Haldor Topsøe A/S for technical assistance with the elemental analysis, and the Organic Analysis Department at Haldor Topsøe A/S for analysis of the organic phase.

6 References

- (1) Stummann, M. Z.; Hansen, A. B.; Hansen, L. P.; Davidsen, B.; Rasmussen, S. B.; Wiwel, P.; Gabrielsen, J.; Jensen, P. A.; Jensen, A. D.; Høj, M. Catalytic Hydropyrolysis of Biomass Using Molybdenum Sulfide Based Catalyst. Effect of Promoters. *Energy & Fuels* **2019**, *33* (2), 1302–1313. <https://doi.org/10.1021/acs.energyfuels.8b04191>.
- (2) Independent Statistics & Analysis - U.S. Energy Information Administration. *International Energy Outlook 2016 - DOE/EIA-0484*; 2016.
- (3) IPCC - Intergovernmental Panel on Climate Change. Global Warming of 1.5°C an IPCC Special Report on the Impacts of Global Warming of 1.5 °C above Pre-Industrial Levels and Related Global Greenhouse Gas Emission Pathways, in the Context of Strengthening the Global Response to the Threat of Climate Change,. **2018**, No. October.
- (4) Bridgwater, A. V. Review of Fast Pyrolysis of Biomass and Product Upgrading. *Biomass and Bioenergy* **2012**, *38*, 68–94. <https://doi.org/10.1016/j.biombioe.2011.01.048>.
- (5) Venderbosch, R. H.; Prins, W. Fast Pyrolysis Technology Development. *Biofuels, Bioprod. Biorefining* **2010**, *4* (2), 178–208. <https://doi.org/10.1002/bbb.205>.
- (6) Trinh, T. N.; Jensen, P. A.; Dam-Johansen, K.; Knudsen, N. O.; Sørensen, H. R.; Hvilsted, S. Comparison of Lignin, Macroalgae, Wood, and Straw Fast Pyrolysis. *Energy & Fuels* **2013**, *27* (3), 1399–1409. <https://doi.org/10.1021/ef301927y>.
- (7) Mortensen, P. M.; Grunwaldt, J.-D.; Jensen, P. A.; Knudsen, K. G.; Jensen, A. D. A Review of Catalytic Upgrading of Bio-Oil to Engine Fuels. *Appl. Catal. A Gen.* **2011**, *407* (1–2), 1–19.

<https://doi.org/10.1016/j.apcata.2011.08.046>.

(8) Dabros, T. M. H.; Stummann, M. Z.; Høj, M.; Jensen, P. A.; Grunwaldt, J.-D.; Gabrielsen, J.; Mortensen, P. M.; Jensen, A. D. Transportation Fuels from Biomass Fast Pyrolysis, Catalytic Hydrodeoxygenation, and Catalytic Fast Hydropyrolysis. *Prog. Energy Combust. Sci.* **2018**, *68*, 268–309. <https://doi.org/10.1016/j.pecs.2018.05.002>.

(9) Marker, T. L.; Felix, L. G.; Linck, M. B.; Roberts, M. J. Integrated Hydropyrolysis and Hydroconversion (IH²) for the Direct Production of Gasoline and Diesel Fuels or Blending Components from Biomass, Part 1: Proof of Principle Testing. *Environ. Prog. Sustain. Energy* **2012**, *31* (2), 191–199. <https://doi.org/10.1002/ep.10629>.

(10) Marker, T. L.; Felix, L. G.; Linck, M. B.; Roberts, M. J.; Ortiz-Toral, P.; Wangerow, J. Integrated Hydropyrolysis and Hydroconversion (IH²) for the Direct Production of Gasoline and Diesel Fuels or Blending Components from Biomass, Part 2: Continuous Testing. *Environ. Prog. Sustain. Energy* **2014**, *33* (3), 762–768. <https://doi.org/10.1002/ep.11906>.

(11) Maleche, E.; Glaser, R.; Marker, T.; Shonnard, D. A Preliminary Life Cycle Assessment of Biofuels Produced by the IH²™ Process. *Environ. Prog. Sustain. Energy* **2014**, *33* (1), 322–329. <https://doi.org/10.1002/ep.11773>.

(12) Fan, J.; Gephart, J.; Marker, T.; Stover, D.; Updike, B.; Shonnard, D. R. Carbon Footprint Analysis of Gasoline and Diesel from Forest Residues and Corn Stover Using Integrated Hydropyrolysis and Hydroconversion. *ACS Sustain. Chem. Eng.* **2016**, *4* (1), 284–290. <https://doi.org/10.1021/acssuschemeng.5b01173>.

(13) Dayton, D. C.; Carpenter, J.; Farmer, J.; Turk, B.; Gupta, R. Biomass Hydropyrolysis in a Pressurized Fluidized Bed Reactor. *Energy & Fuels* **2013**, *27* (7), 3778–3785. <https://doi.org/10.1021/ef400355t>.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

- (14) Dayton, D. C.; Hlebak, J.; Carpenter, J. R.; Wang, K.; Mante, O. D.; Peters, J. E. Biomass Hydropyrolysis in a Fluidized Bed Reactor. *Energy & Fuels* **2016**, *30* (6), 4879–4887. <https://doi.org/10.1021/acs.energyfuels.6b00373>.
- (15) Wang, K.; Dayton, D. C.; Peters, J. E.; Mante, O. D. Reactive Catalytic Fast Pyrolysis of Biomass to Produce High-Quality Bio-Crude. *Green Chem.* **2017**, *19* (14), 3243–3251. <https://doi.org/10.1039/C7GC01088E>.
- (16) Gamliel, D. P.; Wilcox, L.; Valla, J. A. The Effects of Catalyst Properties on the Conversion of Biomass via Catalytic Fast Hydropyrolysis. *Energy & Fuels* **2017**, *31* (1), 679–687. <https://doi.org/10.1021/acs.energyfuels.6b02781>.
- (17) Gamliel, D. P.; Bollas, G. M.; Valla, J. A. Bifunctional Ni-ZSM-5 Catalysts for the Pyrolysis and Hydropyrolysis of Biomass. *Energy Technol.* **2017**, *5* (1), 172–182. <https://doi.org/10.1002/ente.201600136>.
- (18) Gamliel, D. P.; Bollas, G. M.; Valla, J. A. Two-Stage Catalytic Fast Hydropyrolysis of Biomass for the Production of Drop-in Biofuel. *Fuel* **2018**, *216* (December 2017), 160–170. <https://doi.org/10.1016/j.fuel.2017.12.017>.
- (19) Chandler, D. S.; Resende, F. L. P. Comparison between Catalytic Fast Pyrolysis and Catalytic Fast Hydropyrolysis for the Production of Liquid Fuels in a Fluidized Bed Reactor. *Energy and Fuels* **2019**, *33* (4), 3199–3209. <https://doi.org/10.1021/acs.energyfuels.8b03782>.
- (20) Şenol, O. İ.; Ryymin, E.-M.; Viljava, T.-R.; Krause, A. O. I. Reactions of Methyl Heptanoate Hydrodeoxygenation on Sulphided Catalysts. *J. Mol. Catal. A Chem.* **2007**, *268* (1–2), 1–8. <https://doi.org/10.1016/j.molcata.2006.12.006>.
- (21) Şenol, O. İ.; Viljava, T.-R.; Krause, A. O. I. Hydrodeoxygenation of Aliphatic Esters on Sulphided

- NiMo/ γ -Al₂O₃ and CoMo/ γ -Al₂O₃ Catalyst: The Effect of Water. *Catal. Today* **2005**, *106*, 186–189.
<https://doi.org/10.1016/j.cattod.2005.07.129>.
- (22) Şenol, O. İ.; Viljava, T.-R.; Krause, A. O. I. Effect of Sulphiding Agents on the Hydrodeoxygenation of Aliphatic Esters on Sulphided Catalysts. *Appl. Catal. A Gen.* **2007**, *326* (2), 236–244.
<https://doi.org/10.1016/j.apcata.2007.04.022>.
- (23) Ryymin, E.-M.; Honkela, M. L.; Viljava, T.-R.; Krause, A. O. I. Competitive Reactions and Mechanisms in the Simultaneous HDO of Phenol and Methyl Heptanoate over Sulphided NiMo/ γ -Al₂O₃. *Appl. Catal. A Gen.* **2010**, *389* (1–2), 114–121. <https://doi.org/10.1016/j.apcata.2010.09.010>.
- (24) Gutierrez, A.; Turpeinen, E.-M.; Viljava, T.-R.; Krause, O. Hydrodeoxygenation of Model Compounds on Sulfided CoMo/ γ -Al₂O₃ and NiMo/ γ -Al₂O₃ Catalysts; Role of Sulfur-Containing Groups in Reaction Networks. *Catal. Today* **2017**, *285*, 125–134. <https://doi.org/10.1016/j.cattod.2017.02.003>.
- (25) Dabros, T. M. H.; Gaur, A.; Pintos, D. G.; Sprenger, P.; Høj, M.; Hansen, T. W.; Studt, F.; Gabrielsen, J.; Grunwaldt, J.-D.; Jensen, A. D. Influence of H₂O and H₂S on the Composition, Activity, and Stability of Sulfided Mo, CoMo, and NiMo Supported on MgAl₂O₄ for Hydrodeoxygenation of Ethylene Glycol. *Appl. Catal. A Gen.* **2018**, *551* (October 2017), 106–121.
<https://doi.org/10.1016/j.apcata.2017.12.008>.
- (26) Bui, V. N.; Laurenti, D.; Afanasiev, P.; Geantet, C. Hydrodeoxygenation of Guaiacol with CoMo Catalysts. Part I: Promoting Effect of Cobalt on HDO Selectivity and Activity. *Appl. Catal. B Environ.* **2011**, *101* (3–4), 239–245. <https://doi.org/10.1016/j.apcatb.2010.10.025>.
- (27) Centeno, A.; Laurent, E.; Delmon, B. Influence of the Support of CoMo Sulfide Catalysts and of the Addition of Potassium and Platinum on the Catalytic Performances for the Hydrodeoxygenation of Carbonyl, Carboxyl, and Guaiacol-Type Molecules. *J. Catal.* **1995**, *154* (2), 288–298.
<https://doi.org/10.1006/jcat.1995.1170>.

- 1
2
3
4 585 (28) Badawi, M.; Paul, J.-F.; Cristol, S.; Payen, E. Guaiacol Derivatives and Inhibiting Species Adsorption
5
6 586 over MoS₂ and CoMoS Catalysts under HDO Conditions: A DFT Study. *Catal. Commun.* **2011**, *12* (10),
7
8 587 901–905. <https://doi.org/10.1016/j.catcom.2011.02.010>.
9
10
11
12 588 (29) Dabros, T. M. H.; Andersen, M. L.; Lindahl, S. B.; Hansen, T. W.; Høj, M.; Gabrielsen, J.; Grunwaldt, J.;
13
14 589 Jensen, A. D. Hydrodeoxygenation (HDO) of Aliphatic Oxygenates and Phenol over NiMo/MgAl₂O₄:
15
16 590 Reactivity, Inhibition, and Catalyst Reactivation. *Catalysts* **2019**, *9* (6), 521.
17
18 591 <https://doi.org/10.3390/catal9060521>.
19
20
21
22 592 (30) Stummann, M. Z.; Høj, M.; Schandel, C. B.; Hansen, A. B.; Wiwel, P.; Gabrielsen, J.; Jensen, P. A.;
23
24 593 Jensen, A. D. Hydrogen Assisted Catalytic Biomass Pyrolysis. Effect of Temperature and Pressure.
25
26 594 *Biomass and Bioenergy* **2018**, *115* (March), 97–107.
27
28 595 <https://doi.org/10.1016/j.biombioe.2018.04.012>.
29
30
31
32 596 (31) Stummann, M. Z.; Høj, M.; Hansen, A. B.; Davidsen, B.; Wiwel, P.; Gabrielsen, J.; Jensen, P. A.;
33
34 597 Jensen, A. D. New Insights into the Effect of Pressure on Catalytic Hydropyrolysis of Biomass. *Fuel*
35
36 598 *Process. Technol.* **2019**, *193* (January), 392–403. <https://doi.org/10.1016/j.fuproc.2019.05.037>.
37
38
39 599 (32) Stummann, M. Z.; Høj, M.; Davidsen, B.; Hansen, A. B.; Hansen, L. P.; Wiwel, P.; Schandel, C. B.;
40
41 600 Gabrielsen, J.; Jensen, P. A.; Jensen, A. D. Effect of the Catalyst in Fluid Bed Catalytic Hydropyrolysis.
42
43 601 *Catal. Today* **2019**. <https://doi.org/10.1016/j.cattod.2019.01.047>.
44
45
46 602 (33) Mortensen, P. M.; Gardini, D.; de Carvalho, H. W. P.; Damsgaard, C. D.; Grunwaldt, J.-D.; Jensen, P.
47
48 603 A.; Wagner, J. B.; Jensen, A. D. Stability and Resistance of Nickel Catalysts for Hydrodeoxygenation:
49
50 604 Carbon Deposition and Effects of Sulfur, Potassium, and Chlorine in the Feed. *Catal. Sci. Technol.*
51
52 605 **2014**, *4* (10), 3672–3686. <https://doi.org/10.1039/c4cy00522h>.
53
54
55
56 606 (34) Mortensen, P. M.; Gardini, D.; Damsgaard, C. D.; Grunwaldt, J.-D.; Jensen, P. A.; Wagner, J. B.;
57
58 607 Jensen, A. D. Deactivation of Ni-MoS₂ by Bio-Oil Impurities during Hydrodeoxygenation of Phenol
59
60

- and Octanol. *Appl. Catal. A Gen.* **2016**, 523, 159–170. <https://doi.org/10.1016/j.apcata.2016.06.002>.
- (35) Stummann, M. Z.; Høj, M.; Bente, D.; Hansen, L. P.; Beato, P.; Gabrielsen, J.; Jensen, P. A.; Jensen, A. D. Deactivation of a CoMo Catalyst during Catalytic Hydropyrolysis of Biomass. Part II: Characterization of the Spent Catalysts and Char. *Submitted* **2019**.
- (36) Olsen, B. K.; Kügler, F.; Castellino, F.; Jensen, A. D. Poisoning of Vanadia Based SCR Catalysts by Potassium: Influence of Catalyst Composition and Potassium Mobility. *Catal. Sci. Technol.* **2016**, 6 (7), 2249–2260. <https://doi.org/10.1039/c5cy01409c>.
- (37) Zheng, Y.; Jensen, A. D.; Johnsson, J. E. Laboratory Investigation of Selective Catalytic Reduction Catalysts: Deactivation by Potassium Compounds and Catalyst Regeneration. *Ind. Eng. Chem. Res.* **2004**, 43 (4), 941–947. <https://doi.org/10.1021/ie030404a>.
- (38) Zheng, Y.; Jensen, A. D.; Johnsson, J. E.; Thøgersen, J. R. Deactivation of V2O5-WO3-TiO2SCR Catalyst at Biomass Fired Power Plants: Elucidation of Mechanisms by Lab- and Pilot-Scale Experiments. *Appl. Catal. B Environ.* **2008**, 83 (3–4), 186–194. <https://doi.org/10.1016/j.apcatb.2008.02.019>.
- (39) Chen, J. P.; Yang, R. T. Mechanism of Poisoning of the V2O5 / TiO2 Catalyst for the Reduction of NO by NH3. *J. Catal.* **1990**, 125 (2), 411–420. [https://doi.org/10.1016/0021-9517\(90\)90314-A](https://doi.org/10.1016/0021-9517(90)90314-A).
- (40) Nicosia, D.; Elsener, M.; Kröcher, O.; Jansohn, P. Basic Investigation of the Chemical Deactivation of V2O5/WO3-TiO2 SCR Catalysts by Potassium, Calcium, and Phosphate. *Top. Catal.* **2007**, 42–43 (1–4), 333–336. <https://doi.org/10.1007/s11244-007-0200-4>.
- (41) Klimczak, M.; Kern, P.; Heinzelmann, T.; Lucas, M.; Claus, P. High-Throughput Study of the Effects of Inorganic Additives and Poisons on NH3-SCR Catalysts-Part I: V2O5-WO3/TiO2 Catalysts. *Appl. Catal. B Environ.* **2010**, 95 (1–2), 39–47. <https://doi.org/10.1016/j.apcatb.2009.12.007>.
- (42) Fan, Y.; Lu, J.; Shi, G.; Liu, H.; Bao, X. Effect of Synergism between Potassium and Phosphorus on

- 1
2
3
4 630 Selective Hydrodesulfurization Performance of Co-Mo/Al₂O₃FCC Gasoline Hydro-Upgrading
5
6 631 Catalyst. *Catal. Today* **2007**, 125 (3–4), 220–228. <https://doi.org/10.1016/j.cattod.2007.02.022>.
7
8
9
10 632 (43) Mey, D.; Brunet, S.; Canaff, C.; Maugé, F.; Bouchy, C.; Diehl, F. HDS of a Model FCC Gasoline over a
11
12 633 Sulfided CoMo/Al₂O₃catalyst: Effect of the Addition of Potassium. *J. Catal.* **2004**, 227 (2), 436–447.
13
14 634 <https://doi.org/10.1016/j.jcat.2004.07.013>.
15
16
17 635 (44) Beato, P.; Schachtl, E.; Barbera, K.; Bonino, F.; Bordiga, S. Operando Raman Spectroscopy Applying
18
19 636 Novel Fluidized Bed Micro-Reactor Technology. *Catal. Today* **2013**, 205, 128–133.
20
21
22 637 <https://doi.org/10.1016/j.cattod.2012.09.030>.
23
24
25 638 (45) D'Ippolito, V.; Andreozzi, G. B.; Bersani, D.; Lottici, P. P. Raman Fingerprint of Chromate, Aluminate
26
27 639 and Ferrite Spinel. *J. Raman Spectrosc.* **2015**, 46 (12), 1255–1264. <https://doi.org/10.1002/jrs.4764>.
28
29
30 640 (46) Hu, H.; Wachs, I. E. Surface Structures of Supported Molybdenum Oxide Catalysts. Characterization
31
32 641 by Raman and Mo L₃-Edge XANES. *J. Phys. Chem.* **1995**, 99 (27), 10897–10910.
33
34 642 <https://doi.org/10.1021/j100027a034>.
35
36
37 643 (47) Payen, E.; Dhamelinourt, M. C.; Dhamelinourt, P.; Grimblot, J.; Bonnelle, J. P. Study of Co(or Ni)-
38
39
40 644 Mo Oxide Phase Transformation and Hydrodesulfurization Catalysts by Raman Microprobe Equipped
41
42 645 with New Cells. *Appl. Spectrosc.* **1982**, 36 (1), 30–37. <https://doi.org/10.1366/0003702824638953>.
43
44
45 646 (48) Eda, K.; Uno, Y.; Nagai, N.; Sotani, N.; Whittingham, M. S. Crystal Structure of Cobalt Molybdate
46
47 647 Hydrate CoMoO₄·NH₂O. *J. Solid State Chem.* **2005**, 178 (9), 2791–2797.
48
49
50 648 <https://doi.org/10.1016/j.jssc.2005.06.014>.
51
52
53 649 (49) Vuurman, M. A.; Stufkens, D. J.; Oskam, A.; Deo, G.; Wachs, I. E. Combined Raman and IR Study of
54
55 650 MO_x-V₂O₅/Al₂O₃(MO_x= MoO₃, WO₃, NiO, CoO) Catalysts under Dehydrated Conditions. *J. Chem.*
56
57 651 *Soc. - Faraday Trans.* **1996**, 92 (17), 3259–3265. <https://doi.org/10.1039/FT9969203259>.
58
59
60

- (50) Topsøe, H.; Clausen, B. S.; Massoth, F. E. *Catalysis - Science and Technology. Hydrotreating Catalysis*, Volume 11.; Springer-Verlag: Berlin Heidelberg, Germany, 1996.
- (51) Stanislaus, A.; Marafi, A.; Rana, M. S. Recent Advances in the Science and Technology of Ultra Low Sulfur Diesel (ULSD) Production. *Catal. Today* **2010**, *153* (1–2), 1–68.
<https://doi.org/10.1016/j.cattod.2010.05.011>.
- (52) Bouvier, C.; Romero, Y.; Richard, F.; Brunet, S. Effect of H₂S and CO on the Transformation of 2-Ethylphenol as a Model Compound of Bio-Crude over Sulfided Mo-Based Catalysts: Propositions of Promoted Active Sites for Deoxygenation Pathways Based on an Experimental Study. *Green Chem.* **2011**, *13* (9), 2441–2451. <https://doi.org/10.1039/c1gc15181a>.
- (53) Furimsky, E.; Massoth, F. E. Deactivation of Hydroprocessing Catalysts. *Catal. Today* **1999**, *52* (4), 381–495. [https://doi.org/10.1016/S0920-5861\(99\)00096-6](https://doi.org/10.1016/S0920-5861(99)00096-6).
- (54) Fonseca, A.; Zeuthen, P.; Nagy, J. B. ¹³C n.m.r. Quantitative Analysis of Catalyst Carbon Deposits. *Fuel* **1996**, *75* (12), 1363–1376.
- (55) Pan, W. P.; Richards, G. N. Influence of Metal Ions on Volatile Products of Pyrolysis of Wood. *J. Anal. Appl. Pyrolysis* **1989**, *16* (2), 117–126. [https://doi.org/10.1016/0165-2370\(89\)85011-9](https://doi.org/10.1016/0165-2370(89)85011-9).
- (56) Leflaive, P.; Lemberon, J. L.; Pérot, G.; Mirgain, C.; Carriat, J. Y.; Colin, J. M. On the Origin of Sulfur Impurities in Fluid Catalytic Cracking Gasoline - Reactivity of Thiophene Derivatives and of Their Possible Precursors under FCC Conditions. *Appl. Catal. A Gen.* **2002**, *227* (1–2), 201–215.
[https://doi.org/10.1016/S0926-860X\(01\)00936-X](https://doi.org/10.1016/S0926-860X(01)00936-X).
- (57) Schachtl, E.; Yoo, J. S.; Gutiérrez, O. Y.; Studt, F.; Lercher, J. A. Impact of Ni Promotion on the Hydrogenation Pathways of Phenanthrene on MoS₂/γ-Al₂O₃. *J. Catal.* **2017**, *352*, 171–181.
<https://doi.org/10.1016/j.jcat.2017.05.003>.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

674 (58) Bui, V. N.; Laurenti, D.; Delichère, P.; Geantet, C. Hydrodeoxygenation of Guaiacol. Part II: Support
675 Effect for CoMoS Catalysts on HDO Activity and Selectivity. *Appl. Catal. B Environ.* **2011**, *101* (3–4),
676 246–255. <https://doi.org/10.1016/j.apcatb.2010.10.031>.
677 (59) Gonçalves, V. O. O.; Brunet, S.; Richard, F. Hydrodeoxygenation of Cresols over Mo/Al₂O₃ and
678 CoMo/Al₂O₃ Sulfided Catalysts. *Catal. Letters* **2016**, *146* (8), 1562–1573.
679 <https://doi.org/10.1007/s10562-016-1787-5>.

680

1
2
3
4
5
6
7
8

Pressurized
biomass
feeding

ACS Paragon Plus Environment

Page 38 of 38

Low deactivation

Stable oil yield