Air void analysis of hardened concrete without colour enhancement

Li, Gui; Hasholt, M.T.; Jensen, O.M.

Published in:
Concrete Durability and Service Life Planning

Link to article, DOI:
[10.1007/978-3-030-43332-1_16](https://doi.org/10.1007/978-3-030-43332-1_16)

Publication date:
2020

Document Version
Peer reviewed version

[Link back to DTU Orbit](#)

Citation (APA):
Li, G., Hasholt, M. T., & Jensen, O. M. (2020). Air void analysis of hardened concrete without colour enhancement. In *Concrete Durability and Service Life Planning: Proceedings of ConcreteLife'20* (Vol. 26, pp. 79-83). Springer. RILEM Bookseries https://doi.org/10.1007/978-3-030-43332-1_16

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Metadata of the chapter that will be visualized in SpringerLink

Book Title	Concrete Durability and Service Life Planning	
Series Title		
Chapter Title	Air Void Analysis of Hardened Concrete Without Colour Enhancement	
Copyright Year	2020	
Copyright HolderName	RILEM	
Corresponding Author	Family Name	Li
	Particle	
	Given Name	Gui
	Prefix	
	Suffix	
	Role	
	Division	Department of Civil Engineering
	Organization	Technical University of Denmark
	Address	Lyngby, Denmark
	Email	guili@byg.dtu.dk
Author	Family Name	Hasholt
	Particle	
	Given Name	M. T.
	Prefix	
	Suffix	
	Role	
	Division	Department of Civil Engineering
	Organization	Technical University of Denmark
	Address	Lyngby, Denmark
	Email	
Author	Family Name	Jensen
	Particle	
	Given Name	O. M.
	Prefix	
	Suffix	
	Role	
	Division	Department of Civil Engineering
	Organization	Technical University of Denmark
	Address	Lyngby, Denmark
	Email	
Abstract	Air void structure plays a key role in the durability of concrete structures in cold regions. This is because water in the microstructure can escape into the air voids which, thereby, effectively reduce the stresses during cyclic freezing and thawing. This protects the concrete structures from developing frost damage [1, 2]. Therefore, to assure the frost resistance of conventional concrete, it is necessary to quantify its air void structure.	
Keywords	Air void analysis - Hardened concrete - Optical microscopy - Shape From Focus (SFF) - Focused image

Air Void Analysis of Hardened Concrete Without Colour Enhancement

Gui Li^(✉), M. T. Hasholt, and O. M. Jensen

Department of Civil Engineering,
Technical University of Denmark, Lyngby, Denmark
guili@byg.dtu.dk

Keywords: Air void analysis · Hardened concrete · Optical microscopy · Shape From Focus (SFF) · Focused image

1 Introduction

Air void structure plays a key role in the durability of concrete structures in cold regions. This is because water in the microstructure can escape into the air voids which, thereby, effectively reduce the stresses during cyclic freezing and thawing. This protects the concrete structures from developing frost damage [1, 2]. Therefore, to assure the frost resistance of conventional concrete, it is necessary to quantify its air void structure.

AQ1

The most widely used methods for measuring the air void parameters in hardened concrete are the microscopy-based methods described in ASTM C457/457M-16 [3]. The linear-traverse method determines the air void parameters by analysing the data that include the number of air voids traversed by a set of regularly spaced lines and the distances traversed through paste and air voids along these lines. The modified point-count method counts the number of air voids traversed through the lines as well, but instead of summing the traverse distances, a grid of points is used to record the frequency of locations in paste and air voids. Both methods can be conducted manually, but this is time-consuming, tedious and expensive. In addition, the results can be influenced by operator judgment. To address these drawbacks, the contrast-enhanced methods can be used to identify the air voids by image analysis. Then colour enhancement needs to be done before the microscopy analysis. This also needs significant efforts for sample preparation. Furthermore, the quality of surface treatment can influence the accuracy of test results [4].

In the 1990s, Nayar [5] developed a shape from focus method to analyse the texture of different objects that have a rough surface. An optical microscope is used to get a sequence of images with different focus planes. Then the focused image and 3D texture of the object surface can be reconstructed and the depth map can be computed. In the present study, the shape from focus method is used to obtain the focused image and the depth information of the concrete surface. This enables automatic identification of the air void structure in hardened concrete, without pre-treatment like colour enhancement.

2 The Principle of a New Test Method: Shape from Focus (SFF)

Before introducing the principle of the shape from focus method (SFF), the image formation process should be kept in mind. As shown in Fig. 1, when the light rays radiated by a point pass through the lens, they are refracted and converged at a single point. For a thin lens, the relationship between the focal length of the lens f , the distance from the point to the lens plane o , and the distance from the image plane to the lens plane i , follow the Gaussian lens law [5]:

$$\frac{1}{o} + \frac{1}{i} = \frac{1}{f} \quad (1)$$

Fig. 1. Principle of the image formation and the shape from focus method. (Note: The microscope can be moved from top to bottom as well.)

Therefore, for an optical microscope system, when the configuration of the lens plane and the image plane is fixed, the only focal plane is defined, see Fig. 1. It means that only the surface points that lie on the focal plane (like S_A) will be perfectly focused on the image plane. Other points located outside the focal plane (like S_B and S_C) will form defocused or blurred areas on the image plane (S_B'' and S_C'').

Based on this, when an object with a rough surface is placed on a fixed stage, moving the focal plane away from the stage by moving the microscope allows getting the focused image of each point located in different positions, as presented in Fig. 1. For each point on the object surface, it is possible to determine its degree of focus in different image frames by using a focus measure operator and then record the displacement of the microscope at the position of maximum focus. After that, the height of the point with respect to the stage d can be calculated by Eq. (2):

$$d = d_f + (n - 1)\Delta d \quad (2)$$

Where d_f is the distance between the initial position of the focal plane ($n = 1$) and the fixed stage, which can be measured directly, n is the number of steps, and Δd is the displacement of the microscope at each step. This procedure allows determining of the height of all points with respect to the stage independently to get the focused image and the depth map of the entire surface. And it can also be used to calculate the distance between all points and other planes such as the lens plane.

3 Materials and Methods

3.1 Sample Preparation

A concrete sample was prepared using Portland cement CEM I 52.5 N, sea sand, and crushed granite (4–16 mm). Instead of traditional air entraining agents, suspension polymerized superabsorbent polymers (SAP) was used to create the air void structure in the hardened concrete. The total w/c was 0.52, and the SAP dosage was 0.4% relative to the mass of cement. The SAP absorption capacity was 17 g/g. The percentage by volume of sand and coarse aggregate was approx. 23% and 35%, respectively. The sample was cast in a cylindrical mould ($\varnothing$ 150 mm $\times$ 300 mm) and demoulded after 24 h. Then the sample was cured in a polythene bag at 20 ± 1 °C 14 days after mixing, a 20 ± 1 mm thick specimen was cut from the cylinder perpendicular to the end surfaces. Finally, the surface of the specimen was ground with successively finer silicon carbide abrasive papers (grit sizes corresponding to 75, 35, 17.5 and 12.5 μ m).

3.2 Image Acquisition and Preliminary Analysis

A Nikon SMZ25 stereo microscope equipped with NIS-Elements software was used. The specimen was placed on the fixed microscope stage and adjusted, so the test surface was horizontal. The magnification was $70\times$ (obtained by an objective lens with the magnification of $2\times$ and azoom of $35\times$). After setting the displacement of the microscope ($\Delta d = 10$ μ m) and the number of steps ($n = 51$), the program digitized and stored images at each position.

The NIS-Elements software was used to obtain the preliminary results, see Fig. 2. The software module is based on the so-called extended depth of focus method (EDF), instead of the shape from focus method. The principle of EDF is different from that of SFF, but both methods can be used to obtain the focused image and the depth

information of the object surface [6]. As shown in Fig. 2 left, it is impossible, without colour enhancement, to distinguish air voids from aggregates by using traditional threshold segmentation methods directly. However, due to the difference of depth between air voids and the rest of the test surface, air voids can be identified from the depth map presented in Fig. 2 centre via a threshold segmentation method, see Fig. 2 right. Thus, preliminary results illustrate that it is generally possible to distinguish air voids from aggregates based on the depth information. However, some air voids are not detected, and this is the topic for further investigations.

Fig. 2. Images obtained by the NIS-Elements software in the microscope system. Left: focused image; centre: depth map; right: binary image.

3.3 Upcoming Work

In the near future, the SSF method will be used to process and analyse microscope images. After image acquisition, a modified Laplacian focus measure operator is used to determine the degree of focus of each pixel [5]. Based on this, the image frame with the maximum sharpness measure at each pixel is determined. After that, the focused image and depth map of the concrete surface can be obtained to enable analysis of the air void structure of hardened concrete.

To test the accuracy and robustness of the SFF method, a comparison between the results obtained by the SFF method and that of the modified point-count method will be performed. A study will also be conducted on influencing factors including the brightness and resolution of images, the number and magnitude of the displacement steps, the smoothness of the specimen surface, etc.

Acknowledgement. The authors would like to thank China Scholarship Council and Technical University of Denmark for funding this research project. Shengying Zhao, guest PhD student at Technical University of Denmark, provided the polished specimen, and this is also acknowledged.

References

1. Powers, T.C.: The air requirement of frost resistant concrete. *Proc. Highw. Res. Board* **29**, 184–221 (1949)
2. Pigeon, M., Pleau, R.: *Durability of Concrete in Cold Climates*. CRC Press, Boca Raton (1995). Spon

3. ASTM C457/C457M-16: Standard Test Method for Microscopical Determination of Parameters of the Air-Void System in Hardened Concrete. ASTM International, West Conshohocken, PA (2016)
4. Pleau, R., Michel, P., Jean, L.L.: Some findings on the usefulness of image analysis for determining the characteristics of the air-void system on hardened concrete. *Cem. Concr. Compos.* **23**(2–3), 237–246 (2001)
5. Nayar, S.K.: Shape from focus system. In: IEEE Computer Society Conference on Computer Vision and Pattern Recognition (1992)
6. Zalevsky, Z.: Extended depth of focus imaging: a review. *SPIE Rev.* **1**(1), 018001 (2010)

Author Query Form

Book ID : **496482_1_En**

Chapter No : **16**

Please ensure you fill out your response to the queries raised below and return this form along with your corrections.

Dear Author,

During the process of typesetting your chapter, the following queries have arisen. Please check your typeset proof carefully against the queries listed below and mark the necessary changes either directly on the proof/online grid or in the ‘Author’s response’ area provided below

Query Refs.	Details Required	Author’s Response
AQ1	Please confirm if the corresponding author is correctly identified. Amend if necessary.	

MARKED PROOF

Please correct and return this set

Please use the proof correction marks shown below for all alterations and corrections. If you wish to return your proof by fax you should ensure that all amendments are written clearly in dark ink and are made well within the page margins.

<i>Instruction to printer</i>	<i>Textual mark</i>	<i>Marginal mark</i>
Leave unchanged	... under matter to remain	Ⓟ
Insert in text the matter indicated in the margin	⧵	New matter followed by ⧵ or ⧵ [Ⓢ]
Delete	/ through single character, rule or underline or ⎓ through all characters to be deleted	⧻ or ⧻ [Ⓢ]
Substitute character or substitute part of one or more word(s)	/ through letter or ⎓ through characters	new character / or new characters /
Change to italics	— under matter to be changed	↵
Change to capitals	≡ under matter to be changed	≡
Change to small capitals	≡ under matter to be changed	≡
Change to bold type	~ under matter to be changed	~
Change to bold italic	≈ under matter to be changed	≈
Change to lower case	Encircle matter to be changed	≡
Change italic to upright type	(As above)	⧻
Change bold to non-bold type	(As above)	⧻
Insert 'superior' character	/ through character or ⧵ where required	Y or Y under character e.g. Y or Y
Insert 'inferior' character	(As above)	⧵ over character e.g. ⧵
Insert full stop	(As above)	⊙
Insert comma	(As above)	,
Insert single quotation marks	(As above)	Y or Y and/or Y or Y
Insert double quotation marks	(As above)	Y or Y and/or Y or Y
Insert hyphen	(As above)	⎓
Start new paragraph	⌞	⌞
No new paragraph	⌞	⌞
Transpose	⌞	⌞
Close up	linking ○ characters	○
Insert or substitute space between characters or words	/ through character or ⧵ where required	Y
Reduce space between characters or words		↑