Raman Spectroscopy Evidence of 1:1:1 Complex Formation during Dissolution of WO₃ in a Melt of K₂S₂O₇: K₂SO₄

Berg, Rolf W.; Ferré, Irene Maijó; Schäffer, Susan Jeanne Cline

Published in:
Vibrational Spectroscopy

Link to article, DOI:
[10.1016/j.vibspec.2006.05.021](https://doi.org/10.1016/j.vibspec.2006.05.021)

Publication date:
2006

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Berg, R. W., Ferré, I. M., & Schäffer, S. J. C. (2006). Raman Spectroscopy Evidence of 1:1:1 Complex Formation during Dissolution of WO₃ in a Melt of K₂S₂O₇: K₂SO₄. *Vibrational Spectroscopy*, 42(2), 346–352. <https://doi.org/10.1016/j.vibspec.2006.05.021>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Raman spectroscopy evidence of 1:1:1 complex formation during dissolution of WO_3 in a melt of $\text{K}_2\text{S}_2\text{O}_7\text{:K}_2\text{SO}_4$

Rolf W. Berg^{a,*}, Irene Maijó Ferré^{a,b}, Susan J. Cline Schäffer^a

^a Department of Chemistry, The Technical University of Denmark, Kemitorvet, Building 207, DK-2800 Lyngby, Denmark

^b Facultat de Química, University of Rovira i Virgili, Tarragona 43007, Spain

Available online 21 June 2006

Abstract

Highly inert yellow solid WO_3 was found to be soluble in considerable amounts in molten $\text{K}_2\text{S}_2\text{O}_7$ at elevated temperatures ($\sim 650^\circ\text{C}$), if only similar molar amounts of sulfates were also present. The dissolution reaction of WO_3 into a melt consisting of a 1:1 molar mixture of $\text{K}_2\text{S}_2\text{O}_7$ and K_2SO_4 was studied in detail, and Raman spectroscopy was used to characterize the products. In combination with single crystal X-ray crystal structure determination, it was shown that a new dimeric compound, $\text{K}_8[\{\text{W}^{\text{VI}}\text{O}_2(\text{SO}_4)_2\}_2(\mu\text{-SO}_4)_2]$, was formed and its assigned Raman spectrum at room temperature is given. The WO_2^{2+} cores of the dimeric complex have their symmetrical and antisymmetrical stretching modes $\nu_1(\text{WO}_2^{2+})$ and $\nu_3(\text{WO}_2^{2+})$ at around 1054 (strong) and 1042 (weak), and the bending mode $\nu_2(\text{WO}_2^{2+})$ at around 292 (medium intensity), respectively (positions given in cm^{-1}).

© 2006 Elsevier B.V. All rights reserved.

Keywords: Assignment; Dissolution; K_2SO_4 ; $\text{K}_2\text{S}_2\text{O}_7$; $\text{K}_8[\{\text{W}^{\text{VI}}\text{O}_2(\text{SO}_4)_2\}_2(\mu\text{-SO}_4)_2]$; Melt; Raman; Solid; Spectroscopy; Tungsten oxide; WO_3

1. Introduction

Previously we have studied the dissolution properties of a number of oxide salts in disulfate (pyrosulfate) salt melts. In one case, Nb_2O_5 was found to dissolve in considerable amounts into molten $\text{K}_2\text{S}_2\text{O}_7$ at about 450°C [1,2]. The stoichiometric properties of this and similar reactions were studied by Raman spectroscopy [3] and X-ray single crystal diffraction [4]. Other oxide salts, e.g. ZnO [5] and MoO_3 [6], were recently found to dissolve into $\text{Na}_2\text{S}_2\text{O}_7$ and $\text{K}_2\text{S}_2\text{O}_7$, and references to more systems are described there.

In this communication, we report results on tungsten oxide, WO_3 . This oxide is known as a highly inert yellow solid compound that is practically insoluble in acids. This insolubility, combined with other properties, makes tungsten oxide itself and mixtures with other metal oxides commonly used catalysts or supported catalyst surfaces, see e.g. [7].

Recently we confirmed that WO_3 is sparingly soluble in acidic melts of $\text{K}_2\text{S}_2\text{O}_7$, but, surprisingly, we also discovered

[8] that considerable amounts of WO_3 did dissolve in into melts of $\text{K}_2\text{S}_2\text{O}_7$ at elevated temperatures ($\sim 650^\circ\text{C}$) if similar amounts of sulfates (or possibly potassium oxide and SO_3) were also present. The purpose of the present project, therefore, was to use Raman spectroscopy to characterize the products formed by mixing WO_3 , K_2SO_4 and $\text{K}_2\text{S}_2\text{O}_7$ in varying molar amounts in sealed ampoules, and then to study the range of stability of the products.

In the following, we will interpret the Raman spectra of the molten solutions to show that a 1:1:1 reaction:

took place, and that $[\text{WO}_2]^{2+}$ ions solvated by SO_4^{2-} ions are formed. The stoichiometry of the reaction was determined by isolating crystals and examining them by single crystal X-ray diffraction; the results were confirmed by Raman spectroscopy.

2. Experimental

2.1. Samples

The hygroscopic $\text{K}_2\text{S}_2\text{O}_7$ [7790-62-7] was synthesized from dried $\text{K}_2\text{S}_2\text{O}_8$ salt [7727-21-1] (Merck, pro analysi > 99%) by thermal decomposition at 250°C for 1 h under a dry nitrogen

* Corresponding author. Fax: +45 4525 2412.

E-mail addresses: rwb@kemi.dtu.dk (R.W. Berg), irene.maijo@estudiants.urv.es (I.M. Ferré), ss@kemi.dtu.dk (S.J.C. Schäffer).

Table 1
Relative molar compositions studied by Raman spectroscopy

WO ₃ (mol%)	K ₂ SO ₄ (mol%)	K ₂ S ₂ O ₇ (mol%)
0.0	0.0	100.0
3.0	3.0	94.0
7.0	7.0	86.0
10.0	10.0	80.0
13.0	13.0	74.0
17.0	17.0	66.0
18.0	18.0	64.0
19.0	19.0	62.0
21.0	21.0	58.0
27.0	27.0	46.0
29.0	29.0	42.0
33.0	33.0	34.0

atmosphere [9]. The anhydrous product was immediately transferred to an air-filled dry box (the hygroscopic K₂S₂O₇ requires handling in a dry box to avoid that it picks up water) [9]. In the box weighed amounts of WO₃ (tungsten (VI) oxide [1314-35-8], Merck, reinst > 99%) and K₂SO₄ ([7778-80-5], Merck, suprapur > 99.999%), were mixed with K₂S₂O₇ in varying molar amounts. The mixtures were introduced into cylindrical quartz ampoules that were subsequently removed from the dry box and immediately sealed under vacuum. The relative molar compositions are given in Table 1. A composition triangle diagram is shown in Fig. 1. The ampoules were heated for a few hours in a rocking furnace at ~650 °C, a temperature high enough for liquids to form (the m.p. of K₂S₂O₇ is 419 °C [10]). The appearance of three samples after reaction is shown in Fig. 2.

2.2. Raman equipment

Raman spectra were obtained by use of a DILOR-XY 800 mm focal-length multi-channel spectrometer with macro- and micro-entrances (see Fig. 3). Excitation was done with filtered Ar⁺-ion laser light (wavelength 514.5 nm, power

Fig. 1. Ternary composition diagram. Molar percentages of the two reactants (WO₃ and K₂SO₄) are given along the axes as denoted. The solid circle in the middle corresponds to the dimeric compound K₈[{W^{VI}O₂(SO₄)₂]₂(μ-SO₄)₂].

Fig. 2. Three samples (frozen melts) in ampoules at 25 °C are shown; at the top: 3% WO₃ + 3% K₂SO₄; in the middle: 17% + 17%; at the bottom: 29% WO₃ + 29% K₂SO₄ (in K₂S₂O₇ on mole basis).

~400 mW continuously, vertical polarization obtained by suitable rotation of the half-wave plate). The horizontal macro-entrance was used for the melts, and crystals were measured under the microscope. Filtration of Rayleigh scattering was done with a Kaiser holographic SuperNotch-Plus[®] filter or near the laser line with the double pre-monochromator. Depending on the selected grating, the Raman spectral resolution was within 2–8 cm^{−1}. The light was detected with a liquid N₂-cooled CCD detector (140 K) connected to a MS Windows-98 computer with the Horiba-JobinYvon LAB-SPEC[®] software. A sheet polarization analyzer, permitting vertically (V) or horizontally (H) polarized light to pass, was used to obtain VV- and VH-polarized spectra of liquids. Calibration was done with cyclohexane and sulfur lines to a precision of 1 cm^{−1} [11].

2.3. Heating

Sample temperature control was achieved by means of a homemade four-window electric furnace with PID regulation, based on C/A thermocouple control, or for the case of crystals under the microscope, by a LINKAM HFS91/TP93 cryostat/furnace stage. The temperature was determined with a Pt 100 Ω resistor (±5 °C).

3. Results and discussion

By inspection through the furnace windows, it was found that WO₃ dissolved (reacted) in considerable amounts in molten K₂S₂O₇ + K₂SO₄ mixtures to form viscous yellowish melts, especially at high temperatures. When samples were cooled slowly, the melts froze to microcrystalline lumps (for low WO₃ contents) and clear glasses (for higher WO₃ contents) (see Fig. 2, bottom).

Equimolar amounts of K₂S₂O₇, K₂SO₄ and WO₃ gave clear homogeneous glass masses of gross formulae K₄(WO₂)(SO₄)₃. No chemical analysis was made, since the compositions were already known and the melts were homogeneous. No attack on the quartz wall was seen even after prolonged heating.

Crystals were grown by quenching the melts, partly remelting them and then cooling at a rate of 6 °C per hour, allowing for better crystallization. The ampoules were studied directly or, for crystallographic examination, broken and the

Fig. 3. Schematics of the Raman DILOR-XY spectrometer. M, mirror; $\lambda/2$, half-wave plate; IF, interference filter; L, lens; NF, notch filter; P, polarizer; G, grating. The furnace was mounted on a XYZ-table (not shown), allowing the melts to be placed at the sample position to the right.

Fig. 4. Plot of the $[\{W^{VI}O_2(SO_4)_2\}_2(\mu-SO_4)_2]^{8-}$ anion, showing 50% probability ellipsoids. The eight K^+ ions have been omitted for clarity.

colorless crystals taken out at ambient temperature. They proved to be quite stable in ordinary air. Single crystals of a compound, made from $1WO_3:1K_2S_2O_7:1K_2SO_4$, have recently been obtained, and the X-ray structures of a couple of crystals solved [8] to show that the dimeric compound, $K_8[\{W^{VI}O_2(SO_4)_2\}_2(\mu-SO_4)_2]$, is formed. The structure is shown in Fig. 4. The compound crystallizes in the monoclinic space group $P2_1/n$ with two dimeric units in the unit cell of dimensions $a = 9.4362 \text{ \AA}$, $b = 13.9625 \text{ \AA}$, $c = 10.1948 \text{ \AA}$, and $\beta = 90.780^\circ$ [8].

The $(\mu-SO_4)_2$ way of linking of two MO_2^{2+} centers (see Fig. 4, M = metal) has previously been found for molybdenum, where polymeric strands occurred by repetition of the linking in the $K_2MoO_2(SO_4)_2$ structure [6]. Here in the Mo-containing melts, bands assignable to $\nu_1(C_{2v})$ in bridging sulfato groups were seen at 958 cm^{-1} [6]. The W(VI) coordination sphere [8] shown in Fig. 4 is generated by inversion symmetry from the independent $[W(VI)O_2(SO_4)_3]^{4+}$ moiety, resulting in two bridging sulfato ligands.

During this work, by varying the composition of the melt (Table 1) and isolating crystals, it was shown that the dimeric

compound $K_8[\{W^{VI}O_2(SO_4)_2\}_2(\mu-SO_4)_2]$ exists from at least 5 to 29 mol% (see Fig. 1). Melting of the $K_8[\{W^{VI}O_2(SO_4)_2\}_2(\mu-SO_4)_2]$ crystals started at about 600°C (visual observation).

3.1. Vibrational spectra

Raman spectra of melts at $\sim 650^\circ\text{C}$ and frozen solutions at $\sim 25^\circ\text{C}$ are shown in Figs. 5–8 (X = formal mole fraction of WO_3 and K_2SO_4 in the WO_3 – K_2SO_4 – $K_2S_2O_7$ system, see Table 1).

The spectra of melts of different compositions (see Fig. 5) showed that the characteristic bands of $K_2S_2O_7$ gradually disappeared when the tungsten oxide content was increased. At the same time, new bands appeared monotonically, indicating that a reaction has occurred. More precisely, it was seen that the most characteristic 1086 cm^{-1} band of $K_2S_2O_7$ disappeared and the new 1045 cm^{-1} band of the mixture (the new compound)

Fig. 5. Raman spectra of melts of different compositions (X = formal mole fraction of WO_3 and $K_2S_2O_7$ in the WO_3 – K_2SO_4 – $K_2S_2O_7$ system) at $\sim 650^\circ\text{C}$ (spectra shifted in y-axis for clarity).

Fig. 6. Polarized Raman spectra of the melt of composition $X = 0.27$ (X = formal mole fraction of WO_3 and $K_2S_2O_7$ in the WO_3 – K_2SO_4 – $K_2S_2O_7$ system) at $\sim 650^\circ\text{C}$. WO_2^{2+} and SO_4^{2-} stretches and WO_2^{2+} bending can be assigned to bands at ~ 1100 , ~ 900 and $\sim 390 \text{ cm}^{-1}$. Other assignments are presented in Table 2. Spectra have been shifted in y-axis for clarity.

Table 2

Observed Raman bands at ~ 600 °C (in cm^{-1}) and tentative assignments to fundamental group vibrations^a

$\text{K}_2\text{S}_2\text{O}_7$ melt saturated with K_2SO_4 at 500 °C (Fig. 7)	Complex in melt at 650 °C (Figs. 6 and 7)	$\text{K}_2\text{S}_2\text{O}_7$ crystal at 25 °C (Fig. 7)	Complex in frozen glass at 25 °C (Fig. 7)	$\text{K}_8\text{W}_2\text{S}_6\text{O}_{28}$ crystal at 25 °C (Fig. 8)	Tentative assignment
~ 1304 w, br, dp		1281 m		1264 s	Asymmetric S–O stretches in SO_4^{2-} and $\text{S}_2\text{O}_7^{2-}$ like $\nu_3(\text{SO}_4^{2-})$ stretches
~ 1253 w, br, dp	~ 1240 w, br	1274 m 1257 m 1231 w	1256 w, br	1255 s, m 1239 w 1224 w 1211 w 1185 s 1175 s	
~ 1137 vw				1170 sh	
~ 1085 vs, p	~ 1086 s, p	1098 vs 1092 w, sh 1046 vw 983 vw	1170 w, br 1092 vs	1090 w, p	$\nu(\text{S}_2\text{O}_7^{2-})$ symmetric stretching
~ 1045 s, p	~ 1045 s, p		1057 s	1054 s 1042 w 1025 s	$\nu_1(\text{WO}_2^{2+})$ symmetric stretching $\nu_3(\text{WO}_2^{2+})$ asymmetric stretching $\nu_1(\text{WO}_2^{2+})$ symmetric stretching
			980 vw, br	983 m	Coordinated SO_4^{2-} : bridging $\nu_1(\text{C}_{2v})$ at ~ 950 °C and terminal $\nu_1(\text{C}_{3v})$ at ~ 925 °C
	~ 958 s, br, p ~ 928 s, br, p ~ 900 m, br, dp		940 s, br 905 m, br	947 s 927 w 911 w, sh 904 s 849 w 838 w	
~ 775 w, br, dp ~ 730 m, p	~ 727 m, p ~ 660 m, p ~ 590 w, dp	765 w 746 s	740 m	740 vw 675 w, sh 667 m 607 m, sh 649 w	$\text{K}_2\text{S}_2\text{O}_7$ – SO_4^{2-} bending $\nu_4(\text{SO}_4^{2-})$ bending in complex
		653 w	655 vw		$\text{K}_2\text{S}_2\text{O}_7$ and complex SO_4^{2-} and $\text{S}_2\text{O}_7^{2-}$ bending
~ 599 w, dp		600 m 585 w	600 m 565 w	600 m 590 w	
~ 560 w, dp ~ 508 w, p	~ 558 w, br, p ~ 506 w, dp	561 w 517 m	554 w 512 m	504 w 481 vw 460 w 455 w 446 w 435 w	Complex $\text{K}_2\text{S}_2\text{O}_7$
~ 450 vw		455 vw		385 m 325 vw, br 292 m 274 w 260 m 227 w	Complex $\nu(\text{S}_2\text{O}_7^{2-})$ bending $\nu_2(\text{WO}_2^{2+})$ bending
~ 320 m, dp	~ 368 w, dp ~ 313 s, p ~ 278 m, br, dp	326 m	387 w 324 m 287 w, br 261 w, br	274 w 260 m 227 w 207 vw, br 180 w, br 139 w, br 92 w, br	Lattice
191 w, p					

^a Intensity codes: w, weak; m, medium; s, strong; sh, shoulder; v, very; br, broad; p, polarized; dp, depolarized.

These values refer to matrix isolated WO_2 molecules at low temperatures (in neon and argon gas matrix 4 and 20 K) and have been obtained from analysis of electronic transition spectra with long vibrational progressions [14]. Vibrations in different WO_3 polymorphous phases occur in the same range [15].

Hence, WO_2^{2+} stretches and bendings should occur at about ~ 1100 , ~ 900 and ~ 390 cm^{-1} . For the melts, we observed

(Table 2) the appearance of two of these bands, $\nu_1 = 1045$ and $\nu_2 = 368$ cm^{-1} , ν_3 being probably weak and broad. The higher values observed here relative to the WO_2 at low temperature are due to the hexavalent state of W in the $[\text{WO}_2]^{2+}$ ion and to the high temperature.

This means, taking into consideration the low symmetry and the bonding between the WO_2^{2+} and SO_4^{2-} units in the dimeric

$[\{W^{VI}O_2(SO_4)_2\}_2(\mu-SO_4)_2]^{8-}$, that excessive mixing of group vibrations must occur. The assignments presented in Table 2 are therefore only tentative approximations.

In Fig. 8 we present Raman spectra of four $K_8[\{W^{VI}O_2(-SO_4)_2\}_2(\mu-SO_4)_2]$ crystals, recorded while still inside the ampoule. The crystals were grown and decanted from a melt at $\sim 600^\circ\text{C}$ of composition $X = 0.27$ (X = formal mole fraction of WO_3 in the WO_3 – K_2SO_4 – $K_2S_2O_7$ system).

Again stretching vibrations from WO_2^{2+} and SO_4^{2-} are assigned to bands between ~ 1100 and $\sim 900\text{ cm}^{-1}$. We clearly see increasing bands that we assign to coordinated sulfate: bridging $\nu_1(C_{2v})$ at $\sim 950\text{ cm}^{-1}$ and terminal $\nu_1(C_{3v})$ at $\sim 925\text{ cm}^{-1}$. WO_2^{2+} bendings can be assigned to the bands in the range from ~ 200 to $\sim 400\text{ cm}^{-1}$, as presented in Table 2.

The narrow lines seen below 150 cm^{-1} are rotational bands from the air surrounding the ampoule. Bands likely to be (at least partly) due to traces of the frozen $K_2S_2O_7$ solvent are indicated with asterisks in Fig. 8.

4. Conclusion

By means of Raman spectroscopy and X-rays work [8], it has been possible to determine and confirm the stoichiometry of the reaction as 1:1:1. We have only indication of formation of one kind of complex, the dimeric $K_8[\{W^{VI}O_2(SO_4)_2\}_2(\mu-SO_4)_2]$ with two bridging sulfate ligands and four terminally bound sulfato groups. The complex seems to be very stable and exists as the only compound formed in the molten and solid state. It seems reasonable to describe the system in terms of the formation of rather free bent $[WO_2]^{2+}$ ions of C_{2v} point group symmetry with fundamentals at around: $\nu_1 = 1045$, $\nu_2 = 278\text{ cm}^{-1}$, and with ν_3 being weak and broad at the high temperature. In the dimeric $[\{W^{VI}O_2(SO_4)_2\}_2(\mu-SO_4)_2]^{8-}$ complexes, excessive mixing of these $[WO_2]^{2+}$ -group vibrations with modes in coordinated bridging and terminal sulfate $\{\nu_1(C_{2v})$ at $\sim 950\text{ cm}^{-1}$ and $\nu_1(C_{3v})$ at $\sim 925\text{ cm}^{-1}\}$ must occur so the assignments presented are only tentative approximations.

Acknowledgments

The authors acknowledge Bodil Holten and Lise Lotte Berring of the Technical University of Denmark for preparative and crystallographic help. I.M. Ferré thanks the Erasmus Program of the European Union for a studentship making the visit to Denmark possible.

References

- [1] S. Boghosian, F. Borup, R.W. Berg, Stoichiometry, vibrational modes and structure of molten Nb_2O_5 – $K_2S_2O_7$ mixtures, in: Proceedings of the 11th International Symposium on Molten Salts, The Electrochemical Society, Pennington, NJ, November, (1998), pp. 536–543.
- [2] A. Paulsen, F. Borup, R.W. Berg, S. Boghosian, Spectroscopic study of niobium oxosulfato complexes in the Nb_2O_5 – $K_2S_2O_7$ – K_2SO_4 system at 450 – 700°C . Determination of complex stoichiometry by Raman spectroscopy, in: R.W. Berg, H.A. Hjuler (Eds.), Progress in Molten Salts Chemistry, vol. 1, Elsevier, 2000, pp. 393–397.
- [3] S. Boghosian, R.W. Berg, Determination of stoichiometry of solutes in molten salt solvents by correlations of relative Raman band intensities, Appl. Spectrosc. 53 (1999) 565–571.
- [4] F. Borup, R.W. Berg, K. Nielsen, The crystal structure of $K_7Nb(SO_4)_6$ and $K_7Ta(SO_4)_6$, Acta Chem. Scand. 44 (1990) 328–331.
- [5] R.W. Berg, N. Thorup, The reaction between ZnO and molten $Na_2S_2O_7$ or $K_2S_2O_7$ forming $Na_2Zn(SO_4)_2$ or $K_2Zn(SO_4)_2$, studied by Raman spectroscopy and X-ray diffraction, Inorg. Chem. 44 (2005) 3485–3493.
- [6] T. Nørbygaard, R.W. Berg, K. Nielsen, Reaction between MoO_3 and molten $K_2S_2O_7$, forming $K_2MoO_2(SO_4)_2$, studied by Raman and IR spectroscopy and X-ray crystal structure determination, in: Proceedings of the 11th International Symposium on Molten Salts, The Electrochemical Society, Pennington, NJ, November, (1998), pp. 553–573.
- [7] G. Mestl, In situ Raman spectroscopy for the characterization of MoVW mixed oxide catalysts, J. Raman Spectrosc. 33 (2002) 333–347.
- [8] S.J.C. Schäffer, R.W. Berg, Potassium bis(μ -sulfato- $1\kappa O$: $2\kappa O'$)/bis-[*cis*-dioxido-*cis*-bis(sulfato- κO)/tungstate(VI)], Acta Crystallogr. E 61 (2005) i49–i51.
- [9] N.H. Hansen, R. Fehrmann, N.J. Bjerrum, Complex formation in pyrosulfate melts. 1, Inorg. Chem. 21 (1982) 744–752.
- [10] S.B. Rasmussen, K.M. Eriksen, G. Hatem, F. da Silva, K. Ståhl, R. Fehrmann, Conductivity, thermal measurements, X-ray investigations, and phase diagram of the $Na_2S_2O_7$ – $K_2S_2O_7$ system, J. Phys. Chem. B 105 (2001) 2747–2752.
- [11] R.L. McCreery, Calibration and validation. Raman Spectroscopy for Chemical Analysis, Chemical Analysis, vol. 157, Wiley-Interscience, 2000, pp. 251–291 (Chapter 10).
- [12] K. Nakamoto, Infrared and Raman Spectra of Inorganic and Coordination Compounds. Part B: Applications in Coordination, Organometallic, and Bioinorganic Chemistry, John Wiley and Sons Inc., New York, 1997.
- [13] J.D. Dyekjaer, R.W. Berg, H. Johansen, Ab initio calculation of conformation and vibrational spectrum for the pyrosulfate ion, J. Phys. Chem. A 107 (2003) 5826–5830.
- [14] W. Weltner Jr., D. McLeod Jr., Spectroscopy of tungsten oxide molecules in neon and argon matrices at 4 and 20 K, J. Mol. Spectrosc. 17 (1965) 276–299.
- [15] J. Gabrusenoks, A. Veispals, A. von Czarnowski, K.-H. Meiwes-Broer, Infrared and Raman spectroscopy of WO_3 and $CdWO_4$, Electrochim. Acta 46 (2001) 2229–2231.