



## Editorial

Advances and trends in microbial production of biopolymers and their building blocks

**Feng, Xinjun; Jiang, Xinglin; Zhao, Guang**

*Published in:*

Frontiers in Bioengineering and Biotechnology

*Link to article, DOI:*

[10.3389/fbioe.2022.1025797](https://doi.org/10.3389/fbioe.2022.1025797)

*Publication date:*

2022

*Document Version*

Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

*Citation (APA):*

Feng, X., Jiang, X., & Zhao, G. (2022). Editorial: Advances and trends in microbial production of biopolymers and their building blocks. *Frontiers in Bioengineering and Biotechnology*, 10, 1-3. Article 1025797. <https://doi.org/10.3389/fbioe.2022.1025797>

---

### General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.



## OPEN ACCESS

## EDITED AND REVIEWED BY

Georg M. Guebitz,  
University of Natural Resources and Life  
Sciences, Austria

## \*CORRESPONDENCE

Xinjun Feng,  
fengxj@qibebt.ac.cn

## SPECIALTY SECTION

This article was submitted to Industrial  
Biotechnology,  
a section of the journal  
Frontiers in Bioengineering and  
Biotechnology

RECEIVED 23 August 2022

ACCEPTED 09 September 2022

PUBLISHED 27 September 2022

## CITATION

Feng X, Jiang X and Zhao G (2022),  
Editorial: Advances and trends in  
microbial production of biopolymers  
and their building blocks.  
*Front. Bioeng. Biotechnol.* 10:1025797.  
doi: 10.3389/fbioe.2022.1025797

## COPYRIGHT

© 2022 Feng, Jiang and Zhao. This is an  
open-access article distributed under  
the terms of the [Creative Commons  
Attribution License \(CC BY\)](https://creativecommons.org/licenses/by/4.0/). The use,  
distribution or reproduction in other  
forums is permitted, provided the  
original author(s) and the copyright  
owner(s) are credited and that the  
original publication in this journal is  
cited, in accordance with accepted  
academic practice. No use, distribution  
or reproduction is permitted which does  
not comply with these terms.

# Editorial: Advances and trends in microbial production of biopolymers and their building blocks

Xinjun Feng<sup>1\*</sup>, Xinglin Jiang<sup>2</sup> and Guang Zhao<sup>3</sup>

<sup>1</sup>CAS Key Laboratory of Biobased Materials, Qingdao Institute of Bioenergy and Bioprocess Technology, Chinese Academy of Sciences, Qingdao, China, <sup>2</sup>The Novo Nordisk Foundation Center for Biosustainability, Technical University of Denmark, Kongens Lyngby, Denmark, <sup>3</sup>State Key Laboratory of Microbial Technology, Shandong University, Jinan, China

## KEYWORDS

biopolymer, polyhydroxyalkanoates, polysaccharide, poly (lactic acid), succinic acid, 3-hydroxypropionic acid, microbial technology, carbon emission

## Editorial on the Research Topic

[Advances and trends in microbial production of biopolymers and their building blocks](#)

Petroleum-based polymers have played an important role in human daily life, but they also cause serious environmental pollution due to their low biodegradability. In contrast, biopolymers have attracted unprecedented attentions with advantage of life cycle carbon emission reduction under the global achievement of “carbon peak” and “carbon neutrality”. However, some shortcomings of biopolymers remain and restrict their popular application, such as high cost, low productivity, and poor material properties.

This special issue consists of six original papers, one brief research report, two specialized review papers and one mini review article covering workhorse strains, cheap raw materials utilization, enzyme screening, monomer biosynthesis and bio-process optimization, which showcase current progress on biopolymers and aim to provide possible solutions to the existing problems.

Polyhydroxyalkanoates (PHAs) are one of the most popular biopolymers that exhibit similar mechanical properties to petrochemical-derived polymers with the added benefit of biodegradability and biocompatibility (Rekhi et al., 2022). To date, over 150 types of PHAs have been produced in the form of homopolymers, random and block copolymers, thus supporting a wide range of applications. Gao et al., systematically reviewed the recent advances in microbial synthesis of PHAs, including chassis engineering, substrate utilization, PHA synthase modification, and scale-up biomanufacturing, which will be of special interest to the researchers in the field of PHA biosynthesis.

The microbial hosts are crucial to desired biopolymer production. More than 70 genera of microbes have been identified and/or engineered for PHAs production

(Alcántara et al., 2020), such as *Ralstonia eutropha*, *Pseudomonas*, *Escherichia coli*, etc. The choice of microbiological strains directly impacts the chemical composition, structure and properties of the final polymers, as well as the substrate used. In recent years, some bacteria with particular characteristics have been proved to be economical and effective hosts. *Halomonas bluephagenesis*, a halophilic bacteria, can accumulate poly-3-hydroxybutyrate (PHB) up to more than 80% of the cell dry weight in an open unsterile process (Tan et al., 2011). *Rhodospseudomonas palustris*, a photosynthetic bacteria, has the ability to convert various carbon sources, especially CO<sub>2</sub>, into valuable chemicals and biopolymers. A review by Li et al. provided a comprehensive overview of the advantages, the challenges and possible solutions of *R. palustris* as a powerful microbial cell factory, specifically discussed its applications in production of PHAs, polysaccharides and isoprenoids monomers.

PHA synthases polymerize various hydroxyacyl-CoAs into different PHA polymers. However, PHA synthases prefer 3-hydroxyacyl-CoAs rather than 2-hydroxyacyl-CoAs, which makes it very difficult to synthesize polylactic acid (PLA) directly in microbial cells. To screen robust PHA synthase for PLA homopolymer biosynthesis, Shi et al. evaluated the class I PHA synthase from *Chromobacterium* sp. USM2 in engineered *E. coli* using glucose as carbon source, and demonstrated that it is feasible to catalyze the polymerization of lactyl-CoA with better performance in PLA production than that of the evolved class II PHA synthase PhaC<sub>I<sub>P86-19</sub></sub>. This work proved that class I PHA synthase has catalytic ability to 2-hydroxyacyl-CoAs.

As the cost of the substrate can account for up to 50% of the overall production cost (Urtuvia et al., 2014), various renewable and inexpensive carbon sources including lignocellulosic biomass hydrolysates, sugarcane molasses, crude glycerol, have been evaluated for PHAs production. Szacherska et al. explores to use short- and medium-chain fatty acids (SMCFAs) as raw materials for PHA production in three individual *Pseudomonas* strains. This study demonstrated that high PHA productivity can be obtained in *Pseudomonas* sp. G106 cultivation under nitrogen limitation conditions with cheap SMCFAs-rich stream from a cheese production line, and the extracted polymers possess better properties with lower melting point and degradation temperature.

Moreover, many bio-monomers can be utilized for polyesters production directly through chemical polymerization. Succinic acid is one of building blocks of the commercial polyester poly (butylene succinate) (PBS) with wide temperature window for thermoplastic processing. Liu et al. summarized different succinic acid biosynthetic pathways, concentrating on the key enzymes and metabolic engineering approaches, and future perspectives were also proposed. 3-Hydroxypropionic acid (3-HP) is a versatile platform compound which can be polymerized into polymers. Liu et al. engineered a 3HP biosynthetic pathway

from glucose with glycerol as intermediate in *Klebsiella pneumoniae*, and improved 3-HP production by CRISPR interference. 2-fluoro-3-hydroxypropionic acid was firstly biosynthesized by Liu et al., which is expected to obtain fluorine-containing materials such as poly (2-fluoro-3-hydroxypropionic acid) with better properties. Liu et al. investigated the biosynthesis of lactate in *E. coli* and proved that lysine acetylation of lactate dehydrogenase can regulate lactate synthesis effectively. In another study, Zhang et al. improved the bioconversion of phenylpyruvate to L-phenyllactate, whose homopolymer exhibits high-ultraviolet-absorbing properties, by introducing a NADH-dependent L-lactate dehydrogenase mutant into *Pichia pastoris* coupling with a NADH regeneration system.

As an important natural biopolymer, polysaccharides have been widely used in the food, pharmacy, cosmetics, and chemical industries, and microbial polysaccharides in particular offer many advantages compared to plant-derived polysaccharides (Chaabouni et al., 2014). Xu et al., presented the systematic optimization of fermentation process of exopolysaccharide using *Candida glabrata* mutant, resulting in significantly improved production of exopolysaccharide that shows great industrial application potential.

Finally, we sincerely thank all the submitting authors for considering to share their updated research outcomes and opinions in this special issue, the reviewers for their time and constructive comments to improve the manuscripts, also the editors Dr. Xiao-Jun Ji and Dr. Ka Yu Cheng for their kind support. We hope that readers find these articles in this special issue interesting and useful for their own research.

## Author contributions

XF and GZ conceived the manuscript; XF wrote the manuscript; XF, XJ, and GZ reviewed and edited the manuscript.

## Funding

XF is supported by the Youth Innovation Promotion Association of Chinese Academy of Sciences (2020214), National Natural Science Foundation of China (31800081), and Natural Science Foundation of Shandong Province (ZR2019QB015). GZ is supported by the National Natural Science Foundation of China (32170085, 31961133014).

## Conflict of interest

The authors declare that the research was conducted in the absence of any commercial or financial relationships that could be construed as a potential conflict of interest.

## Publisher's note

All claims expressed in this article are solely those of the authors and do not necessarily represent those of their affiliated

organizations, or those of the publisher, the editors and the reviewers. Any product that may be evaluated in this article, or claim that may be made by its manufacturer, is not guaranteed or endorsed by the publisher.

## References

- Alcántara, J. M. G., Distante, F., Storti, G., Moscatelli, D., Morbidelli, M., and Sponchioni, M. (2020). Current trends in the production of biodegradable bioplastics: The case of polyhydroxyalkanoates. *Biotechnol. Adv.* 42, 107582. doi:10.1016/j.biotechadv.2020.107582
- Chaabouni, E., Gassara, F., and Brar, S. K. (2014). "Biopolymers synthesis and application," in *Biotransformation of waste biomass into high value biochemicals*. Editors S. K. Brar, G. S. Dhillon, and C. R. Soccol (New York: Springer Press), 415–443.
- Rekhi, P., Goswami, M., Ramakrishna, S., and Debnath, M. (2022). Polyhydroxyalkanoates biopolymers toward decarbonizing economy and sustainable future. *Crit. Rev. Biotechnol.* 42 (5), 668–692. doi:10.1080/07388551.2021.1960265
- Tan, D., Xue, Y. S., Aibaidula, G., and Chen, G. Q. (2011). Unsterile and continuous production of polyhydroxybutyrate by *Halomonas* TD01. *Bioresour. Technol.* 102, 8130–8136. doi:10.1016/j.biortech.2011.05.068
- Urtuvia, V., Villegas, P., González, M., and Seeger, M. (2014). Bacterial production of the biodegradable plastics polyhydroxyalkanoates. *Int. J. Biol. Macromol.* 70, 208–213. doi:10.1016/j.ijbiomac.2014.06.001