



Experimental Evaluation of the Indistinguishability of Single Photons at 1.55 μm Generated by InAs(P)/InP Quantum Dots

Vajner, D. A.; Wasiluk, M.; Holewa, Pawel; Zieba-Ostój, E.; Gaal, Benedek; Sakanas, Aurimas; Krajnik, B.; Xiong, Meng; Yvind, Kresten; Gregersen, Niels

Total number of authors:

14

Publication date:

2023

Document Version

Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):

Vajner, D. A., Wasiluk, M., Holewa, P., Zieba-Ostój, E., Gaal, B., Sakanas, A., Krajnik, B., Xiong, M., Yvind, K., Gregersen, N., Syperek, M., Semenova, E., Musial, A., & Heindel, T. (2023). *Experimental Evaluation of the Indistinguishability of Single Photons at 1.55 μm Generated by InAs(P)/InP Quantum Dots*. Abstract from 51st International School & Conference on the Physics of Semiconductors, Szczyrk, Poland.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Experimental Evaluation of the Indistinguishability of Single Photons at 1.55 μm Generated by InAs(P)/InP Quantum Dots

D. A. Vajner¹, M. Wasiluk², P. Holewa^{2,3,4}, E. Zięba-Ostój², B. Gaál³,
A. Sakanas³, B. Krajnik², M. Xiong^{3,4}, K. Yvind^{3,4}, N. Gregersen³,
M. Syperek², E. Semenova^{3,4}, A. Musiał², T. Heindel¹

¹ *Institute of Solid State Physics, Technical University of Berlin, 10623 Berlin, Germany*

² *Laboratory for Optical Spectroscopy of Nanostructures, Department of Experimental Physics, Wrocław University of Science and Technology, 50-370 Wrocław, Poland*

³ *DTU Electro, Technical University of Denmark, 2800 Kongens Lyngby, Denmark*

⁴ *NanoPhoton-Center for Nanophotonics, Technical University of Denmark, 2800 Kongens Lyngby, Denmark*

Epitaxial quantum dots (QDs) have great potential as non-classical light sources in quantum technologies [1,2]. For advanced quantum cryptographic key exchange algorithms, single indistinguishable photons, generated on demand, are needed [3]. An appealing technology platform in this context are QDs emitting at 1.55 μm , showing prospects for long-haul low-loss optical transmission in a standard silica fiber [4,5].

In this contribution we investigate quantum optical properties of single photons emitted by InAs(P)/InP QDs heterogeneously integrated with silicon. The QDs are grown by metalorganic vapor-phase epitaxy in the Stranski-Krastanow mode and exhibit low areal density ($3.1 \times 10^8 \text{ cm}^{-2}$) and emission at $\sim 1.55 \mu\text{m}$ [6]. A metallic mirror beneath the QDs increases photon extraction efficiency to about 10% [7]. It enables imaging of the QD emission, letting localize a specific QD with $\sim 50 \text{ nm}$ accuracy, allowing for engineering of QD photonic environment.

In our study, we confirm single-photon emission from the QDs via measurements of the second-order autocorrelation function $g^{(2)}(\tau)$, revealing $g^{(2)}(0) = (3.2 \pm 0.6) \times 10^{-3}$ under quasi-resonant pulsed excitation. To investigate the degree of indistinguishability of emitted photons and gain insight into underlying dephasing mechanisms, Hong-Ou-Mandel-type two-photon interference (TPI) experiments are conducted as a function of the temporal delay δt between consecutively emitted photons. The TPI visibility, quantifying the degree of indistinguishability, was comparatively analyzed using both, integration of the raw experimental data and applying a fitting model, revealing the raw (i.e. ‘as measured’) and the post-selected TPI visibility. For $\delta t = 4 \text{ ns}$, we determine the visibility by evaluating the coincidences around $\tau = 0$ for co- and cross-polarized photons and compare the result with the method based on evaluating the areas of adjacent coincidence maxima in a characteristic five-peak pattern [8]. We obtain raw (post-selected) TPI visibilities of up to 20% (99%) and comparatively discuss the experimental uncertainties.

In summary, our work provides important insights and shows progress in generating telecom C-band single indistinguishable photons for applications in quantum information technologies.

[1] X. Zhou, L. Zhai, and J. Liu, *Photon. Insights* **1**, 2 R07 (2023).

[2] P. Michler, *Quantum Dots for Quantum Information Technologies* Vol. 237, Springer (2017).

[3] D. A. Vajner, L. Rickert, T. Gao *et al.*, *Adv. Quantum Technol.* **5**, 2100116 (2022)

[4] Y. Arakawa and M. J. Holmes, *Appl. Phys. Rev.* **7**, 021309 (2020).

[5] M. Benyoucef and A. Musiał, Chapter 18 in *Photonic Quantum Technologies: Science and Applications*, in press, WILEY-VCH GmbH (2023).

[6] P. Holewa, M. Gawęłczyk, C. Ciostek, *et al.*, *Phys. Rev. B* **101**, 195304 (2020).

[7] P. Holewa, A. Sakanas, U. M. Gür *et al.*, *ACS Photonics* **9**, 7, 2273–2279 (2022).

[8] A. Thoma, P. Schnauber, M. Gschrey, *et al.*, *Phys. Rev. Lett.* **116**, 033601 (2016).