A beam expander facility for studying x-ray optics

Christensen, Finn Erland; Hornstrup, Allan; Frederiksen, P.; Nilsson, C.; Grundsøe, Peter; Ørup, P.; Jacobsen, E.; Schnopper, H. W.; Lewis, R.; Hall, C.

Published in:
Review of Scientific Instruments

Link to article, DOI:
[10.1063/1.1143124](https://doi.org/10.1063/1.1143124)

Publication date:
1992

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Christensen, F. E., Hornstrup, A., Frederiksen, P., Nilsson, C., Grundsøe, P., Ørup, P., Jacobsen, E., Schnopper, H. W., Lewis, R., & Hall, C. (1992). A beam expander facility for studying x-ray optics. *Review of Scientific Instruments*, 63(1), 1168-1171. <https://doi.org/10.1063/1.1143124>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

A beam expander facility for studying x-ray optics

F. E. Christensen, A. Hornstrup, P. Frederiksen, C. Nilsson,
P. Grundsøe, P. Ørup, E. Jacobsen, and H. W. Schnopper
Danish Space Research Institute, Gl. Lundtoftevej 7, DK-2800 Lyngby, Denmark

R. Lewis and C. Hall
Daresbury Laboratory, Daresbury, Warrington WA4 4AD, United Kingdom

(Presented on 17 July 1991)

The detailed study of the performance of full scale x-ray optics often requires the illumination of large areas. This paper describes a beam expander facility at the Daresbury Synchrotron Radiation Facility. It combines monochromatization and beam expansion in one dimension. The beam expansion is obtained from an extremely asymmetric reflection in a large single crystal of Si. An expansion of a factor of 50 was obtained in one dimension. The expanded beam of ~ 85 mm is limited only by the crystal size. The facility is installed in a 12-m-long hutch. A specific application, in which a high throughput x-ray telescope will be studied, is described in detail.

I. INTRODUCTION

It is of crucial importance for the development of advanced x-ray optics and detectors, that testing and experimentation can be performed under realistic conditions over a wide range of x-ray energies. For large x-ray devices such as two-dimensional position sensitive detectors (PSD),¹ grazing incidence high throughput x-ray telescopes (XSPECT/SODART,² ASTRO-D,³ JET-X,⁴ and XMM⁵ telescopes) and crystal spectrometers [the $\sim 1000 \times 600$ mm² objective crystal spectrometer⁶ (OXS), to be flown on the SPECTRUM-X-GAMMA (SRG) satellite] the illumination of large areas with a suitably monochromatized and collimated beam is required. A pencil beam which is both monochromatized and collimated, is readily available over a wide energy range from synchrotrons and conventional x-ray sources. The testing of large area devices with such a beam is, however, very time consuming and requires an elaborate, two-dimensional, scanning apparatus.

The broad continuum of synchrotron radiation is extremely useful. For example, the efficiency of most x-ray devices is a function of wavelength and there are discontinuities which occur at absorption edges or emission features of the materials in reflectors, transmission windows, and detectors. In many cases, at least one or more features occur within the useful operating energy range. It is very difficult to accurately calibrate the device near such a feature with the limited number of emission line energies, which are available from either radioactive or x-ray tubes. Synchrotron light is linearly polarized in the plane of the electron orbit and the beam expander can be used to evaluate the polarization sensitivity of crystal spectrometers,⁶ polarimeters,⁷ and x-ray optics over a wide range of energy.

The working energy range covered by the telescopes which will be flown in the period from 1994 to 2000 (ASTRO-D, SRG, JET-X & XMM) is from ~ 0.1 to ~ 25 keV.²⁻⁵ All of them are based on the Wolter-1 design⁸ which allows accurate images to be recorded with a high signal to noise ratio by focusing the x rays on relatively

small pixels in a position sensitive x-ray detector. These x-ray telescopes are designed to yield images with an angular resolution of a few arcmin or less. The design resolution of ASTRO-D³ and SRG² is ~ 120 arcsec, of JET-X⁴ ~ 20 arcsec, and of XMM⁵ ~ 30 arcsec. A beam expander with good collimation and which can provide a beam wide enough to cover the radial aperture of these telescopes in the energy range from 5 to 15 keV will, therefore, be extremely useful.

II. THE BEAM EXPANDER

The principle of the device is based upon the one-dimensional expansion of a beam which undergoes extremely asymmetric reflection in a perfect single crystal of Si. The most efficient use of the crystal in terms of the width of the expanded beam versus the length of the crystal required, is obtained with a Bragg angle in the vicinity of 45° . The beam from the synchrotron is polarized in the horizontal plane and, as a compromise, a Bragg angle of $\sim 60^\circ$ has been chosen for the first experiments. Since the horizontal source dimension is 2.8 mm [full width at half-maximum (FWHM)] at the Daresbury Synchrotron,⁹ it is necessary to expand the beam by a factor of 50–100 to get an expanded beam of 100–200 mm which is our design goal. A premonochromator avoids higher order contamination. It is shown together with the beam expander in Fig. 1.

The testing of optics with focal lengths in the range 3–8 m, such as the high throughput x-ray telescopes mentioned above, imposes the need for an adequately large work area. The premonochromator is located in a pre-hutch. It is a standard, double-reflection, Si(111) channel-cut crystal and is oriented to reflect in the vertical plane. The main hutch (hutch 8.4) contains the beam expander and the optics to be tested. The monochromator and the beam expander crystal define a $(n, -n)$ double reflection system where the same reflection is used in both crystals. The beam from the monochromator strikes the beam expander crystal at a small grazing angle ($\sim 1^\circ$) relative to the surface. The reflecting planes make an angle ϕ relative to the surface and a beam of width H makes a footprint on

FIG. 1. A topview of the beam expander unit. A premonochromatized beam of horizontal width H is reflected in the symmetric monochromator crystal followed by beam expansion in the extremely asymmetrically cut beam expander crystal.

the beam expander crystal of $L \equiv H / \sin(\theta_B - \phi)$ where θ_B is the Bragg angle of the reflection. The width of the expanded beam is $H \sin(\theta_B + \phi) / \sin(\theta_B - \theta)$ or $L \sin(\theta_B + \theta)$. The factor $\sin(\theta_B + \phi) / \sin(\theta_B - \phi)$ defines the beam expansion factor F_{exp} and plays a central role in the classical theory of dynamical x-ray diffraction. As is well known $(F_{\text{exp}})^{1/2}$, determines, for a constant wavelength, the angular width of an asymmetric reflection.¹⁰

We have chosen Si(333), Si(444), and Si(555) reflections with $\phi = 59^\circ$ for the first experiments and this gives the theoretical F_{exp} versus $\theta_B - \phi$ shown in Fig. 2. This figure also shows the size of the illuminated footprint in the plane of reflection on the beam expander crystal for the case where $H = 2$ mm. Expansion factors of 50–100 can be

FIG. 2. F_{exp} and illuminated length L on beam expander crystal as a function of $(\theta_B - \phi)$. ϕ is assumed to be 59° and $H = 2$ mm.

achieved for $\theta_B - \phi$ in the range 0.5° – 1° which are well above θ_c , the critical angle for total reflection for the relevant wavelengths. Higher order correction to the classical theory of dynamical x-ray diffraction is important for angles between the surface and the incident beam at or below θ_c .¹¹

III. BEAM EXPANDER CRYSTAL PREPARATION

The crystals were sawed after careful alignment of the 111 planes relative to a fixture fitting into the diamond saw¹² at the Laboratory of Applied Physics at the Technical University of Denmark. The raw crystal was obtained from Topsil Semiconductor, Inc. It was a cylindrical Si boule ~ 7.5 cm in diameter and ~ 10 cm long with the 111 planes perpendicular to the axis of the cylinder. After sawing the crystals were lapped in a standard facility at Topsil to achieve a sufficiently flat surface. Finally, one of the faces of each crystal was polished. The dimension of crystal A are $84 \times 38 \times 3.65$ mm³ and those of crystal B are $98 \times 38 \times 3.65$ mm³. Larger crystals from a 12.5 cm diameter and 30 cm long crystal boule are now being prepared.

IV. EXPERIMENTAL RESULTS

The purpose of the first experiment was to establish the beam expander facility and test the performance of the two crystals A and B. The beam expander unit consists of the monochromator axis and the beam expander axis. The monochromator axis has a step resolution of 0.2 arcsec. The beam expander axis is supported on a rotatable arm (step resolution 1 mdeg) extending from the monochromator axis. The distance between the two axes along this arm can be varied. This construction allows the expanded beam to remain undeviated when different crystal reflections are used in the double reflection monochromator-beam expander system. As a result, the optics under test need not be moved (except for alignment) when crystals with different ϕ values (see Fig. 1) or different reflections are used. A precise crystal translation (step resolution 10 μ m) perpendicular to its surface accurately positions the expander crystal in the beam from the monochromator.

Precise (± 5 eV) energy calibration was accomplished by detecting the K -absorption edge from transmission measurements of thin foils of Cu, Zn, and Ni. Following the selection of an appropriate energy with the premonochromator, the reflected beam from the monochromator was readily obtained. The beam expander crystal is carefully positioned to be parallel to the beam and to intercept half of the intensity reflected from the monochromator. Finally, the expanded beam is found by rotating the beam expander from the zero angle until the reflection is detected. This provides an accurate determination of $\theta_B - \phi$ (see Fig. 1). Since θ_B is known from the energy calibration this measurement determines the value of ϕ . These are listed in Table I together with the values of F_{exp} calculated from θ_B and ϕ for the energies and reflections used in the experiment.

The width of the slit (see Fig. 1) in the vertical direction was fixed to be ~ 1 mm in all cases. This means that

TABLE I. Overview of experimental data.

Crystal/ reflection	$E[\text{keV}]/$ θ_B (deg)	Measured ϕ (deg)	F_{exp}	Measured width of reflection (arcsec)	Calculated width of reflection (arcsec)	
					polarization out-of-plane	polarization in-plane
A/Si(444)	9.00/61.47	59.04	20.3	10	12.5	6.8
B/Si(444)	9.00/61.47	59.06	20.5			
B/Si(444)	9.14/59.93	59.06	57.6			
B/Si(555)	11.41/60.01	59.06	52.7	4	6.5	3.4
B/Si(333)	6.85/60.01	59.07	53.3	24	31.2	17.9

$\Delta\lambda/\lambda$, the wavelength resolution following the premonochromator, is given by $\Delta E/E = \Delta\lambda/\lambda = \Delta\theta_V \cot[\theta_B(\text{PM})]$ where $\theta_B(\text{PM})$ is the Bragg angle in the Si(111) premonochromator and $\Delta\theta_V = 2.86 \times 10^{-5}$ rad is the angular collimation of the synchrotron beam in the vertical direction. For 9 keV this yields $\Delta\lambda/\lambda \sim 1.3 \times 10^{-4}$. For Si(444) reflection at 9 keV a $\Delta\lambda/\lambda$ of 9×10^{-5} was measured, when a symmetrically cut crystal with a Si(444) reflection was used, in place of the asymmetrically cut beam expander crystal, together with the monochromator in the dispersive (4, +4) setting. Since the Bragg angle for the reflections listed in Table I is $\sim 60^\circ$, this implies that the horizontal collimation $\Delta\theta_H \sim 9 \times 10^{-5} \tan(60^\circ) \sim 33$ arcsec. The collimation must be the same in the expanded beam since the monochromator and beam expander crystal form a nondispersive system. Reducing the slit width in the vertical direction from 1 mm to ~ 0.35 mm (the vertical source size) in future experiments, will reduce the $\Delta\lambda/\lambda$ obtained from the premonochromator to $\sim 4 \times 10^{-5}$ and, therefore, reduce the obtainable horizontal, angular collimation to ~ 15 arcsec. F_{exp} was measured as a function of the horizontal slit width H for crystal B used in the 444 reflection at 9 keV. For the data shown in Fig. 3, values of F_{exp} are obtained by dividing the width of the observed expanded beam by H . The theoretical value of F_{exp} is 20.5. The data show that near theoretical expansion is obtained for H values up to 2 mm

but reduced expansion is observed for $H = 4$ mm. This is in good agreement with a horizontal source size of 2.8 mm.⁹

The measured rocking curve widths obtained by rotating the beam expander crystal through its reflection range may be directly related to predictions of dynamical diffraction theory. Measured rocking curve widths (FWHM) are given in Table I. For these measurements H was adjusted to illuminate the entire length of the beam expander crystal. The angular widths of reflection in the asymmetric beam expander crystal which are calculated from dynamical diffraction theory, are also given in Table I for both in-plane and out-of-plane polarizations. The data in Table I show, as expected, that the measured reflection widths lie between these two values.

The intensity across the expanded beam measured in the one-dimensional PSD is shown in Fig. 4. In this case, the energy of the expanded beam was 6.85 keV and the Si(333) reflection was used with a H of 2 mm and a theoretical F_{exp} of 53.3 (see Table I). This should give $L \approx 121$ mm. Since the crystal is only 98 mm long an expanded beam of only $98 \sin(\theta_B + \phi) \sim 86$ mm (see Fig. 1) can be observed. Figure 4 shows that a reasonably constant intensity is observed along the detector for a length which corresponds to this value. The data in Figure 4 show that the width of the expanded beam is now limited only by the crystal size. We plan to produce crystals of length ≥ 200

FIG. 3. Measured values F_{exp} vs slit width H for a Si(444) reflection at 9 keV.

FIG. 4. The expanded beam reflected from Si(333) at 6.85 keV detected in one-dimensional PSD.

TABLE II. Energy table (keV) in x-ray telescope test.

ϕ [deg]	40	50	59	71
Reflection				
Si(333)	9.13	7.69	6.88	6.25
Si(444)	12.17	10.25	9.18	8.34
Si(555)	15.22	12.81	11.47	10.42

Energies are calculated assuming $\theta_B - \phi = 0.5^\circ$.

mm, and they will be used to obtain an expansion factor of >100 for $(\theta_B - \phi) \sim 0.5^\circ$. Finally, we measured a countrate in the expanded beam of ~ 30 kHz under the following conditions: Ring current ~ 200 mA/multibunch mode, slit dimensions 2×1 mm², $E = 9.14$ keV, and a Si(444) reflection.

Generating the expanded beam using the arrangement in Fig. 1 is, of course, possible without the premonochromator. In that case, all the orders of reflection will be expanded simultaneously. In addition, the intensity in each order will be increased when compared with the arrangement which includes the premonochromator. This may be impractical for testing of x-ray telescopes with a two-dimensional PSD developed especially for the low countrates encountered in x-ray astronomy. Using the facility without the premonochromator will be very useful for the testing of large PSDs developed for special high countrate synchrotron beam lines.¹

V. X-RAY TELESCOPE CALIBRATION

The detailed calibration of the SRG telescopes being produced at the Danish Space Research Institute² will be performed using the beam expander facility at important energies between ~ 5 and 15 keV,² using the four beam expander crystals listed in Table II. The SRG telescopes (Table III) are described in detail in Ref. 2. The complete arrangement which will be used for the calibration of x-ray telescopes is shown in Fig. 5. A distance of 400 mm will be fixed between the axis of the beam entering hutch 8.4 and the center of the expanded beam. Not shown in Fig. 5 are the evacuated beam pipes which will be used between the various elements especially in the 8 -m-long stretch from the telescope to the detector. The calibration data will be obtained by recording the image of the focused beam as the telescope is rotated around its optical axis. This produces the equivalent of a full aperture test of the telescope. A

TABLE III. Parameters of SRG telescope.

Focal length	8000 mm
Number of mirrors	8×154
Outer mirror diameter	600 mm
Inner mirror diameter	160 mm
Mirror length	200 mm
Mirror thickness	0.3 mm
Minimum mirror separation	0.5 mm
Substrate material	Al
Reflecting material	Au
Mass of one telescope	98 kg

FIG. 5. Complete arrangement for the full aperture calibration of a high throughput x-ray telescope.

precise rotation mechanism which supports the telescope has been constructed at the Danish Space Research Institute (DSRI) and initial tests indicate that the rotation of this mechanism contributes < 3 arcsec to the image blur.¹³ This is much less than the requirement for any of the high throughput telescopes mentioned above.

Future high energy x-ray telescopes such as a proposed graded d -spacing multilayer telescope¹⁴ which has a substantial throughput up to ~ 60 keV, can be evaluated in the beam expander facility since the synchrotron source will provide sufficient intensity at these energies.

ACKNOWLEDGMENTS

We thank O. Pedersen for the accurate alignment and cutting of the crystals. Further we thank Topsil Semiconductor Inc., for lapping the crystals and O. Rupsch for his expertise in polishing the crystals.

- ¹R. Lewis, N. Fore, C. Hall, B. Parker, I. Sumner, and J. Worgan, these proceedings; C. B.-Jørgensen, these proceedings.
- ²N. J. Westergaard, B. P. Byrnak, F. E. Christensen, P. Grundsøe, A. Hornstrup, S. Henriksen, U. Henriksen, E. Jespersen, H. U. Nørgaard-Nielsen, J. Polny, H. W. Schnopper, and P. Ørup, *Opt. Eng.* **29**, 658 (1990).
- ³P. J. Serlemitsos, *SPIE* **830**, 179 (1987).
- ⁴A. Wells *et al.* *SPIE* **1546**, (1991).
- ⁵B. Aschenbach and H. Bräuninger, *SPIE* **982**, 10 (1988).
- ⁶F. E. Christensen, B. P. Byrnak, A. Hornstrup, Zhu Shou-hua, and H. W. Schnopper, *SPIE* **1344**, 14 (1990).
- ⁷E. H. Silver, A. Simionivici, S. E. Labov, R. Novick, P. Kaaret, C. Martin, T. Hamilton, M. C. Weisskopf, R. F. Elsner, J. Beeman, G. A. Chanan, G. Manzo, E. Costa, G. C. Perola, and G. W. Fraser *SPIE* **1160**, 587 (1989).
- ⁸H. Wolter, *Ann. Phys. NY* **10**, 94 (1952). H. Wolter, *Ann. Phys. NY* **10**, 286 (1952).
- ⁹P. Quinn (private communication).
- ¹⁰W. H. Zachariassen, *X-ray Diffraction in Crystals*, (Dover, New York, 1935).
- ¹¹O. Brümmer, H. R. Höche, and J. Nieber, *Z. Naturforsch.* **37a**, 519 (1982).
- ¹²G. Christiansen, L. Gerward, and I. Alstrup, *Acta. Crystallogr. A* **31**, 142 (1975).
- ¹³C. Nilsson, P. Frederiksen, Masters thesis, Danish Space Research Institute, 1991.
- ¹⁴F. E. Christensen, A. Hornstrup, N. J. Westergaard, H. W. Schnopper, J. Wood, and K. Parker, *SPIE* **1546**, (1991).