Highly tunable large core single-mode liquid crystal photonic bandgap fiber

Alkeskjold, Thomas Tanggaard; Lægsgaard, Jesper; Bjarklev, Anders Overgaard; Hermann, David Sparre; Broeng, Jes; Li, Jun; Gauza, Sebastian; Wu, Shin-Tson

Published in:
Conference on Lasers and Electro-Optics and 2006 Quantum Electronics and Laser Science Conference. CLEO/QELS 2006.

Link to article, DOI:
[10.1109/CLEO.2006.4627627](https://doi.org/10.1109/CLEO.2006.4627627)

Publication date:
2006

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Alkeskjold, T. T., Lægsgaard, J., Bjarklev, A. O., Hermann, D. S., Broeng, J., Li, J., Gauza, S., & Wu, S-T. (2006). Highly tunable large core single-mode liquid crystal photonic bandgap fiber. In *Conference on Lasers and Electro-Optics and 2006 Quantum Electronics and Laser Science Conference. CLEO/QELS 2006.*: CLEO/QELS 2006 (pp. 1-2). IEEE. <https://doi.org/10.1109/CLEO.2006.4627627>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Highly Tunable Large Core Single-Mode Liquid Crystal Photonic Bandgap Fiber

Thomas Tanggaard Alkeskjold, Jesper Lægsgaard and Anders Bjarklev

*COM.DTU Department of Communication, Optics and Materials, Technical University of Denmark, DK-2800 Lyngby, Denmark.
tal@com.dtu.dk*

David Sparre Hermann

Photonics Laboratory, Department of Microtechnology and Nanoscience MC2, Chalmers University of Technology, 412 96 Gothenburg, Sweden.

Jes Broeng

Crystal Fibre A/S, Blokken 84, DK-3460 Birkerød, Denmark

Jun Li, Sebastian Gauza and Shin-Tson Wu

College of Optics and Photonics: CREOL & FPCE, University of Central Florida, Orlando, Florida 32816, USA

Abstract: We demonstrate a highly tunable photonic bandgap fiber, which has a core diameter of 2 μm , and a bandgap tuning sensitivity of 2 $\text{nm}/^\circ\text{C}$ at room temperature. The insertion loss is estimated to be less than 0. dB.

© 200 Optical Society of America

OCIS codes: 2 0. 0 Microstructure devices 0 0.2 0 Fiber optics components

1. Introduction

The presence of air holes in Photonic Crystal Fibers (PCFs) gives the possibility of infusing liquids into the fibers and in this way creating tunable fiber based devices using both index-guiding [1-] and bandgap-guiding fibers [-]. It has been demonstrated that an initial index-guiding PCF can be converted to a highly tunable bandgap-guiding type PCF by infiltrating the air holes with a Liquid Crystal (LC), which allow for thermal [], electrical [,] and all-optical tuning []. The spectral properties of LC PCFs can be thermally tuned using LCs having nematic, smectic A and cholesteric mesophases, which yield different functionalities such as threshold switching and tunable spectral filtering with a bandgap tuning sensitivity of $\text{nm}/^\circ\text{C}$ [] below phase transitions. In the latter case, thermal shifting of the bandgaps may for example be achieved by utilizing the temperature dependence of the ordinary refractive index of nematic LCs by resistive or optical pump induced heating []. In this case, it is desirable to have a high tuning sensitivity around room temperature in order to decrease the power consumption and ease handling and packaging. Here, we present a tunable large-core single-mode photonic bandgap fiber, which has a core diameter of 2 μm , an effective mode area of $0\mu\text{m}^2$ and a high bandgap tuning sensitivity of 2 $\text{nm}/^\circ\text{C}$ at room temperature. This is achieved with a specially synthesized LC exhibiting an extraordinary large thermo-optic effect [].

2. Device characterization

The fiber has a large central core surrounded by six rings of air holes arranged in a triangular lattice (Fig. 1, right, inset). The hole diameter, inter hole distance, core diameter and outer fiber diameter are 2 μm , 11.2 μm , 2 μm and 0 μm , respectively. The large mode-area is obtained using a three-rod core design, giving a core having three-fold symmetry. The air holes were infiltrated with the specially synthesized LC called UCF-1 [] formulated by the University of Central Florida. The air holes were filled with UCF-1 over 10mm of the length using capillary forces. The LC was heated to isotropic phase and cooled down again slowly to achieve a homogenous alignment. Polarized microscopy observations on a single silica capillary tube, with an inner diameter of μm , indicated that the LC was planar aligned, i.e., with the LC director aligned along the fiber axis, and, therefore, with the ordinary index predominantly determining the spectral features of the fiber. Fig. 1 left shows the transmission spectrum for the LCPCF normalized to the unfilled PCF. The spectrum shows high transmission in two bandgaps, bandgap A centered around 11 0 nm and bandgap B centered around 1 00 nm. In between these two bandgaps, a weaker transmission peak appears. This feature is a direct consequence of the LC anisotropy, which causes a splitting of the EH_{11} mode of an LC-infiltrated microchannel from the HE_{12} and HE_1 modes, so that a narrow bandgap opens up between the cladding states derived from these modes. Simulations confirmed this and the modal cut-off wavelengths of the EH_{11} and HE_{12} mode, which represents the stopbands in the anti-resonant model [10], is also

plotted for $T = 25^\circ\text{C}$ in Fig. 1. As observed from Fig. 1, the width and transmission level of the bandgap between A and B is reduced as the temperature of UCF-1 $T_c = 25^\circ\text{C}$ is increased, which decreases the LC anisotropy and thereby reduces the splitting of the EH_{11} , HE_{12} and HE_{11} cladding modes. The spectral tuning sensitivity of the UCF-1 infiltrated PCF at 25°C was measured at the long wavelength edge of bandgap A to be $2\text{ nm}/^\circ\text{C}$, which is approximately 10% higher than when using the commercial available LC E-70 Merck above 0°C [11]. Fig. 1 right shows a comparison between the measured normalized transmission spectrum of bandgap B and simulation of two-times the coupling loss between the index-guided mode in an unfilled PCF and the bandgap-guided mode in LC filled PCF evaluated using overlap integrals. Insets show simulated mode fields of the index-guided mode in an unfilled PCF (TIR mode) and a PBG guided mode at the center wavelength of the bandgap. The mode profiles have been normalized to equal intensity and to exhibit same contour levels. The simulated coupling loss agrees well with the shape of the PBG spectrum, which indicates that coupling loss $> 0\text{ dB}$ is the dominant loss mechanism, as was also found by Steinvurzel et al. [12].

In conclusion, a highly tunable bandgap fiber has been demonstrated. The fiber exhibits a bandgap tuning sensitivity of $2\text{ nm}/^\circ\text{C}$ at room temperature. The guided mode has an effective area of $0.05\mu\text{m}^2$ with a device insertion loss of less than 0.5 dB .

Fig. 1 Temperature dependent transmission spectra of the LCPCF at $T = 25^\circ\text{C}$, 27°C and 29°C (left). Also plotted are the calculated modal cut-offs of the HE_{12} and EH_{11} modes of a single LC capillary (dashed vertical lines). Simulated coupling loss between filled and unfilled section compared to measured transmission spectrum (right). Insets show an optical micrograph of the PCF end facet, simulated mode fields of the PBG mode at the center of the bandgap and the index-guided mode of the unfilled section.

3. References

- [1] B. J. Eggleton, C. Kerbage, P. S. Westbrook, R. Windeler & A. Hale, "Microstructured optical fiber devices," *Opt. Express* **9**, 1-10 (2001).
- [2] C. Kerbage, R. S. Windeler, B. J. Eggleton, P. Mach, M. Dolinski, and J. A. Rogers, "Tunable devices based on dynamic positioning of micro-fluids in micro-structured optical fiber," *Opt. Comm.* **204**, 1-10 (2002).
- [3] F. Du, Y. Q. Lu and S. T. Wu, "Electrically tunable liquid-crystal photonic crystal fiber," *Appl. Phys. Lett.* **85**, 2111-2113 (2004).
- [4] R. T. Bise, R. S. Windeler, K. S. Kranz, C. Kerbage, B. J. Eggleton, and D. J. Trevor, "Tunable photonic band gap fiber," in *OSA Trends in Optics and Photonics TOPS 00*, Optical Fiber Communication Conference Technical Digest, Postconference Edition Optical Society of America, Washington, DC, 2002, pp. 1-4.
- [5] T. T. Larsen, A. Bjarklev, D. S. Hermann, and J. Broeng, "Optical devices based on liquid crystal photonic bandgap fibres," *Opt. Express* **11**, 212-219 (2003).
- [6] M. W. Haakestad, T. T. Alkeskjold, M. D. Nielsen, L. Scolari, J. Riishede, H. E. Engan and A. Bjarklev, "Electrically tunable photonic bandgap guidance in a liquid crystal filled photonic crystal fiber," *IEEE Photonics Technology Letters*, volume 14, issue 4, page 1511-1513, April 2002.
- [7] T. T. Alkeskjold, J. Lægsgaard, D. S. Hermann, A. Anawati, J. Broeng, J. Li, S. T. Wu, and A. Bjarklev, "All-optical modulation in dye-doped nematic liquid crystal photonic bandgap fibers," *Opt. Express* **12**, 1011-1018 (2004).
- [8] L. Scolari, T. T. Alkeskjold, J. Riishede, A. Bjarklev, D. S. Hermann, A. Anawati, M. D. Nielsen, and P. Bassi, "Continuously tunable devices based on electrical control of dual-frequency liquid crystal filled photonic bandgap fibers," *Opt. Express* **13**, 1011-1018 (2005).
- [9] J. Li, S. Gauza, and S. T. Wu, "High temperature-gradient refractive index liquid crystals," *Opt. Express* **12**, 2002-2010 (2004).
- [10] N. M. Litchinitser, S. C. Dunn, P. E. Steinvurzel, B. J. Eggleton, T. P. White, R. C. McPhedran, and C. M. de Sterke, "Application of an ARROW model for designing tunable photonic devices," *Opt. Express* **12**, 1011-1018 (2004).
- [11] T. T. Alkeskjold, J. Lægsgaard, A. Bjarklev, D. Hermann, J. Broeng, J. Li, S. Gauza and S. T. Wu, "Highly tunable large core single-mode liquid crystal photonic bandgap fibre", To appear in *Applied Optics*.
- [12] P. Steinvurzel, B. T. Kuhlmeier, T. P. White, M. J. Steel, C. Martijn de Sterke, B. J. Eggleton Long wavelength anti-resonant guidance in high index inclusion microstructured fibers, *Opt. Express* **12**, p. 212-219 (2004).