Trapping of cubic ZnO nanocrystallites at ambient conditions

Decremps, F.; Pellicer-Porres, J.; Datchi, F.; Itie, J.P.; Polian, A.; Baudalet, F.; Jiang, Jianzhong

Published in:
Applied Physics Letters

Link to article, DOI:
[10.1063/1.1527696](https://doi.org/10.1063/1.1527696)

Publication date:
2002

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Decremps, F., Pellicer-Porres, J., Datchi, F., Itie, J. P., Polian, A., Baudalet, F., & Jiang, J. (2002). Trapping of cubic ZnO nanocrystallites at ambient conditions. *Applied Physics Letters*, 81(25), 4820-4822.
<https://doi.org/10.1063/1.1527696>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Trapping of cubic ZnO nanocrystallites at ambient conditions

F. Decremps,^{a)} J. Pellicer-Porres,^{b)} F. Datchi, J. P. Itié, A. Polian, and F. Baudalet
*Laboratoire de Physique des Milieux Condensés, CNRS-UMR 7602, Université Pierre et Marie Curie,
Tour 13, B77, 4, place Jussieu, 75252 Paris Cedex 05, France*

J. Z. Jiang

Department of Physics, Technical University of Denmark, Building 307, DK-2800 Lyngby, Denmark

(Received 21 May 2002; accepted 14 October 2002)

Dense powder of nanocrystalline ZnO has been recovered at ambient conditions in the metastable cubic structure after a heat treatment at high pressure (15 GPa and 550 K). Combined x-ray diffraction (XRD) and x-ray absorption spectroscopy (XAS) experiments have been performed to probe both long-range order and local crystallographic structure of the recovered sample. Within uncertainty of these techniques (about 5%), all the crystallites are found to adopt the NaCl structure. From the analysis of XRD and XAS spectra, the cell volume per chemical formula unit is found to be 19.57(1) and 19.60(3) Å³, respectively, in very good agreement with the zero-pressure extrapolation of previously published high-pressure data. © 2002 American Institute of Physics. [DOI: 10.1063/1.1527696]

With a direct band gap of 3.4 eV at ambient conditions, wurtzitic ZnO (*w*-ZnO), like GaN or 6H-SiC, is intensively studied in view of potential applicability in the field of optoelectronics (e.g., laser or light-emitting diodes).¹ Furthermore, in comparison with its previous competitors, *w*-ZnO combines several unique electrical, acoustic, and chemical properties, which make it one of the most technologically relevant binary compounds.²

Recently, it has been shown that intentionally as well as unintentionally doped *w*-ZnO give rise to high-quality *n*-type (electron) conductivity that directly comes with its wurtzite ambient condition stable structure.³ The *p*-type *w*-ZnO conductivity has been theoretically predicted to be increased by doping with nitrogen through the use of NO or NO₂,⁴ and some recent publications demonstrated that *p*-type *w*-ZnO thin films could be fabricated.^{5–7} However, physical limitations preclude the synthesis of high *p*-type (hole) conductivity, and therefore, the practical applicability of short-wavelength optoelectronic devices based on *p*-*n* junctions.⁸ On the other hand, ZnO in its ionic NaCl high-pressure phase (*c*-ZnO) has an electronic structure with an indirect band gap that may be compatible for high *p*-type doping. The possibility to trap this high-pressure phase at ambient condition would, therefore, be of great interest. Several high-pressure structural investigations of ZnO have been done in the last two decades⁹ and all agree that the *w*-ZnO→*c*-ZnO transition is reversible at ambient temperature (with a transition pressure of 9 GPa upon increasing pressure and 2 GPa upon decreasing pressure¹⁰). In this work, we demonstrate a way to obtain *c*-ZnO crystallites metastable at ambient conditions based on the peculiar physical features observed in the nanocrystal regime.

Unlike extended solids, nanocrystals are nearly interior

defect-free and externally faceted with a defined shape directly related to the crystallographic structure. Under pressure, a structural transformation in these systems occurs with a single nucleation center per crystallite,¹¹ which is usually associated with shape change.^{12,13} Thus, the average surface tension as well as the surface areas of the nanocrystallites should obviously affect the internal energy difference between the high- and low-pressure structure, unlike bulk crystals. For example, measurements on CdSe (Ref. 11) indicate that both forward and backward pressure transitions are particle-size dependent. In a same manner, Jiang *et al.*¹⁴ found an enhancement of the upstroke transition pressure (15.1 GPa) in 12(2) nm size ZnO nanocrystals compared to the bulk value. After a decompression from 52.5 GPa down to ambient pressure, a coexistence of the *w* and *c* phases was recovered with a large fraction of the NaCl phase. We reproduced this experiment with the same type of nanopowder [12(2) nm] and we found that the *c* fraction of the recovered sample after decompression at ambient conditions increases with the maximum pressure reached upon compression. This phenomenon cannot be ascribed to a size distribution effect, since above the transition pressure the whole sample is observed to be in the high-pressure phase independently of the maximum pressure reached (which also rejects a possible effect due to a pressure gradient). From the work of Tolbert and Alivisatos¹¹ and Wickham, Herhold, and Alivisatos,¹³ we suggest that this phenomenon is related to the shape change of the crystallites that occurs at the phase transition. At room temperature, and pressure above the phase transition, a fraction of the crystallites may acquire an unstable shape compared to the equilibrium configuration (despite the interior high-pressure structure). Since the shape change (due to atomic diffusion) is mainly determined by dynamic processes, heating at high pressure should help to anneal the unstable shape to the equilibrium one. Finally, heating would lead to a larger number of rocksalt nanocrystallites of ZnO trapping at ambient conditions.

Obtained from planetary ball mill, nanocrystalline pow-

^{a)}Electronic address: frederic.decremps@pmc.jussieu.fr

^{b)}Permanent address: Institut de Ciència dels Materials, Universitat de València, Departamento de Física Aplicada, Edifici Investigació, E-46100 Burjassot (València), Spain.

FIG. 1. X-ray energy dispersive spectra for nanopowder of ZnO at ambient conditions before (bottom pattern) and after (top pattern) the high-pressure, high-temperature (15 GPa, 550 K) cycle. Single NaCl phase spectrum of ZnO measured at 10 GPa and 1000 K ($V=19.16 \text{ \AA}^3$) is also shown for comparison.

der of *w*-ZnO with an average size of 12(2) nm was used in this work. The high-pressure cell was a membrane diamond anvil cell (DAC) specifically designed for high-temperature studies.¹⁵ The DAC was surrounded by a heater and a thermocouple was glued on one end of the diamond anvil to determine the average temperature on the sample with an accuracy of 20 K. A rhenium gasket was preindented from 200 to 30 μm , and a 150 μm hole was drilled in the center by spark erosion. Silicon oil was used as a pressure transmitting medium because it is amorphous and chemically inert. Pressure was measured using the fluorescence emission of a ruby ball¹⁶ placed into the gasket hole. The accuracy was better than 1 GPa at the maximum pressure reached.

Combined x-ray diffraction (XRD) and x-ray absorption spectroscopy (XAS) experiments have been performed at the LURE synchrotron facility in Orsay (France), giving, respectively, long-range and local structure. The powder x-ray diffraction measurements were made in the energy dispersive mode with the wiggler at the DW11 station. After the energy calibration of the Ge detector, the 2θ angle was determined by collecting diffraction patterns of a gold sample placed in between the anvils. The polychromatic x-ray beam was collimated to a $50 \times 50 \mu\text{m}^2$ spot centered on to the gasket hole. Absorption spectroscopy was performed at the D11 dispersive XAS station at the Zn *K* edge (see Ref. 17 for technical details) and the Zn–O distance was deduced from the experimental data using the FEFF6 (Ref. 18) codes for theoretical calculations of x-ray absorption fine structure including multiple-scattering pathways.

The sample was first pressurized at ambient temperature up to 15 GPa and then heated to 550 K. Under these conditions, ZnO was in a pure rocksalt structure (*Fm*3*m*), as expected from the phase diagram of the extended crystal.¹⁹ After cooling down to 300 K and a gradual decompression to ambient pressure, the crystallographic structure of the sample recovered from the previous *P*–*T* path was examined in detail by XRD and XAS.

X-ray diffraction spectra recorded before and after high-pressure treatment are reproduced in Fig. 1. Exposure times between 30 and 40 min were sufficient to collect diffraction

FIG. 2. Zn *K*-edge XAFS $k\chi(k)$ experimental data for nanopowder of ZnO before (bottom pattern) and after (top pattern) the high-pressure, high-temperature (15 GPa, 550 K) cycle, compared with the experimental $k\chi(k)$ signal of pure *c*-ZnO recorded at 15 GPa and 300 K.

patterns with a suitable signal-to-noise ratio. The five peaks observed in the recovered sample spectrum are unambiguously indexed to a cubic cell and used to compute the structural parameter, leading to $a_0=4.278(3) \text{ \AA}$ [i.e., $V_0=19.57(1) \text{ \AA}^3$].

The local structure (up to 8 $\text{\AA}$) around the Zn atoms of ZnO has been probed by XAS. X-ray absorption fine structure (XAFS) spectra before and after a high-pressure, high-temperature cycle are compared in Fig. 2 with that of pure rocksalt zinc oxide recorded at 15 GPa and 300 K (after cooling down from 550 K). Here, again, the recovered sample is found to be in a sixfold coordination scheme (within uncertainty of 5%, given by the crystalline structure sensitivity of both XRD and XAS techniques), corresponding to a NaCl type structure (in *w*-ZnO, the coordination number is 4).

Figure 3 shows the magnitude of the experimental and calculated Fourier transform. The theoretical data have been fitted for a cubic structure to the experimental spectra in the [0.5–3.65 $\text{\AA}$] range with only four parameters: the first-

FIG. 3. Magnitude of the Fourier transform of the recovered sample $k^2\chi(k)$ spectra (solid line) compared with the best fit of the theory (dotted line) including all single and multiple-scattering paths between 0.5 and 3.65 $\text{\AA}$. Best fit is obtained with $d_{\text{Zn-O}}=2.14(1) \text{ \AA}$, $\sigma^2=0.01 \text{ \AA}^2$, $E_0=9659.4 \text{ eV}$, and $S_0^2=0.83$.

neighbor distance $d_{\text{Zn-O}}$, the corresponding variance σ^2 , the theoretical energy origin E_0 , and a nonstructural parameter S_0^2 for amplitude correction. The best fit gives $d_{\text{Zn-O}} = 2.14(1) \text{ \AA}$ [i.e., $V_0 = 19.60(3) \text{ \AA}^3$], in very good agreement with the present XRD data, as well as with the zero-pressure extrapolation of high-pressure x-ray diffraction data obtained on bulk cubic ZnO: $V_0 = 19.66 \text{ \AA}^3$,¹⁹ $V_0 = 19.48 \text{ \AA}^3$,²⁰ or $V_0 = 19.60 \text{ \AA}^3$.⁹

In conclusion, while the wurtzite-to-rocksalt phase transition has been shown to be reversible for bulk ZnO crystals, this property is demonstrated to be drastically altered by the reduction of grain size. From the combined XRD and XAS observations, we argue that high-pressure (15 GPa) heat (550 K) treatment of ZnO nanocrystallites yields to a single metastable cubic phase of zinc oxide at room conditions. This result is of most interest since this metastable phase may open a broad range of technical applications as heterojunctions for photodetection and photovoltaic devices.²¹ Moreover, while a small volume of *c*-ZnO powder has only been obtained in the present work (through the use of a diamond anvil cell), the P - T conditions required to obtain this sample can also be reached by a multianvil high-pressure apparatus where the sample volume is of 100 mm^3 . Finally, and from a more general point of view, the present study indicates that the phase diagram of semiconductors with reduced size may be different from that of the bulk compounds and deserve further studies.

This research has been partly supported by a Marie Curie Fellowship of the European Community Human Potential Program under Contract No. HPMF CT2000-00764. The European Commission is not responsible for any views or results expressed.

¹H. Kawazoe, M. Yakusakawa, H. Hyodo, M. Kurita, H. Yanagi, and H. Hosono, *Nature (London)* **389**, 389 (1997).

²D. C. Look, *Mater. Sci. Eng., B* **80**, 383 (2001).

³D. M. Hofmann, A. Hofstaetter, F. Leiter, H. Zhou, F. Henecker, B. K.

Meyer, S. B. Orlinskii, J. Schmidt, and P. G. Baranov, *Phys. Rev. Lett.* **88**, 045504 (2002).

⁴Y. Yan, S. B. Zhang, and S. T. Pantelides, *Phys. Rev. Lett.* **86**, 5723 (2001).

⁵M. Joseph, H. Tabata, and T. Kawai, *Jpn. J. Appl. Phys., Part 2* **38**, L2505 (1999).

⁶M. Joseph, H. Tabata, H. Saeki, K. Ueda, and T. Kawai, *Physica B* **302-303**, 140 (2001).

⁷Y. R. Ryu, S. Zhu, D. C. Look, J. M. Wrobel, H. M. Jeong, and H. W. White, *J. Cryst. Growth* **216**, 330 (2000).

⁸D. J. Chadi, *Phys. Rev. Lett.* **72**, 534 (1994).

⁹S. Desgreniers, *Phys. Rev. B* **58**, 14102 (1998); F. Decremps, J. Pellicer-Porres, A. M. Saitta, J.-C. Chervin, and A. Polian, *ibid.* **65**, 092101 (2002), and references therein.

¹⁰With the exception of J. M. Recio, M. A. Blanco, V. Luaña, R. Pandey, L. Gerward, and J. Staun Olsen, *Phys. Rev. B* **58**, 8949 (1998). In this paper, the authors claimed that the rocksalt phase of a fraction of pressurized ZnO microcrystalline powder is retained metastable at ambient conditions. However, due to mechanical frictions, the applied force on the diamond anvils (and, therefore, the pressure on the sample) may still be present without ram load. Thus, if the x-ray diffraction spectra recorded by J. M. Recio *et al.* have been performed without opening the cell, remanent pressure due to the friction effect could explain the disagreement with all other previously cited studies.

¹¹S. H. Tolbert and A. P. Alivisatos, *J. Chem. Phys.* **102**, 4642 (1995).

¹²S. H. Tolbert, A. B. Herhold, L. E. Brus, and A. P. Alivisatos, *Phys. Rev. Lett.* **76**, 4384 (1996).

¹³J. N. Wickham, A. B. Herhold, and A. P. Alivisatos, *Phys. Rev. Lett.* **84**, 923 (2000).

¹⁴J. Z. Jiang, J. S. Olsen, L. Gerward, D. Frost, D. Rubie, and J. Peyronneau, *Europhys. Lett.* **50**, 48 (2000).

¹⁵J. C. Chervin, B. Canny, J. M. Besson, and P. Pruzan, *Rev. Sci. Instrum.* **66**, 2595 (1995).

¹⁶G. J. Piermarini, S. Block, J. D. Barnett, and R. A. Forman, *J. Appl. Phys.* **46**, 2774 (1975).

¹⁷H. Tolentino, E. Dartyge, A. Fontaine, and G. Tourillon, *J. Appl. Crystallogr.* **21**, 15 (1988).

¹⁸S. I. Zabinsky, J. J. Rehr, A. Ankudinov, R. C. Albers, and M. J. Eller, *Phys. Rev. B* **52**, 2995 (1995).

¹⁹F. Decremps, J. Zhang, and R. C. Liebermann, *Europhys. Lett.* **51**, 268 (2000).

²⁰H. Karzel, W. Potzel, M. Köferlein, W. Schiessl, U. Hiller, G. M. Kalvius, D. W. Mitchell, T. P. Das, P. Blaha, K. Schwartz, and M. P. Pasternak, *Phys. Rev. B* **53**, 11425 (1996).

²¹M. Purica, E. Budianu, and E. Rusu, *Microelectron. Eng.* **51-52**, 425 (2000).