Geometrical tuning of nanoscale split-ring resonators

Jeppesen, Claus; Kristensen, Anders; Xiao, Sanshui; Mortensen, Asger

Published in:

2010 Conference on Lasers and Electro-Optics (CLEO) and Quantum Electronics and Laser Science Conference (QELS)

Publication date:

2010

Document Version

Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):

Jeppesen, C., Kristensen, A., Xiao, S., & Mortensen, A. (2010). Geometrical tuning of nanoscale split-ring resonators. In *2010 Conference on Lasers and Electro-Optics (CLEO) and Quantum Electronics and Laser Science Conference (QELS)* (pp. 1-2). IEEE.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Geometrical tuning of nanoscale split-ring resonators

Claus Jeppesen, Anders Kristensen

Department of Micro- and Nanotechnology, DTU Nanotech, Technical University of Denmark, DK-2800 Kongens Lyngby, Denmark
Corresponding author: anders.kristensen@nanotech.dtu.dk; Phone: +45- 4525 6331, Fax: +45- 4588 7762

Sanshui Xiao, N. Asger Mortensen,

Department of Photonics Engineering, DTU Fotonik, Technical University of Denmark, DK-2800 Kongens Lyngby, Denmark

Abstract: We investigate the capacitance tuning of nanoscale split-ring resonators. An *LC*-model predicts a simple dependence of resonance frequency on slit aspect ratio. Experimental and numerical data follow the predictions of the *LC*-model.

© 2010 Optical Society of America

OCIS codes: (160.3918) Metamaterials, (250.5403) Plasmonics

1. Introduction

Metamaterials are artificially structured materials with exceptional optical properties inherited from the structure of the sub-wavelength, mesoscopic unit-cell. Designing negative index materials with simultaneously negative permittivity ϵ as well as a negative permeability μ is one of the promising aspects of metamaterials. Since a negative electric response is common in metals at e.g. optical frequencies, the search has primarily focused on designing structures with a negative magnetic response. Different types of split-ring resonator (SRR) geometries [1–3] are particularly central in this context and have been realized at Terahertz [1, 4] to visible frequencies [3, 5]. The analogy with inductor-capacitor (*LC*) circuits have motivated considerable efforts in establishing simple circuit models, allowing for an estimate of the resonance frequency $\omega_0 = 1/\sqrt{LC}$ in terms of geometrical parameters of the split-ring resonator structure, see. e.g. Refs. [6–7] and references therein. The *LC*-model has proven to be a good approximation as long as the coupling response of the SRR array is small compared to the response of a single SRR, hence the period Λ has to be sufficiently large [8]. Tuning of the resonance has been accomplished by scaling of a single geometrical dimension [9], linear scaling of all SRR dimensions [5], and finally by altering the cladding [10].

Figure 1. Schematic drawing of the split-ring resonator design, indicating central geometrical parameters as well as the polarization configuration of the excitation.

In this paper, the influence on resonance frequency of geometrical scaling of split-ring resonators is studied experimentally and by means of full-wave numerical simulations. The SRRs are placed in a periodic array keeping the period constant and large, $\Lambda=500$ nm, to minimize coupling effects. The system is described by an *LC*-model [7]. The model predicts a data collapse, which is experimentally verified.

$$(k_0 l)^2 \sim d/w \quad (1)$$

where k_0 is the free-space wave number, l is the side length, d is the slit width, w is the slit length, see Fig. 1.

2. Results

The LC-model is compared to experimental and numerical simulation data. Full-wave simulations were performed in CST Microwave Studios. The numerical data in Fig. 2(b) are calculated for a structure with $l=200$ nm, $d=80$ nm, $h=30$ nm, $\Lambda=440$ nm. The numerical data support the predicted linear scaling of the LC-model.

For the experimental investigations, 8 samples with 2 mm by 2 mm arrays of gold SRRs were fabricated on glass substrates by electron beam lithography and lift-off [7], see Fig. 2(a). The geometrical parameters of the samples covered: $d=80$ nm, $w=90$ -110 nm, $l=200$ nm, $h=35$ nm.

The transmission was measured using a 1 mm diameter laser spot, thus effectively probing an ensemble of 10^8 - 10^9 SRRs. The experimental data are fitted to the LC-model in Fig. 2(b), using $k=2\pi/\lambda$, where λ is the measured resonance wavelength λ , and the split ring dimensions d , l , w are measured by SEM inspections.

Figure 2. (a) Micrograph of a SRR array with pitch $\Lambda = 440$ nm. This sample has $l = 200$ nm, $w = 95$ nm, $d = 80$ nm, and $h = 35$ nm. (b) Plot of $(k_0 l)^2$ versus d/w where experimental and numerical data are plotted together with the LC-model. The x-error bars on the experimental data represent the standard deviation (SD) of ten individual measurements of w , and d added together. The y-error bars are the 1 nm spectral resolution of the Ando AQ-6315E Optical Spectrum Analyzer added to the SD of ten measurements of the length.

In conclusion, we have fabricated periodic arrays of subwavelength, nanoscale split-ring resonators to investigate geometrical tuning. Our key observation is that the experimental and numerical data follow the predictions of the LC-model.

- [1] T. J. Yen, W. J. Padilla, N. Fang, D. C. Vier, D. R. Smith, J. B. Pendry, D. N. Basov, and X. Zhang, "Terahertz magnetic response from artificial materials", *Science* **303**, 1494 (2004).
- [2] N. Katsarakis, G. Konstantinidis, A. Kostopoulos, R. S. Penciu, T. F. Gundogdu, M. Kafesaki, E. N. Economou, T. Koschny, and C. M. Soukoulis, "Magnetic response of split-ring resonators in the far-infrared frequency regime", *Opt. Lett.* **30**, 1348 (2005).
- [3] C. Enkrich, M. Wegener, S. Linden, S. Burger, L. Zschiedrich, F. Schmidt, J. F. Zhou, T. Koschny, and C. M. Soukoulis, "Magnetic Metamaterials at Telecommunication and Visible Frequencies", *Phys. Rev. Lett.* **95**, 203901 (2005).
- [4] S. Linden, C. Enkrich, M. Wegener, J. F. Zhou, T. Koschny, and C. M. Soukoulis, "Magnetic response of metamaterials at 100 terahertz", *Science* **306**, 1351 (2004).
- [5] M. W. Klein, C. Enkrich, M. Wegener, C. M. Soukoulis, and S. Linden, "Single-slit split-ring resonators at optical frequencies: limits of size scaling", *Opt. Lett.* **31**, 1259 (2006).
- [6] T. D. Corrigan, P. W. Kolb, A. B. Sushkov, H. D. Drew, D. C. Schmadel, and R. J. Phaneuf, "Optical plasmonic resonances in split-ring resonator structures: an improved LC model", *Opt. Express* **16**, 19850 (2008).
- [7] C. Jeppesen, N. A. Mortensen, and A. Kristensen, "Capacitance tuning of nanoscale split-ring resonators", *Appl. Phys. Lett.* **95**, 1931084 (2009).
- [8] B. Kante, A. de Lustrac, and J. M. Lourtioz, "In-plane coupling and field enhancement in infrared metamaterial surfaces", *Phys. Rev. B* **80** (2009).
- [9] K. Aydin, I. Bulu, K. Guven, M. Kafesaki, C. M. Soukoulis, and E. Ozbay, "Investigation of magnetic resonances for different split-ring resonator parameters and designs", *New J. Phys.* **7**, 1367 (2005).
- [10] Y. Sun, X. Xia, H. Feng, H. Yang, C. Gu, and L. Wang, "Modulated terahertz responses of split ring resonators by nanometer thick liquid layers", *Appl. Phys. Lett.* **92** (2008).