Characterization of donor-acceptor-pair emission in fluorescent 6H-SiC

Ou, Yiyu; Jokubavicius, Valdas; Linnarsson, Margareta; Yakimova, Rositza; Syväjärvi, Mikael; Ou, Haiyan

Publication date:
2011

[Link back to DTU Orbit](#)

Citation (APA):

Ou, Y., Jokubavicius, V., Linnarsson, M., Yakimova, R., Syväjärvi, M., & Ou, H. (2011). *Characterization of donor-acceptor-pair emission in fluorescent 6H-SiC*. Abstract from 24th Nordic Semiconductor Meeting, Aarhus, Denmark. <http://phys.au.dk/NSM2011/>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Characterization of donor-acceptor-pair emission in fluorescent 6H-SiC

Yiyu Ou¹*, Valdas Jokubavicius², Margareta Linnarsson³, Rositza Yakimova², Mikael Syväjärvi², and Haiyan Ou¹

¹Department of Photonics Engineering, Technical University of Denmark, DK-2800 Lyngby, Denmark

²Department of Physics, Chemistry and Biology, Linköping University, SE-58183, Linköping, Sweden

³School of Information and Communication Technology, Royal Institute of Technology, SE-16440, Kista, Sweden

*Email: yiyo@fotonik.dtu.dk

Boron (B)- and nitrogen (N)-codoped 6H-SiC epilayer exhibits strong donor to acceptor pair (DAP) band luminescence which makes it a promising candidate for the white light emitting diode (LED) [1]. To investigate the optimized dopant concentrations, five samples with the same B concentration level and varies N concentrations were grown by the fast sublimation growth process (FSGP) and analyzed by the photoluminescence (PL) and angle-resolved PL measurements. Secondary ion mass spectrometry (SIMS) and Raman spectroscopy confirm the increasing N concentration from sample #a to #e [2].

Figure 1. PL spectra of B-N-codoped 6H-SiC sample with emission angle of 0 degree (normal incidence, insert: zoom-in of sample #a, #b, #c).

Figure 2. Variation of PL peak shift and FWHM with increasing emission angle in sample #d (Insert: change of normalized PL intensity).

The PL spectra are shown in Fig. 1. It is seen that high-level p-type sample (#a) exhibits extremely low DAP emission efficiency, while low-level p-type samples (#b, #c) have relatively stronger DAP emission but still at a low level. Intense DAP emission was observed in n-type samples (#d, #e) and the strongest DAP emission occurred in sample d with B and N concentration difference of $4.6 \times 10^{18} \text{ cm}^{-3}$. Despite the intensity difference, all the DAP emission spectra show the same peak wavelength at 584 nm and with a full width at half maximum (FWHM) of 120 nm. From Fig. 2, it is shown that the peak wavelength blue shifts with increasing emission angle in sample #d, and the FWHM starts to decrease and becomes more dramatic when the emission angle is larger than 45 degrees. Our results revealed that the optimized way to achieve intense DAP emission in B-N-doped 6H-SiC is to use low-level n-type doping with both B and N concentrations exceeding 10^{18} cm^{-3} . Also the their difference should be larger than $4 \times 10^{18} \text{ cm}^{-3}$.

References

1. S. Kamiyama, et al., J. Appl. Phys., 99, 093108 (2006).
2. Y. Ou, et al., submitted to ICSCRM 2011 (2011).