Effect of annealing on the structure and optical properties of InGaAs/GaAs quantum dots

Xu, Zhangcheng; Leosson, Kristjan; Birkedal, Dan; Hvam, Jørn Märcher; Sadowski, J.; Liu, Y.; Yang, K.; Zhao, Z.; Chen, X.

Published in:
International Conference on Molecular Beam Epitaxy, 2002

Link to article, DOI:
[10.1109/MBE.2002.1037915](https://doi.org/10.1109/MBE.2002.1037915)

Publication date:
2002

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Xu, Z., Leosson, K., Birkedal, D., Hvam, J. M., Sadowski, J., Liu, Y., Yang, K., Zhao, Z., & Chen, X. (2002). Effect of annealing on the structure and optical properties of InGaAs/GaAs quantum dots. In *International Conference on Molecular Beam Epitaxy, 2002* (pp. 373-374). IEEE. <https://doi.org/10.1109/MBE.2002.1037915>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Effect of Annealing on the Structure and Optical properties of InGaAs/GaAs Quantum Dots

Zhangcheng Xu, Kristjan Leosson, Dan Birkedal, Jørn M. Hvam
Research Center COM, Technical University of Denmark, Lyngby, DK-2800, Denmark
Janusz Sadowski
Niels Bohr Institute, Copenhagen University, Copenhagen, DK-2100, Denmark
Yanmei Liu, Kuntang Yang, Zongyan Zhao
Department of Physics, Anhui University, Hefei, 230039, P.R.China
Xiaoshuang Chen
Shanghai Institute of Technical Physics, Chinese Academy of Sciences, P.R.China

Corresponding author: Mr. Zhangcheng Xu, E-mail: zxu@com.dtu.dk,
Tel: +45-45256388 Fax: +45-45256581

In this paper, we report the effect of annealing on self-assembled InGaAs/GaAs quantum dots, as investigated by means of resonant photoluminescence (PL), resonant Raman scattering, polarization dependent PL, and high resolution X-ray diffraction.

Two InGaAs/GaAs quantum dot samples are grown in Stranski-Krastnov (SK) mode by solid source MBE, on (001) oriented undoped GaAs substrates. A 5-monolayer-In_{0.5}Ga_{0.5}As QD layer was embedded in the GaAs matrix. One sample was in-situ annealed at 660°C for 11 minutes under As overpressure.

Figure 1 shows the PL spectra excited at different energies (E_{ex}) at 10 K. At $E_{ex} = 1.3883\text{eV}$ close to the edge of the density of states in the wetting layer, a resonant PL peak appears on the high-energy shoulder of the broad PL band excited non-resonantly ($E_{ex} = 1.9592\text{eV}$), for both the as-grown and annealed samples. Resonant Raman scattering peaks are also observed in Fig. 1, the LO phonon energy of InGaAs in the annealed sample (34.2 meV) is higher than in the as-grown sample (33.9 meV), which means the Indium composition in the QDs of annealed sample is lower than that of as-grown sample.

Figure 2 shows the polarization of surface-emitted PL from the as-grown and annealed samples. The PL polarization anisotropy P is defined as $(I_{[\bar{1}\bar{1}0]} - I_{[110]}) / (I_{[110]} + I_{[\bar{1}\bar{1}0]})$, where $I_{[110]}$ and $I_{[\bar{1}\bar{1}0]}$ are intensities polarized along the $[110]$ and $[\bar{1}\bar{1}0]$ directions, respectively. The value of P is indication of the elongation of QDs along $[\bar{1}\bar{1}0]$ with respect to $[110]$ due to anisotropic surface diffusion of indium. As shown in Fig.2, little change in the anisotropy P can be seen for the as-grown and annealed samples.

Figure 3 shows the high-resolution X-ray diffraction (XRD) rocking curves around the GaAs (004) peak. It can be seen that the fringes in the range of -1000 to -1500 arcsecs evolve into a broad tail for the annealed sample, which means the strain relief occurs in the growth direction during annealing the QDs' sample.

Fig. 1 PL spectra at different excitation energies at 10 K, for (a) the as-grown sample, and (b) the annealed one

Fig. 2 PL polarization anisotropy measured at 10 K

Fig. 3 High resolution XRD rocking curves around GaAs (004) peak