Poling of UV-written Waveguides

Arentoft, Jesper; Kristensen, Martin; Hübner, Jörg; Xu, W.; Bazylenko, M.

Published in:
Conference Proceedings of OFC` 99

Link to article, DOI:
[10.1109/OFC.1999.766399](https://doi.org/10.1109/OFC.1999.766399)

Publication date:
1999

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Arentoft, J., Kristensen, M., Hübner, J., Xu, W., & Bazylenko, M. (1999). Poling of UV-written Waveguides. In *Conference Proceedings of OFC` 99* (pp. 250-252). IEEE. <https://doi.org/10.1109/OFC.1999.766399>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Poling of UV-written Waveguides

Jesper Arentoft, Martin Kristensen, Jörg Hübner

Mikroelektronik Centret, Technical University of Denmark, Bldg. 345 East,
DK-2800 Lyngby, Denmark, Ph : +45 4525 5723, Fax : +45 4588 7762, E-mail : ja@mic.dtu.dk

Wei Xu

Australian Photonics Co-operative Centre, Optical Fibre Technology Centre,
The University of Sydney, Australian Technology Park, Eveleigh, NSW 1430, Australia

Michael Bazylenko

Australian Photonics Co-operative Centre, Optical Fibre Technology Centre,
School of Electrical Engineering, University of New South Wales, Sydney, NSW 2052, Australia

The inherent lack of second-order nonlinear optical (SONO) properties of centrosymmetric and amorphous media has prevented the development of essential photonic components, e.g. electro-optic (EO) modulators and wavelength converters, in silica-based optical fibres and planar waveguides. Electric field poling is a promising way to induce SONO effects in silica [1-6]. In the poling procedure the silica device (bulk, fibre or planar waveguide) is subjected to a strong electric field, while excited by heat [1-5] or radiation [6]. The physical processes taking place during glass poling are not fully understood, but it is widely accepted that either dipoles in the glass are oriented to the poling field or charge migration leads to the build-up of a space-charge field, which then acts on the third-order properties of the glass to give an apparent second-order response [1,2].

Waveguides were written with 248 nm radiation through an Al mask in a three layer structure, as sketched in Fig.1. The core and the top cladding were deposited by PECVD. The

samples were D₂-loaded prior to UV-exposure. The UV-induced refractive index change of the glass used in the core has proven stable up to 700 °C [7], thus making poling at high temperatures possible.

Two types of poling experiments were carried out : 1) thermally assisted poling and 2) UV-assisted poling. In all experiments the Al mask was used as the top electrode and the Si wafer as the ground electrode. The EO effect was measured in a fibre-based Mach-Zehnder Interferometer (MZI). The MZI setup is shown in Fig. 2. To our best knowledge this is the first reported poling of UV-written waveguides.

Thermally assisted poling was carried out with the samples placed on a

Fig.1 Cross-sectional view of waveguides during UV-writing. All glass layers are 3µm thick.

heater supplied with a temperature controller. The best result was obtained with thermally assisted poling at 405 °C with a voltage of -2.5 kV applied to the top electrode. The EO coefficient measured, 0.05 pm/V, is to our best knowledge one of the highest reported for a silica-based channel waveguide [3,5]. Fig. 3 shows the temperature dependence of the induced EO coefficient. The observed dependence is different from that observed for silica fibres [4], as the optimum poling temperature in our case is ~150 °C higher. The glass temperature (measured on top of the sample) was ~50 °C lower than the temperature of the heater. The temperatures given in Fig.3 is the average of the glass temperature and the heater temperature.

Fig.2 Fibre-based Mach-Zehnder interferometer setup.

In the UV-assisted poling experiments the samples were either poled during or after UV-writing of the waveguides. An EO coefficient of 0.01 pm/V was obtained in both cases. The combined poling and writing, which is demonstrated here for the first time, seems a very attractive fabrication method.

A sample poled at -1.5 kV and ~300 °C showed no measurable decay in the EO response when tested again 9 months after poling. The induced EO coefficient of this sample was 0.02 pm/V. The high stability might be related to the high value of the optimum poling temperature of this glass, as the activation energy for the processes taking place during poling probably is

Fig. 3 Electro-optic coefficient as a function of poling temperature. The horizontal error bars only apply to the absolute temperatures, as explained in the text. The relative positions of the data points are not affected.

comparable to the activation energy for the decay.

In conclusion we have performed thermal poling and UV-poling of UV-written silica-based waveguides. An EO coefficient of 0.05 pm/V was obtained with a poling field of 2.8 MV/cm and a poling temperature of 405 °C. This is to our best knowledge one of the highest EO coefficients reported for a poled silica-based channel waveguide. The optimum poling temperature is ~150 °C higher than reported for optical fibres. We have demonstrated simultaneous UV-writing and UV-poling. However, the EO effect obtained by UV-poling is very small. Repeated measurements indicate that the induced EO effect is stable over a period of 9 months.

References :

- [1] R.A. Myers, X. Long, S.R.J. Brueck, "Recent advances in the second-order nonlinear optical properties of amorphous silica materials", *Proc. of SPIE*, **2289**, 98 (1994)
- [2] P.G. Kazansky, P.St.J. Russel, "Thermally poled glass : frozen-in electric field or oriented dipoles ?", *Opt. Comm.*, **110**, 611 (1994)
- [3] A.C. Liu, M.J.F. Digonnet, G.S. Kino, "Electro-optic phase modulation in a silica channel waveguide", *Opt. Lett.*, **19**, 466 (1994)
- [4] D. Wong, W. Xu, R. Hall, and M. Janos, "Thermal poling of aluminium co-doped germano-silicate fibres," *Proceedings of the 23rd Australian Conference of Optical Fibre Technology*, Melbourne, 197-200 (1998)
- [5] M. Abe, T. Kitagawa, K. Hattori, A. Himeno, Y. Ohmori, "Electro-optic switch constructed with a poled silica-based waveguide on a Si substrate", *Proceedings of the conference on "Integrated Photonics Research" Boston, Massachusetts, Techn. Digest*, **6**, 319 (1996)
- [6] T. Fujiwara, D. Wong, Y. Zhao, S. Fleming, S. Poole, M. Sceats, "Electro-optic modulation in germanosilicate fibre with UV-excited poling", *Electron. Lett.*, **31**(7), 573 (1995)
- [7] C.V. Poulsen, T. Storgaard-Larsen, J. Hübner, O. Leistiko, "Novel Type of Highly Photosensitive Germanium Doped Silica Glass", in *"Photosensitive Optical Materials and Devices"*, *Proc. of SPIE*, **2998**, 132 (1997) and C.V. Poulsen : *"Photonic Components in Active Optical Materials"*, Ph.D. thesis, Mikroelektronik Centret, DTU, Denmark (1995)