

Magnetic High-Field Phases of Magnetoelectric LiNiPO₄

E. Fogh¹, R. Toft-Petersen², H. Nojiri³, G. Granroth⁴, T. Kihara³ and N. B. Christensen¹

¹ Department of Physics, Technical University of Denmark, Kongens Lyngby, Denmark

² Helmholtz Zentrum Berlin für Materialien und Energie, Berlin-Wannsee, Germany

³ Institute for Material Research, Tohoku University, Sendai, Japan

⁴ Neutron Scattering Sciences Division, Oak Ridge National Laboratory, Oak Ridge, Tennessee

In this work the magnetic high-field phases and magnetoelectric properties of LiNiPO₄ are studied up to 30T.

LiNiPO₄ is a member of the family of lithium orthophosphates which are of orthorhombic structure and exhibit the magnetoelectric effect [1]. LiNiPO₄ is a quasi-2D system with long range antiferromagnetic order below T_N=21.8T in zero-field. The magnetic phase diagram of the material has previously been studied up to 17.3T [2,3] and pulsed-field magnetization measurements up to 23T show several additional phase transitions [4].

Here LiNiPO₄ is investigated for fields up to 30T by pulsed high magnetic field time-of-flight Laue neutron diffraction and by magnetization and electric polarization measurements. Two high-field phases were found in agreement with the previous observations. The ordering vectors were determined and possible spin structures were suggested. The polarization measurements show a re-entrance of the magnetoelectric effect for $\mu_0 H \approx 19-21T$, which points towards a commensurate ferrimagnetic state. However, the behavior of the effect is not fully understood. The effect vanishes above 21T where either a linearly polarized spin structure or a spin spiral is present.

The experimental technique using pulsed high magnetic fields in connection with neutrons is relatively new [5]. Nevertheless, the results displayed here show that the technique presents a future possibility to study high-field phases of certain magnetic materials.

References

- [1] M. Mercier, J. Gareyt, and E. F. Bertaut, C. R. Acad. Sci. Ser. B 264, 979, 1967
- [2] T. B. S. Jensen, N. B. Christensen, M. Kenzelmann, H. M. Rønnow, C. Niedermayer, N. H. Andersen, K. Lefmann, J. Schefer, M. Zimmermann, J. Li, J. L. Zarestky, and D. Vaknin, Phys. Rev. B, 79(092412), 2009
- [3] R. Toft-Petersen, J. Jensen, T. B. S. Jensen, N. H. Andersen, N. B. Christensen, C. Niedermayer, M. Kenzelmann, M. Skoulatos, M. D. Le, K. Lefmann, S. R. Hansen, J. Li, J. L. Zarestky, and D. Vaknin, Phys. Rev. B, 84(054408), 2011
- [4] V.M. Khurstalyov, V.N. Savitsky, and N.F. Kharchenko, Czechoslovak Journal of Physics, 54, 2004
- [5] S. Yoshii, K. Ohoyama, K. Kurosawa, H. Nojiri, M. Matsuda, P. Frings, F. Duc, B. Vignolle, G. L. J. A. Rikken, L.-P. Regnault, S. Michimura, and F. Iga, Phys. Rev. Letters, 103(077203), 2009