



Oxygen Transport Properties of Ca/W-Substituted Lanthanum Nickelate

Hendriksen, Peter Vang; Ovtar, Simona

Published in:

Book of Abstracts. 20th International Conference on Solid State Ionics (SSI-20)

Publication date:

2015

Document Version

Peer reviewed version

[Link back to DTU Orbit](#)

Citation (APA):

Hendriksen, P. V., & Ovtar, S. (2015). Oxygen Transport Properties of Ca/W-Substituted Lanthanum Nickelate. In *Book of Abstracts. 20th International Conference on Solid State Ionics (SSI-20)* (pp. 177)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Oxygen Transport Properties of Ca/W-Substituted Lanthanum Nickelate

Peter V. Hendriksen and Simona Ovtar; Department of Energy Conversion and Storage, Technical University of Denmark, Roskilde, Denmark.

Lanthanum nickelates (LNO) are mixed oxygen-ionic and electronic conductors (MIECs) and candidate materials for the cathode of solid oxide fuel cells operating at intermediate temperature (IT-SOFC) and for oxygen permeation membranes. The advantage of LNO compared to the well-known $\text{La}_{1-x}\text{Sr}_x\text{MnO}_{3-d}$ is the thermal stability and the comparable thermal expansion coefficient to the mostly used electrolytes. La_2NiO_4 has a K_2NiF_4 -type crystal structure, with the perovskite-like layers separated by rock-salt La_2O_2 layers. In contrast to perovskite MIECs the LNO has oxygen excess with oxygen anions in interstitial positions in the La_2O_2 layers of the structure which are charge compensated by p-type electronic charge carriers. Doping with the alkaline-earth cations decreases oxygen excess and ionic conductivity but increases the electronic conductivity.

Powders of lanthanum nickelates partially substituted with Ca on A side and/or W on B side were prepared by combustion synthesis. The gel was dried and fired at 300 °C, and subsequently calcined at different temperature to achieve a single phase material. The calcined powders were pressed in rectangular bar shape and sintered at 1300 °C for 10 h. The dense bars were ground and polished to certain size and used for the electrical conductivity measurements. Crystal structures of powders as well as bars were analyzed by x-ray diffraction and the microstructure of polished surface was investigated by scanning electron microscope. The oxygen transport properties of the samples were studied by electrical conductivity relaxation (ECR), which is a well-established method to determine the oxygen transport properties of MIECs; oxygen surface exchange coefficient (k_{ex}) and the chemical diffusion coefficient (D_{chem}). The conductivity of Ca and/or W substituted LNO is thermally activated and activation energies from 4 - 16 kJ/mol were measured for different substitutions. The highest conductivity of 68 S/cm at 500 °C was measured for $\text{La}_{1.4}\text{Ca}_{0.6}\text{Ni}_{0.9}\text{W}_{0.1}\text{O}_{4+d}$. The total conductivity is decreasing with the $p\text{O}_2$, indicating that LNO is a p-type electronic conductor. However, the $p\text{O}_2$ dependence of the conductivity for the Ca and Ca-W substituted LNO is very low. While, for the W substituted LNO ($\text{La}_2\text{Ni}_{0.9}\text{W}_{0.1}\text{O}_{4+d}$) much stronger dependence was observed and the oxygen transport properties were determined. At 500 °C and for $p\text{O}_2$ change from 0.2 to 0.1 bar the k_{ex} is 5×10^{-3} cm/s and D_{chem} is 5×10^{-3} cm²/s, which is several times higher than observed for LNO doped with aluminum [1]. The electrical properties and strategies to achieve fast oxygen transport in substituted LNO as well as possible applications of the materials will be discussed.

[1] S.-Y. Jeon, J. Alloy. Comp. 589 (2014) 572