



Pulsed laser deposition (PLD) of the CZTS absorber for thin solar cells with up to 5.2%-efficiency

Cazzaniga, Andrea Carlo; Canulescu, Stela; Ettliger, Rebecca Bolt; Pryds, Nini; Hansen, Ole; Schou, Jørgen; Crovetto, Andrea; Hansen, Ole; Yan, Chang; Sun, K.

Total number of authors:
11

Publication date:
2017

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Cazzaniga, A. C., Canulescu, S., Ettliger, R. B., Pryds, N., Hansen, O., Schou, J., Crovetto, A., Hansen, O., Yan, C., Sun, K., & Hao, X. (2017). *Pulsed laser deposition (PLD) of the CZTS absorber for thin solar cells with up to 5.2%-efficiency*. Abstract from EMRS Spring meeting 2017, Strasbourg, France.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

A. Cazzaniga, S. Canulescu, R. B. Ettliger, N. Pryds, Ole Hansen and J. Schou*
The Technical University of Denmark, DTU Fotonik, Risø Campus, DK-4000 Roskilde,
Denmark

A. Crovetto, O. Hansen

The Technical University of Denmark, DTU Nanotech, DK-2800 Kgs. Lyngby, Denmark

N. Pryds

The Technical University of Denmark, DTU Energy, DK-4000 Roskilde, Denmark

C. Yan, K. Sun, X. Hao

School of Photovoltaic and Renewable Energy Engineering, University of New Wales, NSW
2052, Sydney, Australia

Pulsed laser deposition (PLD) of the CZTS absorber for thin solar cells with up to 5.2% -efficiency

CZTS ($\text{Cu}_2\text{ZnSnS}_4$) is a promising material for solar cell absorbers and consists of abundant, environmentally friendly elements with a recently obtained efficiency of 9.4 %.

For films produced with pulsed laser deposition (PLD) from a quaternary sintered, multi-element target, the composition can deviate significantly from that of the target, depending on the laser fluence. By tuning the laser fluence from a 248-nm excimer laser beam on a sintered CZTS target ($2\text{CuS}:\text{ZnS}:\text{SnS}$), the metal ratios in the film can be controlled. Films were deposited in high vacuum on a Mo-coated soda lime glass substrate at room temperature. At low fluence below 1 J/cm^2 the copper content in the film is low, while at high fluence the films become copper-rich. At a fluence 0.7 J/cm^2 we have achieved a ratio $\text{Cu}/(\text{Sn}+\text{Zn}) \sim 0.85$ which is in the right regime for a cell.

After sulfurization and the final deposition of the buffer and window layers the best cell with an effective area of 21 mm^2 and only a 400-nm thick CZTS layer had an efficiency of 5.2 % (and $V_{\text{oc}} = 616 \text{ mV}$, a $J_{\text{sc}} = 17.6 \text{ mA/cm}^2$ and a fill factor of 48 %). This efficiency is the highest one obtained with an absorber layer of CZTS made by PLD until now. Despite the thin absorber, there are no signs that material and junction quality are significantly lower than that of thicker absorbers: grain size, carrier lifetimes, collection efficiency, shunt resistance, and dark saturation current are all similar to (thicker) benchmark CZTS cells.