



Production and storage stability of skin carbonated CaO

Jensen, Ole Mejlhede; Fletcher, Jim

Publication date:
2019

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):

Jensen, O. M., & Fletcher, J. (2019). *Production and storage stability of skin carbonated CaO*. Abstract from 73rd RILEM Annual Week & International Conference on Innovative materials for Sustainable Civil Engineering (IMSCE) , Nanjing , China.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Production and storage stability of skin carbonated CaO

Ole Mejlhede Jensen^a and Jim Fletcher^b

Technical University of Denmark (Kgs. Lyngby, Denmark)^a

Saint-Gobain Gypsum (Leicester, United Kingdom)^b

Abstract: Calcium oxide, CaO, has a rapid and vigorous exothermic reaction in contact with liquid water; -104 kJ/mol. Such is CaO desire to react it will even capture water vapor at a low relative humidity from the surrounding atmosphere. This hydration reaction, however, can be considerably delayed if the CaO has a surface layer of CaCO₃ [1]. In dry atmospheric air at room temperature carbonation of CaO is extremely slow, but by exposure to pure CO₂ at elevated temperatures, such as 300 to 700°C a dense skin of CaCO₃ on the CaO particles can be produced in a matter of a few hours, see Table 1. Results of storage stability are given in Table 2.

Temperature (°C)	Time (h)	Carbonation (%)
700	4	36.8
500	5	22.4
375	4.5	9.1

Table 1. Examples of degree of carbonation by exposure of CaO to pure CO₂ gas in a tube furnace. The CaO is soft burned with an average particle size of approximately 10 μm. The degrees of carbonation are calculated based on weight changes and have been confirmed by QXRD.

RH (%) → Time (days) ↓	20		40		61		75		83		88		96	
1	54	0	87	0	88	0	90	0	90	2	92	8	93	15
3	70	0	88	0	89	1	90	20	90	46	91	67	91	78
7	89	0	90	2	90	9	91	67	92	84	93	91	94	94
14	90	1	90	12	90	35	91	87	93	91	93	93	93	97
30	90	6	88	43	91	67	92	92	94	94	94	95	97	98
90	90	30	91	75	92	86	93	93	97	98	-	-	98	99

Table 2. Comparison of degrees of hydration of unprotected non-carbonated CaO (non-bold) and 11.9% skin carbonated CaO (**bold**). Each measurement is based on 2 g of material which has been stored in a humid environment for different times at the shown relative humidities at 40°C. Degrees of hydration were calculated from simple gravimetric measurements.

It is clear that skin carbonation is a very effective method for delaying hydration of CaO. The measurements also indicate that an induction period for the hydration is created by the skin carbonation. This may correspond to the time for sufficient water to diffuse through the protective CaCO₃ skin and disrupt it by expansive Ca(OH)₂ formation.

Potential applications for skin carbonated CaO include shrinkage compensation and chemical prestressing of concrete. It is expected that it is possible to skin carbonate MgO and that it will possess properties similar to skin carbonated CaO apart from a slower hydration rate.

References

[1] H.S. Song and C.H. Kim, Cement and Concrete Research, 20, 815-823, 1990