



## Impact of post-processing stages on vat-photopolymerized specimens

M. Ribo, M.; Danielak, A. H.; Andersen, S. A.; Üstünyagiz, E.; Islam, A.; Pedersen, D. B.

*Published in:*

Proceedings of the Joint Special Interest Group meeting between euspen and ASPE Advancing Precision in Additive Manufacturing (2019)

*Publication date:*

2019

*Document Version*

Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

*Citation (APA):*

M. Ribo, M., Danielak, A. H., Andersen, S. A., Üstünyagiz, E., Islam, A., & Pedersen, D. B. (2019). Impact of post-processing stages on vat-photopolymerized specimens. In A. Bernard, R. K. Leach, D. B. Pedersen, & J. S. Taylor (Eds.), *Proceedings of the Joint Special Interest Group meeting between euspen and ASPE Advancing Precision in Additive Manufacturing (2019)* (pp. 155). The European Society for Precision Engineering and Nanotechnology.

---

### General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

---

## Impact of post-processing stages on vat-photopolymerized specimens

M. M. Ribo<sup>1</sup>, A. H. Danielak<sup>1</sup>, S. A. Andersen<sup>1</sup>, E. Ustunygiz<sup>1</sup>, A. Islam<sup>1,2</sup>, D.B. Pedersen<sup>1</sup>

<sup>1</sup>Department of Mechanical Engineering, Technical University of Denmark, Denmark

<sup>2</sup>Centre for Acoustic-Mechanical Micro Systems, Technical University of Denmark, Denmark

[mmribo@mek.dtu.dk](mailto:mmribo@mek.dtu.dk)

---

### Abstract

Vat photopolymerization additive manufacturing (VPAM) is a technology with a promising future gaining interest from different industries and academic disciplines, such as biology, medicine, robotics and material science just to name a few<sup>1–5</sup>. To achieve repeatable, high-quality features, it is imperative to control all the stages of the VPAM manufacturing chain. At micro-scale, the post-processing procedure has a major impact on the part quality and mechanical properties<sup>6</sup>. The classic post-processing chain consists of an isopropanol rinse, ultrasound cycle, pressurized air dry and ultraviolet post-curing bath. Little has been found in the literature that covers each mentioned step, where the majority of studies solely cover the last phase, i.e. post-curing<sup>6–9</sup>. This work intends to quantify how each of these phases interact with each other and how it affects the final product in order to design a controlled post-processing routine that ensures the highest part quality.

A Placket-Burman design of experiments was used to study the main effect and interaction of six factors of the post-process. These factors are, time and temperature the specimen is under the ultrasonic bath, time and temperature in a vacuum dry oven, and time and temperature in the ultraviolet post-curing bath. The initial results indicated that the incorporation of vacuum drying guarantees greater stability throughout the shelf life of the samples, where a significant weight loss over time was observed on the parts dried only with pressurized air. The experimental post-processing routines with six variables showed significant differences on their mechanical properties and their surface quality. The main effect and interaction plots revealed that each variable sensitive to the change of the other factor's values, proving that each phase of the post-process is accountable for the performance of the final part.

---

### References

- [1] Mu, Q. *et al.* Digital light processing 3D printing of conductive complex structures. *Addit.Manuf.* **18**, 74–83 (2017).
- [2] Feilden, E. *et al.* 3D Printing Bioinspired Ceramic Composites. *Sci. Rep.* **7**, 13759 (2017).
- [2] Capel, A. J., Rimington, R. P., Lewis, M. P. & Christie, S. D. R. 3D printing for chemical, pharmaceutical and biological applications. *Nat. Rev. Chem.* **2**, 422–436 (2018).
- [4] Davoudinejad, A., Ribo, M. M., Pedersen, D. B., Islam, A. & Tosello, G. Direct fabrication of bio-inspired gecko-like geometries with vat polymerization additive manufacturing method. *J. Micromechanics Microengineering* **28**, 085009 (2018).
- [5] Francis, M. P., Kemper, N., Maghdouri-White, Y. & Thayer, N. Additive manufacturing for biofabricated medical device applications. *Addit. Manuf.* 311–344 (2018). doi:10.1016/B978-0-12-812155-9.00009-8
- [6] Salmoria, G. V., Ahrens, C. H., Fredel, M., Soldi, V. & Pires, A. T. N. Stereolithography somos 7110 resin: mechanical behavior and fractography of parts post-cured by different methods. *Polym. Test.* **24**, 157–162 (2005).
- [7] Salmoria, G. V., Ahrens, C. H., Beal, V. E., Pires, A. T. N. & Soldi, V. Evaluation of post-curing and laser manufacturing parameters on the properties of SOMOS 7110 photosensitive resin used in stereolithography. *Mater. Des.* **30**, 758–763 (2009).
- [8] Oakdale, J. S., Ye, J., Smith, W. L. & Biener, J. Post-print UV curing method for improving the mechanical properties of prototypes derived from two-photon lithography. *Opt. Express* **24**, 27077 (2016).
- [9] Chantarapanich, N. *et al.* Study of the Mechanical Properties of Photo-cured Epoxy Resin Fabricated by Stereolithography Process.