



Transport, Thermal Expansion and Redox Properties of $\text{Ce}_{0,80}\text{RE}_{0,20}\text{O}_2$ - (RE=Pr, Tb) Solid Solutions

Chatzichristodoulou, Christodoulos; Grivel, Jean-Claude; Hagen, Anke; Hendriksen, Peter Vang

Published in:
Meeting Abstracts - Electrochemical Society

Publication date:
2008

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Chatzichristodoulou, C., Grivel, J-C., Hagen, A., & Hendriksen, P. V. (2008). Transport, Thermal Expansion and Redox Properties of $\text{Ce}_{0,80}\text{RE}_{0,20}\text{O}_2$ - (RE=Pr, Tb) Solid Solutions. In *Meeting Abstracts - Electrochemical Society* (pp. Abstract 395). The Electrochemical Society.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Transport, thermal expansion and redox properties of $\text{Ce}_{0.80}\text{RE}_{0.20}\text{O}_{2-\delta}$ (RE=Pr, Tb) solid solutions

C. Chatzichristodoulou^{1,2}, J-C. Grivel¹, A. Hagen¹, P.V. Hendriksen¹

¹Risoe National Laboratory, DTU, Frederiksborgsvej 399, DK-4000 Roskilde, Denmark

²Niels Bohr Institute, University of Copenhagen, Blegdamsvej 17, DK-2100 Copenhagen, Denmark

The structure, thermal/chemical expansion coefficients, electronic conductivity and redox properties of $\text{Ce}_{0.80}\text{RE}_{0.20}\text{O}_{2-\delta}$ (RE=Pr, Tb) solid solutions, prepared by co-precipitation, are investigated. The thermal expansion coefficients range between $12 \cdot 10^{-6} \text{ K}^{-1}$ and $45 \cdot 10^{-6} \text{ K}^{-1}$ depending on temperature and composition, while the chemical expansion coefficients are in accordance to the Vegard's slope expected for the change in ionic radius due to reduction of the dopants. The electronic conductivity is measured as a function of the oxygen partial pressure in the range from 10^3 to 10^{-20} bar for temperatures between 600°C and 900°C , using the Hebb-Wagner polarization technique. The electronic conductivity is highest for the 20 at.% Pr doped composition, being significantly enhanced relative to that of CGO in the high- P_{O_2} regime. The valence of Pr and Tb are further investigated by XANES measurements of the Pr and Tb L3 white lines.