



## Possible dislocation configurations in slip-plane-aligned boundaries in fcc metals

Winther, Grethe; Huang, Xiaoxu; Hong, Chuanshi

*Publication date:*  
2012

*Document Version*  
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

*Citation (APA):*

Winther, G., Huang, X., & Hong, C. (2012). *Possible dislocation configurations in slip-plane-aligned boundaries in fcc metals*. Abstract from 4th International Conference on Fundamental Properties of Dislocations , Budapest, Hungary.

---

### General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

# Possible dislocation configurations in slip-plane-aligned boundaries in fcc metals

G. Winther<sup>1</sup>, X. Huang<sup>2</sup> and C.S. Hong<sup>2</sup>

<sup>1</sup> Department of Mechanical Engineering, Technical University of Denmark, DK-2800 Kgs. Lyngby, Denmark

<sup>2</sup> Danish-Chinese Center for Nanometals, Materials Science and Advanced Characterization Section, Department of Wind Energy, Technical University of Denmark, DK-4000 Roskilde, Denmark

---

**Keywords:** Frank equation, Burgers vectors, dislocation lines, slip systems

The deformation-induced extended planar dislocation boundaries in aluminium and copper deformed to medium strains ( $\epsilon < 1$ ) have preferred crystallographic alignments. The crystallographic planes of these boundaries depend on the grain orientation and the deformation mode [1]. In many cases two sets of low-angle planar boundaries, which align with the active slip planes, are formed. This is, for example, the case for grains belonging to the  $\alpha$ -fibre of the rolling texture, spanning from the Goss to the Brass orientation. Slip-plane-aligned boundaries are also typical for other orientations, e.g. the rolled 45° ND-rotated Cube orientation. These grain orientations all have four active slip systems, distributed on two slip planes, which is assumed to be the reason for the characteristic slip-plane-alignment of the boundaries [2].

The planar boundaries have been suggested to be low-energy-dislocation-structures (LEDS) free of long-range stresses, i.e. the Frank equation should apply [3]:

$$\sum \frac{1}{D_i} \mathbf{b}_i \{(\mathbf{n} \times \boldsymbol{\xi}_i) \cdot \mathbf{V}\} = 2 \sin \theta / 2 \mathbf{V} \times \mathbf{a}$$

where  $\mathbf{b}_i$ ,  $\boldsymbol{\xi}_i$  and  $D_i$  are Burgers vector, line direction and spacing of dislocation set  $i$ ,  $\mathbf{n}$  the boundary plane normal, and  $\mathbf{V} \perp \mathbf{n}$ . The misorientation is the axis/angle pair  $\mathbf{a} / \theta$ .

Aiming at investigating the origin of the preferred slip-plane-alignment, a theoretical analysis is conducted of the possible Frank boundaries constructed from dislocations gliding on the active systems. In addition, the boundaries are regarded geometrically necessary by accommodating local differences in slip activities so that strain compatibility as well as the lattice misorientation across the boundaries must be considered.

## References:

[1] X. Huang and G. Winther, *Phil. Mag.* (2007) 83 , 5189-5214.

[2] G. Winther and X. Huang, *Phil. Mag.* (2007) 83 , 5215-5235.

[3] F. Frank, *Phil. Mag.* (1951) 42, 809-819.