



Novel block, graft and random copolymers for biomedical applications

Javakhishvili, Irakli; Jankova Atanasova, Katja; Tanaka, Masaru; Hvilsted, Søren

Publication date:
2011

[Link back to DTU Orbit](#)

Citation (APA):

Javakhishvili, I., Jankova Atanasova, K., Tanaka, M., & Hvilsted, S. (2011). *Novel block, graft and random copolymers for biomedical applications*. Abstract from Nordic Polymer Days 2011, Stockholm, Sweden. <http://www.kth.se/en/che/konferens/npd2011/nordic-polymer-days-june-15-17-2011-1.72785>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.


Novel block, graft and random copolymers for biomedical applications

Irakli Javakhishvili¹, Katja Jankova¹, Masaru Tanaka², Søren Hvilsted¹

Danish Polymer Centre, Department of Chemical and Biochemical Engineering, Technical University of Denmark, DK-2800 Kgs. Lyngby¹; Department of Biochemical Engineering, Graduate School of Science and Technology, Yamagata University, Yonezawa 992-8510, Japan²

kaj@kt.dtu.dk

Despite the simple structure, poly(2-methoxyethyl acrylate) (PMEA) shows excellent blood compatibility [1]. Both the freezing-bound water (intermediate water: preventing the biocomponents from directly contacting the polymer surface) and non-freezing water on the polymer surface play important roles for this [2]. An artificial lung (oxygenator), already in use, is coated with high MW PMEA prepared by radical polymerization with AIBN [2]. To broaden the possibilities for designing biomedical devices [3] and inspired from these findings we first prepared homo polymers of MEA and their block copolymers with MMA [4] utilizing ATRP. Here we present other block, graft and random copolymers of MEA intended for biomedical applications. These macromolecular architectures have been constructed by employing controlled radical polymerization methods such as RAFT and ATRP.



Scheme 1 Synthetic strategies for the design of novel graft and random copolymers of MEA

References

- [1]. M. Tanaka et al. *Biomaterials*, **2000**, *21*, 1471-1481.; *Biomacromolecules* **2002**, *3*, 36-41.
- [2]. M. Tanaka, A. Mochizuki. *J. Biomed. Mater. Res.* **2004**, *68A*, 684-695.; *J. Biomater. Sci. Polym. Edn.* **2010**, *21*, 1849-1863.
- [3]. C.J. Fristrup, K. Jankova, S. Hvilsted. *Soft Matter* **2009**, *5*, 4623-4634.
- [4]. M. Bednarek, K. Jankova, S. Hvilsted. *J. Polym.Sci.: Polym. Chem.* **2007**, *45*, 333-340.