



A high-mobility two-dimensional electron gas at the spinel/perovskite interface of γ - $\text{Al}_2\text{O}_3/\text{SrTiO}_3$ grown by pulsed laser deposition

Chen, Yunzhong; Pryds, Nini

Publication date:
2013

[Link back to DTU Orbit](#)

Citation (APA):

Chen, Y., & Pryds, N. (2013). A high-mobility two-dimensional electron gas at the spinel/perovskite interface of γ - $\text{Al}_2\text{O}_3/\text{SrTiO}_3$ grown by pulsed laser deposition. Abstract from 12th International Conference on Laser Ablation (COLA³2013), Ischia, Italy.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

A high-mobility two-dimensional electron gas at the spinel/perovskite interface of γ -Al₂O₃/SrTiO₃ grown by pulsed laser deposition

Yunzhong Chen*, Nini Pryds

Department of Energy Conversion and Storage, Technical University of Denmark, Risø Campus, 4000 Roskilde, Denmark

Email: yunc@dtu.dk, web site: <http://www.ecs.dtu.dk/English.aspx>

The realization of high-mobility 2DEGs in epitaxially grown heterostructures made of traditional semiconductors is at the heart of present electronics, which has led to a wealth of new physical phenomena as well as new electronic and photonic devices over the past few decades. Recently, high-mobility 2DEGs discovered at the interface between insulating complex oxides provide new opportunities for electronics [1]. Thanks to the strong electronic correlations, oxide 2DEGs not only provide the possibility of multifunctional all-oxide devices with probably even richer behavior than those we experienced in semiconductor devices, but also show the promise to study mesoscopic physics with strongly correlated electrons confined in nanostructures.

So far, complex oxide 2DEGs are nearly exclusively created within the frame of interface polarity, such as the intensively explored LaAlO₃/SrTiO₃ (LAO/STO) heterointerface [2]. Moreover, the carrier mobilities of such oxide interfaces are still several orders lower than that of bulk materials, such as the reduced STO substrate. The low carrier mobility has been assumed to result from, at least partially, the bombardment of the energetic plasma during the pulsed laser deposition (PLD) process. In this presentation, we will firstly show that the reactivity of PLD plasma rather than its kinetic energy can be used to design metallic and insulating interfaces between two insulating oxides by tunable interface redox reactions [3]. Secondly, we will present a new type of oxide 2DEGs created at a nonpolar spinel/perovskite interface of γ -Al₂O₃/SrTiO₃ (GAO/STO). Remarkably, this novel GAO/STO oxide 2DEG grown by PLD exhibits electron mobilities exceeding 100,000 cm²V⁻¹s⁻¹ at 2 K [4], which is 100 times higher than those of LAO/STO heterointerfaces. The dimensionality of the conduction and its spatial confinement at this spinel/perovskite GAO/STO interface will be also discussed. Defect engineering of oxygen vacancies, especially interfacial redox reactions with strongly spatial confinement, turns out to be a crucial issue for the high-mobility 2DEG at the interface between insulating complex oxides.

[1] J. Mannhart and D. G. Schlom, *Science* **327**, 1607-1611 (2010).

[2] A. Ohtomo and H. Y. Hwang, *Nature* **427**, 423-426 (2004).

[3] Y. Z. Chen *et al.*, *Nano Lett.* **11**, 3774 (2011).

[4] Y. Z. Chen *et al.* *Nat. Commun.* **4**:1371 doi: 10.1038/ncomms2394 (2013).