



Evaluation of infiltrated $\text{Bi}_2\text{V}_{0.9}\text{Cu}_{0.1}\text{O}_{5.35}$, $\text{Ce}_{0.9}\text{Gd}_{0.1}\text{O}_{1.95}$ and $\text{Bi}_2\text{V}_{0.9}\text{Cu}_{0.1}\text{O}_{5.35}$ -based composite cathodes for solid oxide fuel cells

Samson, Alfred Junio; Søgaard, Martin; Bonanos, Nikolaos

Published in:
Abstract book

Publication date:
2011

Document Version
Peer reviewed version

[Link back to DTU Orbit](#)

Citation (APA):
Samson, A. J., Søgaard, M., & Bonanos, N. (2011). Evaluation of infiltrated $\text{Bi}_2\text{V}_{0.9}\text{Cu}_{0.1}\text{O}_{5.35}$, $\text{Ce}_{0.9}\text{Gd}_{0.1}\text{O}_{1.95}$ and $\text{Bi}_2\text{V}_{0.9}\text{Cu}_{0.1}\text{O}_{5.35}$ -based composite cathodes for solid oxide fuel cells. In *Abstract book* (pp. 138-138)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

EVALUATION OF INFILTRATED $\text{Bi}_2\text{V}_{0.9}\text{Cu}_{0.1}\text{O}_{5.35}$, $\text{Ce}_{0.9}\text{Gd}_{0.1}\text{O}_{1.95}$ AND $\text{Bi}_2\text{V}_{0.9}\text{Cu}_{0.1}\text{O}_{5.35}$ – BASED COMPOSITE CATHODES FOR SOLID OXIDE FUEL CELLS

Alfred Samson,^{1*} Martin Søggaard,¹ and Nikolaos Bonanos¹

¹ Fuel Cells and Solid State Chemistry Division, Risø National Laboratory for Sustainable Energy, Technical University of Denmark, Frederiksborgvej 399, DK-4000, Roskilde, Denmark

*asam@risoe.dtu.dk

Keywords: $\text{Bi}_2\text{V}_{0.9}\text{Cu}_{0.1}\text{O}_{5.35}$, infiltration, cathode, SOFC

Introduction

The compound $\text{Bi}_2\text{V}_{0.9}\text{Cu}_{0.1}\text{O}_{5.35}$ (BICUVOX) exhibits very high oxide ion conductivities – about two orders of magnitude higher than that of other oxide ion conductors at low temperatures (<500°C) [1]. In a solid oxide fuel cell cathode where high ionic conductivity, high catalytic activity and high electronic conductivity are essential, it is possible to use BICUVOX as an ion conducting component in a composite. However, the choice of BICUVOX in this way is restricted by its micro-structural instability and reaction with other cell components during processing and during operation at high temperatures. A way to mitigate the problem of reactivity of BICUVOX with other materials is to separate the processing of BICUVOX with that of the desired electro-catalyst. This can be accomplished through an infiltration method. In this technique, a liquid solution usually composed of dissolved metal nitrates is introduced into a backbone followed by firing. The present study investigates the electrochemical performance of cathodes prepared using a BICUVOX backbone that is infiltrated with $\text{La}_{0.6}\text{Sr}_{0.4}\text{CoO}_{3-\delta}$ (LSC40). The performance of the cathodes is investigated as a function of firing temperature of the BICUVOX backbone and the number of infiltrations. The obtained results are compared to high performance electrodes prepared by infiltrating LSC40 into a $\text{Ce}_{0.9}\text{Gd}_{0.1}\text{O}_{1.95}$ (CGO10) backbone [2]. Theoretically, the replacement of CGO10 with a much higher ionic conductivity BICUVOX should result in a much higher performance cathode.

Experimental

The starting BICUVOX material was prepared by conventional solid-state synthesis. The electrical conductivity of a dense BICUVOX sample was measured using an ac four-point impedance measurement technique. Porous backbones (BICUVOX and BICUVOX-CGO10, 50:50 vol%) for infiltration were prepared by screen printing onto a dense CGO10 electrolyte followed by firing. The backbones were infiltrated multiple times with LSC40 and PdCo(40%) followed by firing. The electrochemical performance and chemical compatibility among the materials were investigated.

Results and Discussion

The total conductivity of the BICUVOX at 500°C was measured to 0.057 S cm^{-1} which is approximately 10 times higher than CGO10 at this temperature. A firing

temperature greater than 800°C was necessary to ensure adhesion to the dense CGO10 electrolyte. However, at this high temperature the BICUVOX loses porosity due to extensive sintering. From scanning electron microscopy and X-ray diffraction the formation of several phases was revealed. The polarization resistances (R_p) at 500°C, measured using electrochemical impedance spectroscopy on symmetrical cells in ambient air were $41 \Omega \text{ cm}^2$ and $49 \Omega \text{ cm}^2$ for BICUVOX backbones infiltrated 6 times with LSC40 and PdCo40 (all fired at 500°C), respectively. These values are approximately 100 times higher than the one obtained for the CGO10 backbone infiltrated with the same amount of LSC40[2]. The values of R_p as function of the reciprocal absolute temperature are shown in Fig. 1. The inferior cathode performance using BICUVOX backbones is attributed to a poor microstructure and the chemical reactivity with the dense CGO10 electrolyte and with the infiltrated material.




Fig. 1 Polarization resistance, R_p , as a function of the reciprocal absolute temperature for all the infiltrated cathodes. The infiltrated materials were fired at 500°C.

Conclusions

The study has investigated the use of BICUVOX as a backbone material for infiltration. The polarization resistance of the electrode prepared with the BICUVOX backbone was approximately a factor of 100 higher than that of a corresponding electrode prepared using a CGO10 backbone. The poor performance of the BICUVOX backbone is attributed to a coarse microstructure and chemical reaction between the BICUVOX and electrolyte/electro-catalyst.

References

- [1] J.C. Boivin et al., *Chem. Mater.*, 10 (1998) 2870.
- [2] A. Samson et al., submitted to *J. Electrochem Soc.*