



Outdoor Operational Stability of Indium-Free Flexible Polymer Solar Modules Over 1 Year Studied in India, Holland, and Denmark

Angmo, Dechan; Sommeling, Paul M.; Gupta, Ritu; Hösel, Markus; Gevorgyan, Suren; Kroon, Jan M.; Kulkarni, Giridhar U.; Krebs, Frederik C

Publication date:
2014

[Link back to DTU Orbit](#)

Citation (APA):

Angmo, D., Sommeling, P. M., Gupta, R., Hösel, M., Gevorgyan, S., Kroon, J. M., Kulkarni, G. U., & Krebs, F. C. (2014). Outdoor Operational Stability of Indium-Free Flexible Polymer Solar Modules Over 1 Year Studied in India, Holland, and Denmark. Sound/Visual production (digital)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Outdoor Operational Stability of Indium-free Polymer Solar Cell Modules Investigated over 1 year

Dechan Angmo, Ph.D.,
Department of Energy Conversion
Technical University of Denmark

ICCES-2
April 15, 2014
Qingdao, China

In Summary



- Low-cost encapsulation method is demonstrated.
- The method is roll-to-roll compatible.
- Decay in photovoltaic is due to localized defects
 - the edge cross, contacts, and uneven adhesive thickness → O_2 and H_2O infiltration
 - results in PEDOT:PSS degradation/delamination
 - Photooxidation of photoactive polymer → not the main cause of degradation
- Simple design changes → performance is dramatically enhanced ($MPP_{t=0}$ equal $MPP_{t=1 \text{ year}}$)
 - Defects due to edges and uneven adhesive thickness is eliminated
 - Defects due to contacting method persist

Hösel, M., Søndergaard, R. R., Jørgensen, M. and Krebs, F. C. (2013), *Adv. Eng. Mater.*, 15: 1068–1075.

Angmo, Dechan, et al. *Adv. Eng. Mat.* (2014). In Press

Contributors

Paul M. Sommeling and Dr. Jan M. Kroon

ECN Solar Energy, Petten, Netherlands

Dr. Ritu Gupta, Prof. Giridhar U. Kulkarni

Chemistry and Physics of Materials Unit and DST Unit on Nanoscience

Jawaharlal Nehru Centre for Advanced Scientific Research, Bangalore, India

Dr. Suren A. Gevorgyan, Dr. Markus Hösel, Prof. Frederik C. Krebs

Department of Energy Conversion and Storage, Technical University of Denmark, Roskilde,
Denmark

www.coursera.org/course/opv

www.plasticphotovoltaics.com