



Functionalization of PEDOT by Click Chemistry and ATRP

Hoffmann, Christian; Daugaard, Anders Egede

Publication date:
2012

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):

Hoffmann, C., & Daugaard, A. E. (2012). *Functionalization of PEDOT by Click Chemistry and ATRP*. Poster session presented at 49th Nordic Polymer Days 2012, Copenhagen, Denmark.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Abstract Poly(3,4-ethylenedioxythiophene) (PEDOT) is a conductive polymer which has received increasing attention and many developments have been investigated. PEDOT has been applied in many different areas such as biosensors or polymer solar cells. This work presents a modification of PEDOT films through Click Chemistry with alkynes followed by activator regenerated by electron transfer (ARGET) atom transfer radical polymerization (ATRP) to develop PEDOT films with anti-fouling properties through application of a model system based on a crosslinked surface of polystyrene PS-N₃.

Introduction

Conductive polymers demonstrate a material sector of high interest which has been grown during the last few years. Many investigations have been conducted in order to develop the properties and application fields of conductive polymers.

One representative is poly(3,4-ethylenedioxythiophene) (PEDOT) which has become an important polymer in many applications such as in biosensors¹ or polymer solar cells².

The recently discovered PEDOT-N₃ films^{3,4} can be modified through click chemistry with different alkynes, which leads to an open range of functional groups on the conductive polymer backbone especially applications in sensing control over fouling properties are essential. Poly(ethylene glycol)methacrylate (PEGMA) is an important monomer for ATRP reactions which has shown good antifouling properties.

The presented study is focused on the application of ARGET ATRP to produce anti-fouling surfaces on PEDOT. Initial results on PEDOT and a model system is presented. "Grafting to" processes have earlier been tested and the presented work is compared to these results^{3,5}. Furthermore a solution to confirm the validity of the method is an ARGET ATRP system with PEGMA, which has been tested. The presented work has been performed as a bachelor work at DTU.

Surface coating




Figure 1. Functionalization of PEDOT-N₃ film with initiators, which subsequently was grafted through ATRP.

As already tested and reported the polymerization under normal ATRP conditions in an inert atmosphere has been successfully performed.

The advantage of ARGET ATRP is the use of a normal instead of an inert and closed atmosphere.

Due to its self-fluorescence it is difficult to determine the inhibition of protein adsorption of the PEDOT films using fluorescence measurements. For this reason a PS film modified with covalent bonded azide groups on the surface (PS-N₃) has been used for functionalization and further ARGET ATRP reaction.




Figure 2. Preparation and functionalization of PS-N₃ film with initiator, which was subsequently grafted through ARGET ATRP

ATRP study

A well system has been designed to carry out the surface modification. This implies a non inert atmosphere, which should be suitable for ARGET ATRP.

The ARGET ATRP reaction in solution was tested to investigate the stability of the reaction in an open vessel.

The polymerization of PEGMA was performed through ARGET ATRP in water / methanol or pure methanol as solvents.




Figure 3. ARGET ATRP of poly(ethylene glycol) methacrylate (PEGMA) with Poly(ethylene glycol) methyl ether 2-bromoisobutyrate as initiator and CuCl₂ / Tris(2-pyridyl)methyl)amine (TPMA) as a catalyst system and sodium ascorbate as a reducing agent

By varying of the molar ratios (monomer : Cu²⁺, initiator : Cu²⁺ and ascorbic acid : Cu²⁺) and the reaction time the most promising reaction in terms of a controlled reaction were investigated.

The reactions have been carried out in microplate wells under UV-VIS absorption measurements. Molecular weight distribution was determined by size exclusion chromatography (SEC).

PEGMA	Initiator	Cu ²⁺	TPMA	Sodium ascorbate	reaction time / min	solvent
1800	10	1	2,5	5	20 / 60	H ₂ O/MeOH (2:1) or MeOH
1800	10	1	2,5	10	20 / 60 / 120	H ₂ O/MeOH (2:1) or MeOH
1800	10	1	2,5	20	20 / 60 / 120	H ₂ O/MeOH (2:1) or MeOH
1800	10	1	2,5	40	20 / 60 / 120	H ₂ O/MeOH (2:1) or MeOH
7000	80	1	2,5	5	20 / 60	H ₂ O/MeOH (2:1) or MeOH
18000	90	1	2,5	20	20 / 60 / 90	H ₂ O/MeOH (2:1) or MeOH
18000	90	1	2,5	40	20 / 60 / 90	H ₂ O/MeOH (2:1) or MeOH

Table 1. Variation of molar ratios and reaction time for the ARGET ATRP reaction of PEGMA

SEC analysis show a relatively uncontrolled reaction. Polymers with a M_n=70000 have been observed and a polydispersity of 1,9 – 2,2. Many reactions result in polymer precipitation, which shows that the polymerization takes place. However a lack of control was investigated through a number of reactions. An impurity of dimer in the monomer is believed to be the source of crosslinking polymerization.

Since the scope is surface reactions and crosslinking systems tend to better antifouling properties the work was continued by introducing this reaction on the surface.

Model system for surface grafting

In the first step PS-N₃ films were initialized through the reaction with prop-2-yn-1-yl 2-bromo-2-methylpropanoate, as an alkyne functional initiator which has been determined by FT-IR spectroscopical measurements.




Figure 4. FT-IR spectroscopy of the polystyrene films before and after introducing of the ATRP initiator, red: not initialized film, blue: initialized film

The IR measurements clearly show the reaction of the azide groups with the initiator by disappearing of the band at 2100 cm⁻¹, which belongs to the free azides.

After the polymerization procedure the reaction mixtures have been exposed with fluorescent Albumin from bovine serum. The anti-fouling properties have been determined by fluorescence measurements.




Figure 5. Left: ARGET ATRP system in microplate wells

Right: Fluorescence measurements after the samples have been exposed with the protein solution

To establish the surface changes of the polymerized films FT-IR spectroscopy has been used, which show no change in comparison to the initiated surface.

Conclusions

- Polymer synthesis with ATRP was not controlled
- Polymer precipitation leads to the assumption of cross linking reactions, which guide to a better suppression of protein adsorption as already published
- Film initialization with "Click Chemistry" was successful
- Surface polymerization with ARGET ATRP was not successful
- No advantage in terms of protein adsorption

Perspective

The applied method has not provided surfaces with improved antifouling properties compared to the raw polymer surface. These results lead to a more detailed study with different types of monomers and varying of important reaction parameters such as reaction time, ratios between the reactants or the selection of a different system.

Furthermore the change from the PS model system to the PEDOT system is the next step. Investigations for the detection of the protein adsorption needs to be conducted.

Acknowledgment

The Danish Council for Independent Research Technology and Production Sciences (grant 11-10-5986) is thanked for financial support.

References

- (1) Luo, S.-chyang; Ali, E. M.; Tansil, N. C.; Yu, H.-hua; Gao, S.; Kantchev, E. A. B.; Ying, J. Y. *Society* **2008**, 8071-8077.
- (2) Krebs, F. C.; Gevorgyan, S. a.; Alstrup, J. *Journal of Materials Chemistry* **2009**, 19, 5442.
- (3) Daugaard, A. E.; Hvilsted, S.; D.-K.; Hansen, T. S.; Larsen, N. B. *Macromolecules* **2008**, 41, 4321-4327.
- (4) Bu, H.-B.; Götz, G.; Reinold, E.; Vogt, A.; Schmid, S.; Blanco, R.; Segura, J. L.; Bäuerle, P. *Chemical communications* **2008**, 1320-2.
- (5) Hansen, T. S.; Daugaard, A. E.; Hvilsted, S.; Larsen, N. B. *Advanced Materials* **2009**, 21, 4483-4486.